US 20140364548A1

(19) **United States**

(12) **Patent Application Publication**

(10) **Pub. No.: US 2014/0364548 A1**

(43) **Pub. Date: Dec. 11, 2014**

EVERHARDUS et al.

(54) **INK COMPOSITION**

(71) Applicant: **OCE-TECHNOLOGIES B.V.**, Venlo (NL)

(72) Inventors: **Roelof H. EVERHARDUS**, Lomm (NL); **Gerardus C. P. VERCOULEN**, Velden (NL); **Johannes F. J. VAN GAGELDONK**, Venlo (NL); **Johan P. J. LENDERS**, Leveroy (NL); **Antonius P. M. M. VAN ROY**, Grashoek (NL)

(21) Appl. No.: **14/465,917**

(22) Filed: **Aug. 22, 2014**

Related U.S. Application Data

(63) Continuation of application No. PCT/EP2013/054432, filed on Mar. 5, 2013.

(30) **Foreign Application Priority Data**

Mar. 6, 2012 (EP) 12158219.1

Publication Classification

(51) **Int. Cl.**

C09D 11/38 (2006.01)

C08K 13/00 (2006.01)

(52) **U.S. Cl.**

CPC ***C09D 11/38*** (2013.01); ***C08K 13/00*** (2013.01)

USPC **524/166**; 524/377; 524/265

(57) **ABSTRACT**

The present invention relates to an ink composition suitable for being ejected from an inkjet marking device at an operating temperature. The ink composition comprises a water-dispersible resin and has a dynamic surface tension of below 35 mN/m and a static surface tension of above 21 mN/m both determined at the operating temperature. The ink composition may comprise a mixture of water-soluble organic solvents having a difference in the relative dielectric constant of more than 5, preferably between 10 and 50. The ink composition may comprise a polymeric cosolvent, in particular a polyethylene glycol or polyethylene glycol (di)methyl ether. The ink composition may comprise a mixture of surfactants comprising at least one surfactant of a first type selected from the group consisting of acetylene glycols and ethoxylated acetylene glycols and at least one surfactant of a second type selected from the group consisting of silicone surfactants and fluorochemical surfactants.