

such as dip, puddle or spray techniques. Suitable developers are 0.1 to 10 wt %, preferably 2 to 10 wt %, more preferably 2 to 8 wt % aqueous solutions of tetramethylammonium hydroxide (TMAH), tetraethylammonium hydroxide (TEAH), tetrapropylammonium hydroxide (TPAH) and tetrabutylammonium hydroxide (TBAH). The resist film in the exposed area is dissolved in the developer whereas the resist film in the unexposed area is not dissolved. In this way, the desired positive pattern is formed on the substrate. It is appreciated that the resist composition of the invention is best suited for micro-patterning using such high-energy radiation as EB, EUV (soft x-ray), x-ray,  $\gamma$ -ray and synchrotron radiation among others.

Although TMAH aqueous solution is generally used as the developer, TEAH, TPAH and TBAH having a longer alkyl chain are effective in inhibiting the resist film from being swollen during development and thus preventing pattern collapse. JP 3429592 describes an example using an aqueous TBAH solution for the development of a polymer comprising recurring units having an alicyclic structure such as adamantane methacrylate and recurring units having an acid labile group such as t-butyl methacrylate, the polymer being water repellent due to the absence of hydrophilic groups.

The TMAH developer is most often used as 2.38 wt % aqueous solution, which corresponds to 0.26N. The TEAH, TPAH, and TBAH aqueous solutions should preferably have an equivalent normality. The concentration of TEAH, TPAH, and TBAH that corresponds to 0.26N is 3.84 wt %, 5.31 wt %, and 6.78 wt %, respectively.

When a pattern with a line size of 32 nm or less is resolved by the EB and EUV lithography, there arises a phenomenon that lines become wavy, lines merge together, and merged lines collapse. It is believed that this phenomenon occurs because lines are swollen in the developer and the thus expanded lines merge together. Since the swollen lines containing liquid developer are as soft as sponge, they readily collapse under the stress of rinsing. For this reason, the developer using a long-chain alkyl developing agent is effective for preventing film swell and hence, pattern collapse.

Alternatively, a negative tone pattern may be formed by organic solvent development. The organic solvent used as the developer is preferably selected from 2-octanone, 2-nonanone, 2-heptanone, 3-heptanone, 4-heptanone, 2-hexanone, 3-hexanone, diisobutyl ketone, methylcyclohexanone, acetophenone, methylacetophenone, propyl acetate, butyl acetate, isobutyl acetate, amyl acetate, isoamyl acetate, butenyl acetate, phenyl acetate, propyl formate, butyl formate, isobutyl formate, amyl formate, isoamyl formate, methyl valerate, methyl pentenoate, methyl crotonate, ethyl crotonate, methyl propionate, ethyl propionate, ethyl 3-ethoxypropionate, methyl lactate, ethyl lactate, propyl lactate, butyl lactate, isobutyl lactate, amyl lactate, isoamyl lactate, methyl 2-hydroxyisobutyrate, ethyl 2-hydroxyisobutyrate, methyl benzoate, ethyl benzoate, benzyl acetate, methyl phenylacetate, benzyl formate, phenylethyl formate, methyl 3-phenylpropionate, benzyl propionate, ethyl phenylacetate, and 2-phenylethyl acetate. These organic solvents may be used alone or in admixture of two or more.

At the end of organic solvent development, the resist film is rinsed. As the rinsing liquid, a solvent which is miscible with the developer and does not dissolve the resist film is preferred. Suitable solvents include alcohols of 3 to 10 carbon atoms, ether compounds of 8 to 12 carbon atoms, alkanes, alkenes, and alkynes of 6 to 12 carbon atoms, and aromatic solvents. Specifically, suitable alkanes of 6 to 12 carbon atoms include hexane, heptane, octane, nonane, decane, undecane, dodecane, methylcyclopentane, dimethylcyclopentane, cyclohex-

ane, methylcyclohexane, dimethylcyclohexane, cycloheptane, cyclooctane, and cyclononane. Suitable alkenes of 6 to 12 carbon atoms include hexene, heptene, octene, cyclohexene, methylcyclohexene, dimethylcyclohexene, cycloheptene, and cyclooctene. Suitable alkynes of 6 to 12 carbon atoms include hexyne, heptyne, and octyne. Suitable alcohols of 3 to 10 carbon atoms include n-propyl alcohol, isopropyl alcohol, 1-butyl alcohol, 2-butyl alcohol, isobutyl alcohol, tert-butyl alcohol, 1-pentanol, 2-pentanol, 3-pentanol, tert-amyl alcohol, neopentyl alcohol, 2-methyl-1-butanol, 3-methyl-1-butanol, 3-methyl-3-pentanol, cyclopentanol, 1-hexanol, 2-hexanol, 3-hexanol, 2,3-dimethyl-2-butanol, 3,3-dimethyl-1-butanol, 3,3-dimethyl-2-butanol, 2-ethyl-1-butanol, 2-methyl-1-pentanol, 2-methyl-2-pentanol, 2-methyl-3-pentanol, 3-methyl-1-pentanol, 3-methyl-2-pentanol, 3-methyl-3-pentanol, 4-methyl-1-pentanol, 4-methyl-2-pentanol, 4-methyl-3-pentanol, cyclohexanol, and 1-octanol. Suitable ether compounds of 8 to 12 carbon atoms include di-n-butyl ether, diisobutyl ether, di-sec-butyl ether, di-n-pentyl ether, diisopentyl ether, di-sec-pentyl ether, di-tert-amyl ether, and di-n-hexyl ether. The solvents may be used alone or in admixture. Besides the foregoing solvents, aromatic solvents may be used, for example, toluene, xylene, ethylbenzene, isopropylbenzene, tert-butylbenzene and mesitylene.

### Example

Examples and Comparative Examples are given below for further illustrating the invention, but they should not be construed as limiting the invention thereto. Mw is a weight average molecular weight as measured by GPC versus polystyrene standards, and Mw/Mn designates molecular weight distribution or dispersity. All parts (pbw) are by weight.


### Preparation of Polymers

Various polymers (Polymers 1 to 7) to be added to resist compositions were prepared by combining suitable monomers, effecting copolymerization reaction in methyl ethyl ketone solvent, pouring into hexane for crystallization, repeatedly washing with hexane, isolation, and drying. The polymers were analyzed by  $^1\text{H-NMR}$  to determine their composition and by GPC to determine Mw and dispersity Mw/Mn.

#### Polymer 1

Mw=8,300

Mw/Mn=1.85



Polymer 1