

50 g · BX-01 Closed Cell

BEST

Pour this first. **50.00 g B (5.00 g HFO in) + 41.40 g A**. Not 1:1. Write which high-OH drum and which flow drum. Mix 4–5 s. Weigh to 0.01 g.

Cup	
B-side (HFO in)	50.00 g
HFO-1233zd(E)	5.00 g · last, 15–18 °C, cap
A-side PMDI 31.0 % NCO	41.40 g · index 125
Water in this cup	0.60 g → 11.29 g of the A-side
Polyols in this cup	35.05 g → 30.11 g of the A-side

Trial header	
Date / operator	
High-OH drum	TB-307 or PE 104
Flow drum	TEROL 250 or PE 103
PMDI lot / %NCO	
Cup ID	BX-01-50-

Weigh sheet · order as listed

#	INGREDIENT	PBW	TARGET G	ACTUAL G
1	TB-307 or PE 104 — write which	41.3	20.65	
2	TEROL 250 or PE 103 — write which	24.8	12.40	
3	CREAPOL PD 230	4.0	2.00	
4	TCPP lot XLT20260701	6.0	3.00	
5	TEP	4.0	2.00	
6	Reactive FR	2.0	1.00	
7	Emulsifier	1.75	0.875	
8	Closed-cell silicone	1.5	0.75	
9	Water	1.20	0.60	
10	PC-15	1.45	0.725	
11	DABCO 2040	1.10	0.550	
12	CAT-T	0.55	0.275	
13	PC-37	0.35	0.175	
14	HFO-1233zd(E) — last, cold, cap	10.0	5.00	
	B-side	100.00	50.000	
A	PMDI, 31.0 % NCO	82.8	41.40	

Pour	
☐	Hood on · A 21–23 °C · B 15–18 °C after HFO
☐	Closed-cell silicone · no K-15 / DMCHA / sucrose
☐	HFO 5.00 g last · cap · A 41.40 g
☐	A into B · 4–5 s · 2 500–3 000 rpm · do not touch after cream

Record	
Cream / gel / rise / tack-free	s 3–6 / 8–15 / — / 15–28
Density	kg/m³ 32–38
Shrink / scorch / cells	

If HFO flashes off, recap and reweigh — do not add water. If the flow drum is TEROL 250 at EW 224.4, A ≈ 41.05 g. Open-cell 50 g is the next sheet.

50 g · BX-02 Open Cell

BEST

Only if sucrose is on the floor. **50.00 g B + 65.65 g A** at index 105. No HFO. Do not blend with BX-01 or OC-01.

Cup	
B-side	50.00 g
A-side PMDI 31.0 % NCO	65.65 g · index 105
Water in this cup	2.60 g → 41.10 g of the A-side
Polyols in this cup	27.00 g → 24.55 g of the A-side
Sucrose OH assumed	400 · re-index if the lot differs

Trial header	
Date / operator	
Sucrose grade / OH#	
Flow drum	TEROL 250 or PE 103
PMDI lot / %NCO	
Cup ID	BX-02-50-

Weigh sheet · order as listed

#	INGREDIENT	PBW	TARGET G	ACTUAL G
1	Sucrose / sucrose polyol	38.0	19.00	
2	TEROL 250 or PE 103 — write which	16.0	8.00	
3	TEP	20.9	10.45	
4	Reactive FR	7.0	3.50	
5	Ecosurf SA-9	4.0	2.00	
6	Open-cell silicone	1.5	0.75	
7	Water	5.2	2.60	
8	PC-37	1.70	0.85	
9	CAT-T	1.60	0.80	
10	PC-15	2.80	1.40	
11	BDMAEE or DEDEE	0.90	0.45	
12	Biocide	0.40	0.20	
	B-side	100.00	50.00	
A	PMDI, 31.0 % NCO	131.3	65.65	

Pour	
☐ A and B 21–23 °C · open-cell silicone only	
☐ No HFO · A 65.65 g (or re-indexed)	
☐ A into B · 4–5 s · do not touch after cream	
☐ If windows stay closed: +0.20 g water or –0.10 g PC-15	

Record	
Cream / rise / tack-free	s target cream 2–4
Density	kg/m³ 16–22
Cells	open / tight / collapse

If sucrose OH is 350, A ≈ 62 g. If 450, A ≈ 70 g. Do not pour 1:1. Memo screen OC-01 is the next sheet — do not blend the B-sides.

50 g · OC-01 Memo Screen

High-water System C. Not the best card. **50.00 g B + 196.6 g A** at index 100. A 1:1 shot is index ≈ 25 and is invalid. No HFO.

A-side · water then sucrose
Water $12.00 \div 9.0 = 1.3333$ eq $\rightarrow$ **180.67 g** PMDI
Sucrose $16.50 \cdot \text{OH } 400 \cdot \text{EW } 140.25 \rightarrow 0.1176$ eq $\rightarrow$ **15.94 g** PMDI
Index 100 = **196.6 g A**. Index 90 = 176.9 g · index 105 = 206.4 g.

Do not pour 1:1
The old 20–28 g A charge never paid the water. 100 g B needs 393 g A. Pour BX-02 first if sucrose is on the floor.

Weigh sheet · 50.00 g B

INGREDIENT	PBW	TARGET G	ACTUAL G	INGREDIENT	PBW	TARGET G	ACTUAL G
Sucrose / sucrose polyol	33.0	16.50		Reactive FR	8.0	4.00	
TEP	17.0	8.50		Ecosurf SA-9	6.0	3.00	
Open-cell silicone	1.2	0.60		Water	24.0	12.00	
PC-37	2.4	1.20		CAT-T	2.4	1.20	
PC-15	4.2	2.10		BDMAEE / biocide	1.0 / 0.8	0.50 / 0.40	
B-side	100.0	50.00		A-side PMDI		196.6	

Pour
☐ A and B 21–23 °C · no HFO
☐ A weighed 196.6 g — not 20–28 g
☐ A into B · 4–5 s · clock from mix start
☐ Not blended with the BX-02 B-side

Record
Cream / rise / tack-free
Density
Cells

s 2–5 / 8–15 / 10–20
kg/m³ 7–12
open / tight / collapse

If sucrose OH is 350, the sucrose term is 13.95 g A. If 450, 17.94 g A. The water term does not change. [Back to BX-01](#)