

Comparison · This Pack vs Cup-Test v4

Pour **BX-01** first — that is the BazzLab card. This page only shows how the older homepage screens and the ChatGPT cup-test differ. Do not blend any of them into one pour.

BX-01 Best

BEST

NEW

The formula others do not publish: TB-307 f = 2.5 instead of Mannich, TEROL 250 aromatic instead of extra TCP, PO cats instead of K-15 / DMCHA. **HFO-1233zd(E) 10.0 is mandatory**. Faster creaming (3–6 s / 8–15 s). Water 1.20. Index 125 → 83 A : 100 B. Run this first.

Cup-test v4 (ChatGPT)

R&D cup plan on CREAPOL 326 / 1500 / PD 230, plus KIMSPRAY 065 LDO / 066 H2C benchmark. OC is polyether-heavy. CC already includes 10% HFO-1233zd(E) and a K-15 / DMCHA / bismuth catalyst.

What only BX-01 has

POINT	BX-01 BEST	THIS PACK CC-01	CUP-TEST V4 CC
Network	TB-307 / PE 104 41.3 (f = 2.5)	TB-307 / PE 104 35.5	Mannich / sucrose 22 CREAPOL 326 20.0
Flow / fire polyester	TEROL 250 / PE 103 24.8	TEROL 250 / PE 103 24.0	CREAPOL 1500 20.0
Mannich	None	None	Required
HFO in the base	HFO-1233zd(E) 10.0 — mandatory	Must add 10.0 HFO; do not pour water-only	HFO-1233zd(E) 10.0
Water	1.20	2.0	1.1
TCP	6.0 + TEP 4.0 (aromatic does fire work)	12.0 + TEP 6.5 + rFR 5.0	TCP 13.0 only
Catalysts	PC-15 1.45, 2040 1.10, CAT-T 0.55, PC-37 0.35 — faster cream/gel	PC-15 1.30, 2040 1.00, CAT-T 0.25, PC-37 0.15	K-15 / DMCHA / XK-6 MB-20
Mix	83 A : 100 B at index 125	90 A : 100 B at index 120	~100 : 100 after OH c HFO in

Open cell · OC-01

POINT	THIS PACK	CUP-TEST V4	READ
Main polyols	Sucrose 33.0. No CREAPOL in OC-01.	Polyether 1 24.0 + polyether 2 22.0 + sucrose 15.0 + CREAPOL 1500 5.0	Different back
Water	24.0	4.5	v4 is much d