



苏州迈拓金属检测服务有限公司
SUZHOU METAL SERVICES CO., LTD.

我们以所做的专业工作为荣，并始终致力于为客户提供客观、准确、严谨的分析结果。如果您发现报告有任何技术差错或疏漏，请联系我们的材料工程师。如果您有报告之外的其它技术问题，也欢迎联系我们共同探讨。We are pride in our professional work, and always striving to provide the objective, accurate, rigorous analysis results for our clients. If you find any technical error or omission in this report, please contact our lead material engineer. If you have other technical questions which are not included in this report, please contact us for further discussion.

首席材料工程师/Lead Material Engineer: (+86)0512-69361963, (+86)0512-69361960, liuli@metalservices.cn, yaoliang@metalservices.cn

检测报告

Test Report

客户名称:

Client:

重庆三峰卡万塔环境产业有限公司

客户地址:

Client Add.:

重庆市大渡口区建桥工业园建桥大道 5 号

样品名称:

Sample Name:

镍基合金焊丝

收样日期:

Rec. Date:

2024 年 07 月 15 日

检测日期:

Test Date:

2024 年 07 月 24 日~2024 年 07 月 29 日

报告日期:

Report Date:

2024 年 07 月 29 日

签章处

Stamp

刘丽

刘丽 Liuli

批准人 Authorized by

本报告未加盖本公司检测专用章无效。本报告仅对收到的样品负责；未经本公司书面批准，不得部分复制本报告(完整复制除外)；在中华人民共和国境内，本报告加盖 CMA 章，表示检测项目在资质认定范围内，未加盖 CMA 章，数据结果仅供客户内部参考。The report is invalid without SZMS dedicated testing seal. This report is only responsible for sample received. This report can't be partially copied unless got written authorization from SZMS(Complete copy exception). In the People's Republic of China, when CMA seal was stamped, it indicates the test items are within the approval annex, if not stamped, the data and results are only for client internal reference.

苏州工业园区银胜路 125 号 邮箱: info@metalservices.cn 网址: www.metalservices.cn

源自 1989 年，迈拓金属检测始终致力于提供专业的金属材料检测与失效分析服务
Metal Services always dedicated to provide professional metal material testing and failure analysis service



1 样品描述/Sample Description



图 A1 收到的样品

2 客户提供信息/ Information Provided by Client

以下信息除样品编号外均由客户提供，客户对信息的真实性负责。

The following samples were submitted and identified by/on behalf of the client except sample number.

样品名称 Sample Name	样品编号 Sample No.	炉号 Heat No.	批号 Batch No.	材质 Material
镍基合金焊丝	2070-2	013	015	ERNiCrMo-3

3 数据结果及检测依据/Data Result and Testing Method

3.1 密度/Density Test

参考方法/Reference Method: ASTM B311-22

样品名称 Sample Name	样品编号 Sample No.	取样位置 Sampling Position	密度/Density (g/cm ³)
镍基合金焊丝	2070-2	中心	8.47

3.2 晶间腐蚀/Intergranular Corrosion Test

参考方法/Reference Method: ASTM G28-22 Method A

样品名称 Sample Name	试样编号 Specimen No.	取样位置 Sampling Position	试验溶液 Test Solution	测试时间 Time of Test(h)	温度 Temperature
镍基合金焊丝	2070-2	中心	400mL 水+236mL 硫酸+25g 硫酸铁	120	沸腾

● 质量损耗和腐蚀速率/Mass Loss and Corrosion Rate

样品名称 Sample Name	试样编号 Specimen No.	样品尺寸 Sample Size(mm)	表面处理 Surface Preparation	质量损耗 Mass Loss (g)	腐蚀速率 Corrosion Rate (mm/y)
镍基合金焊丝	2070-2	30.05*15.99*3.11	120 目干砂打磨表面	0.049	0.340

-----报告结束/THE END-----