

| Product Overview                           | Specification                                   | Tolerance / Notes                        |
|--------------------------------------------|-------------------------------------------------|------------------------------------------|
| 1. Product Use (Residential, Commercial)   | Residential/Light commercial                    | Ref. Product Performance Requirements    |
| 2. Type (Eng, Solid)                       | Engineered                                      | Ref. Product Performance Requirements    |
| 2.1. Face Veneer Thickness                 | 3.0 mm-4.0mm                                    | Ref. Product CTQ                         |
| 2.2. Face Veneer Type (Sawn, Rot., Sliced) | Sawn cut veneer                                 |                                          |
| 3. Species (Scientific Name)               | European oak                                    |                                          |
| 4. Construction                            | Mulity layer                                    |                                          |
| 4.1. Core Species                          | Poplar & Eucalyptus                             |                                          |
| 4.2. Back Species                          | Poplar                                          |                                          |
| 5. Visual face appearance                  |                                                 |                                          |
| 5.1. Scraped/Wirebrushed or other          | Light Brushed and UV Ultra Matte Lacquer Finish | Ref. Product Identification              |
| 5.2. Filled Face                           | Half filled                                     | Ref. Product Sample                      |
| 5.3. Gloss (60°)                           | 5-10°                                           | 7.5 ± 2.5 gloss units                    |
| 5.4. Coating Type/System                   | UV Coating with Aluminum Oxide                  |                                          |
| 6. Thickness                               | 15.0 mm                                         | Th av (Th n +/-0.45mm), Th max-min<0.5mm |
| 7. Widths                                  | 190mm 260mm                                     | Wd av (Wd n ± 0.15mm), Wd max-min<0.20mm |
| 8. Lengths                                 | 600-2200mm                                      | +/-0.5mm , <1mm                          |
| 9. Drawing Profile                         |                                                 |                                          |
| 9.1. Drawing                               | Tongue & Groove                                 | 0.15mm                                   |

|                                                  |                        |                             |
|--------------------------------------------------|------------------------|-----------------------------|
| <b>9.2. Right/ Left Hand</b>                     | Right Hand             | Ref. Product Sample         |
| <b>9.3. Side Bevel</b>                           | Four side 0.5mm        | Ref. Product Identification |
| <b>10. Installation (Staple, Glue, Floating)</b> | Staple, Glue, Floating |                             |

| <b>Packaging</b>                    | <b>Specification</b>                                                                                                                                                                                           |
|-------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>1. Carton</b>                    |                                                                                                                                                                                                                |
| <b>1.1. Required Box # Type</b>     | As the carton design,                                                                                                                                                                                          |
| <b>1.2. Boxed Footage</b>           | L: 19150mm W: 200mm H: 120mm, 28kg/carton<br>L: 2215mm W: 270mm H: 90mm, 32kg/carton                                                                                                                           |
| <b>1.3. Wood Orientation in Box</b> | Face to face, back to back.                                                                                                                                                                                    |
| <b>1.4. Instructions</b>            |                                                                                                                                                                                                                |
| <b>1.5. Foam Sheeting</b>           | Foam to be used between layers when faces are in contact.                                                                                                                                                      |
| <b>1.6. Sealing</b>                 |                                                                                                                                                                                                                |
| <b>1.7. Batch number</b>            | DH01 + HC#<br>Back printing : -----DH01 + HC#                                                                                                                                                                  |
| <b>2. Palletizing</b>               |                                                                                                                                                                                                                |
| <b>2.1. Square Feet each Pallet</b> | 6pcs per carton, 3.432m <sup>2</sup> /carton<br>40cartons per pallet,137.28 m <sup>2</sup> per pallet<br>8pcs per carton, 2.888m <sup>2</sup> /carton<br>40cartons per pallet,115.52 m <sup>2</sup> per pallet |
| <b>2.2. Pallet Type</b>             | Plywood                                                                                                                                                                                                        |
| <b>2.3. Pallet Dimension</b>        | L: 1920mm W: 1040mm H: 120mm, 1200kg/pallet<br>L: 2220mm W: 1130mm H: 120mm, 1300kg/pallet                                                                                                                     |
| <b>2.4. Container configuration</b> | 40' container: 24 pallets, 2772.48m <sup>2</sup> per container<br>40' container: 20 pallets, 2745.6m <sup>2</sup> per container                                                                                |

### Product CTQ

| Item                | Specification  | Tolerance/ Notes                              |
|---------------------|----------------|-----------------------------------------------|
| 1. Veneer Thickness | 3.0mm<br>4.0mm | Average veneer thickness = 3.0mm +0.5/- 0.3mm |
| 2. Moisture         | 6% - 9%        | Oven dry testing method.                      |
| 3. Bow              | 0"             | Width : fw≤0.2% ; Length : fw≤1.0%            |
| 4. End Lift         | 0"             | Width : fw≤0.1% ; Length : fw≤0.5%            |
| 5. Straightness     | 0"             | ≤0.30mm/m                                     |
| 6. Squareness       | 0"             | ≤0.20mm                                       |
| 7. Overwood         | 0"             | Average <0.15mm , Maximum <0.20mm             |
| 8. Gap              | 0"             | Average <0.10mm , Maximum <0.15mm             |

### Product Performance Requirements

| Performance Tests         | Test Reference           | Specifications                               |
|---------------------------|--------------------------|----------------------------------------------|
| 1. Soak Test              | GB/T 18103-2013          | Pass GB Soak test.                           |
| 2. Moisture Content       | GB/T 18103-2013          | 6%-9%                                        |
| 3. Modulus of Rupture     | GB/T 18103-2013          | >= 30 MPa                                    |
| 4. Modulus of Elastic     | GB/T 18103-2013          | >= 4000 MPa                                  |
| 5. Cross Hatch Adhesion   | GB/T 18103-2013          | Minimum 4B rating ( 95% or greater ) greater |
| 6. Taber Abrasion         | ASTM D 4060 S-33         | >= 150 ( S33 )                               |
| 7. Surface Hardness       | GB/T 18103-2013          | >=2H                                         |
| 8. Formaldehyde Emissions | GB/T 18103-2013          | E1 (GB test)                                 |
| 9. Geothermal performance | ( 70°C , 48h )           | No Crack                                     |
|                           | ( 70°C 2h , -20°C 2h ; ) | No Crack                                     |

### Product Defect

| Grade Appearance                   | European oak ABCD Grade                                                                                            |
|------------------------------------|--------------------------------------------------------------------------------------------------------------------|
| <b>Natural grain pattern</b>       | Allowed.                                                                                                           |
| <b>Sound Knots</b>                 | Allowed. Fully filled and covered with UV and stain.                                                               |
| <b>Dead Knots</b>                  | Diameter <60mm, <= 1 per full length. Diameter <30mm, allowed. Fully filled and covered with UV and stain.         |
| <b>Knot Void</b>                   | Diameter <20mm, <1 per full length. Fully filled and covered with UV and stain.                                    |
| <b>Splits, Checks, Cracks</b>      | Crack at ends < 5mm * 300mm. Surface crack length < 600mm. Fully filled with filler and covered with UV and stain. |
| <b>Rough / Shelly grain</b>        | None allowed.                                                                                                      |
| <b>Sap wood</b>                    | Allowed. Need to be well stained to match the surroundings.                                                        |
| <b>Bark pockets</b>                | Allowed. Fully filled (no loose or unsound surrounding) and covered with UV and stain.                             |
| <b>Mineral streaks / Dark line</b> | Allowed. Color of mineral streaks should probably match with the color of product.                                 |
| <b>Color Variation</b>             | Allowed, refer to master sample for each product.                                                                  |
| <b>Discoloration / Stain</b>       | Very slightly allowed.                                                                                             |
| <b>Water Mark</b>                  | None allowed.                                                                                                      |
| <b>Worm holes</b>                  | None allowed.                                                                                                      |
| <b>Rot</b>                         | Very slightly allowed.                                                                                             |
| <b>Heart wood</b>                  | Allowed.                                                                                                           |
| <b>Species / Face veneer</b>       | No off species allowed.                                                                                            |

| <b>Mismanufacturing</b>                      |                                                              |
|----------------------------------------------|--------------------------------------------------------------|
| <b>Bleed back</b>                            | None allowed.                                                |
| <b>Splice face veneer</b>                    | None allowed.                                                |
| <b>Hull out</b>                              | None allowed.                                                |
| <b>Indents</b>                               | None allowed.                                                |
| <b>Edge splinters</b>                        | None allowed.                                                |
| <b>Edge / Corner breaks</b>                  | None allowed.                                                |
| <b>Core voids</b>                            | 10 mm max opening.                                           |
| <b>Core laps</b>                             | None allowed.                                                |
| <b>Delamination</b>                          | None allowed.                                                |
| <b>Crushed groove</b>                        | Only allowed if planks can be engaged. No stain or UV skips. |
| <b>Coating Defects</b>                       |                                                              |
| <b>Orange peel</b>                           | None allowed.                                                |
| <b>Pin holes</b>                             | Slightly allowed.                                            |
| <b>Scratches</b>                             | Minor, no white wood.                                        |
| <b>Shake</b>                                 | None allowed.                                                |
| <b>White grain</b>                           | None allowed.                                                |
| <b>UV/Sander Lines UV</b>                    | None allowed.                                                |
| <b>UV/Stain skips</b>                        | None allowed.                                                |
| <b>Dark/Light Edges &amp; Ends</b>           | No light ends.                                               |
| <b>Sander burns / bites</b>                  | None allowed.                                                |
| <b>Rough sanding / Finish</b>                | Slight only. Must take immediate corrective action.          |
| <b>Brush marks</b>                           | Allowed if it does not detract from overall appearance.      |
| <b>UV bubbles / Blisters/<br/>Filler Pop</b> | None allowed.                                                |
| <b>Wet UV UV</b>                             | None allowed.                                                |
| <b>Filler / UV on edges</b>                  | None allowed.                                                |
| <b>Color match</b>                           | Must match color standard board.                             |
| <b>Gloss variation</b>                       | No visible gloss variation on full boards or spots allowed.  |

## Reversion Histroy

---