

COLLISION REPAIR INFORMATION BULLETIN



SUBJECT:	IDENTIFICATION OF PLASTIC PARTS		
BULLETIN NO.:	TS-TCI-CRIB-2016	DATE ISSUED:	May, 2013
MODELS:	All Toyota & Scion Models	SECTION:	General Information

When repairing metal body parts by brazing, frame cutting, welding, painting, etc., consideration must be given to the different types of adjoining plastic body parts due to the different properties and the possibility of damage or deformation from these activities.

The repair method for plastic body parts must conform to the type of plastic material being used. The properties and handling procedures for these materials are indicated in pages 2 and 3 of this bulletin.

Plastic components are usually identified by abbreviations that correspond to the name of the plastic material used in the component. The abbreviations are normally found on the backside of the part (not visible when the part is installed). The abbreviations normally appear as raised plastic letters that protrude outward from the surface of the part.

EXAMPLE:

One plastic material used on Toyota/Scion vehicles is "Acrylonitrile Butadiene Styrene Resin", which is abbreviated to "A.B.S." The letters A.B.S. appear on the backside of the plastic part.

Please refer to the chart on pages 2 and 3 of this bulletin for the names of the various plastics. The chart also indicates the temperature resistance temperatures, resistance to alcohol and gasoline or other substances that may damage the plastic.

NOTE: Issue of this Collision Repair Information Bulletin by Toyota Canada Inc. is to ensure that proper repair information is available. It does not constitute an authorization for repair. PLEASE ROUTE THIS BULLETIN TO YOUR COLLISION REPAIR CENTER MANAGER AND COLLISION & REFINISH TECHNICIANS.



TS-TCI-CRIB-2016

May, 2013

IDENTIFICATION OF PLASTIC PARTS

PLASTIC REFERENCE CHART

Code	Material Name	Heat Resisting Temperature C° (F°) *	Resistance to Alcohol or Gasoline	Notes
AAS	Acrylonitrile Acrylic Rubber Styrene Resin	80 (176)	Alcohol is harmless if applied only for short time in small amounts (ex., quick wiping to remove grease)	Avoid gasoline and organic or aromatic solvents
ABS	Acrylonitrile Butadiene Styrene Resin	80 (176)	Alcohol is harmless if applied only for short time in small amounts (ex., quick wiping to remove grease)	Avoid gasoline and organic or aromatic solvents
AES	Acrylonitrile Ethylene Rubber Styrene Resin	80 (176)	Alcohol is harmless if applied only for short time in small amounts (ex., quick wiping to remove grease)	Avoid gasoline and organic or aromatic solvents
EPDM	Ethylene Propylene Rubber	100 (212)	Alcohol is harmless. Gasoline is harmless if applied only for short time in small amounts	Most solvents are harmless but avoid dipping in gasoline, solvents, etc.
PA	Polyamide (Nylon)	80 (176)	Alcohol and gasoline are harmless.	Avoid battery acid
PC	Polycarbonate	120 (248)	Alcohol is harmless	Avoid gasoline, brake fluid, wax, wax removers, and organic solvents
PE	Polyethylene	80 (176)	Alcohol and gasoline are harmless	Most solvents are harmless
POM	Polyoxymethylene (Polyacetal)	100 (212)	Alcohol and gasoline are harmless	Most solvents are harmless
PP	Polypropylene	80 (176)	Alcohol and gasoline are harmless	Most solvents are harmless
PPO	Modified Polyphenylene Oxide	100 (212)	Alcohol is harmless	Gasoline is harmless if applied only for quick wiping to remove grease
PS	Polystyrene	60 (140)	Alcohol and gasoline are harmless if applied only for short time in small amounts	Avoid dipping or immersing in alcohol, gasoline, solvents, etc
PUR	Thermosetting Polyurethane	80 (176)	Alcohol is harmless if applied only for short time in small amounts (ex., quick wiping to remove grease)	Avoid dipping or immersing in alcohol, gasoline, solvents, etc.



TS–TCI–CRIB–2016

May, 2013

IDENTIFICATION OF PLASTIC PARTS

Code	Material Name	Heat Resisting Temperature C° (F°) *	Resistance to Alcohol or Gasoline	Notes
PVC	Polyvinylchloride (Vinyl)	80 (176)	Alcohol and gasoline are harmless if applied only for short time in small amounts (ex., quick wiping to remove grease)	Avoid dipping or immersing in alcohol, gasoline, solvents, etc.
PMMA	Polymethyl Methacrylate	80 (176)	Alcohol is harmless if applied only for short time in small amounts	Avoid dipping or immersing in alcohol, gasoline, solvents, etc.
SAN	Styrene Acrylonitrile Resin	80 (176)	Alcohol is harmless if applied only for short time in small amounts (ex., quick wiping to remove grease)	Avoid dipping or immersing in alcohol, gasoline, solvents, etc.
SMC	Sheet Moulding Compound	180 (356)	Alcohol and gasoline are harmless	Avoid alkali
TPO	Thermoplastic Olefine	80 (176)	Alcohol is harmless. Gasoline is harmless if applied only for short time in small amounts	Most solvents are harmless but avoid dipping in gasoline, solvents, etc.
TPU	Thermoplastic Polyurethane	80 (176)	Alcohol is harmless if applied only for very short time in small amounts (ex., quick wiping to remove grease)	Avoid dipping or immersing in alcohol, gasoline, solvents, etc.
UP	Unsaturated Polyester	110 (233)	Alcohol and gasoline are harmless	Avoid alkali

* Temperatures higher than those listed here may result in material deformation during repair.