

A1 — global hotspot 10 — Annealing 75 °C, 5 h
T = 20 °C, v_over = 5 V

