

A1 — global hotspot 4 — Annealing 125 °C, 5 h
T = 20 °C, v_over = 5 V

