

A1 — global hotspot 54 — Annealing 150 °C, 5 h
T = 20 °C, v_{over} = 5 V

