

4 Polymer-Based Nanocarriers

Dendrimers, Polymeric Micelles, Hydrogels

Juan C. Cruz and Luis H. Reyes

4.1 INTRODUCTION

Polymer-based nanocarriers are revolutionizing drug-delivery systems in the fast-paced field of nanobiotechnology. Dendrimers, polymeric micelles, and hydrogels stand out as up-and-coming innovations. These nanocarriers offer a range of advantages: they enhance drug solubility and bioavailability, enable site-specific targeting, and provide controlled release mechanisms while reducing toxicity. By overcoming the limitations of traditional drug-delivery methods, nanocarrier-equipped pharmaceuticals pave the way for more targeted therapies with fewer side effects for patients. This drug administration paradigm shift exemplifies nanobiotechnology's transformative potential in modern medicine.

In the pharmacological context, there are two major obstacles: solubility and bioavailability. Low solubility in water is a common problem for many drugs and thus presents limited absorption and low therapeutic value (1). Notably, nanotechnology drug-delivery systems using polymer-based nanocarriers are among the most prominent areas. In such nanocarriers, the solubility and bioavailability of the drugs may therefore be increased. For instance, dendrimers are versatile systems for carrying drugs formed using drug encapsulation, increasing poorly water-soluble drugs' solubility.

Another critical feature is targeted drug delivery, where the therapeutic is delivered at the disease site without affecting the rest, lowering the overall side effects. Polymeric micelles formed by the self-assembly of block copolymers have offered great promise for this application. Core-shell structures allow the encapsulation of hydrophobic drugs in the core, which could be delivered to sites, for example, tumor cells, in a targeted manner with the help of receptor-ligand interactions at the shell (2).

Regulation of the drug release from the formulation is needed to maintain an appropriate drug level in the body over an extended period to improve treatment efficacy and patient compliance. Hydrogels are exceptionally hydrophilic polymer networks that are capable of imbibing large amounts of water or biological fluids and hence finding wide use in systems for the controlled release of encapsulated drugs in response to outer stimuli, such as pH, temperature, or enzymes present in the diseased environment (3).

Designing drug-delivery systems with minimal toxicity is crucial for their clinical success. Nanocarriers must be engineered to be biocompatible and biodegradable, ensuring safe metabolism after delivering their therapeutic payload and facilitating proper bodily excretion. This aspect is vital in preventing the accumulation of potentially harmful materials and mitigating adverse reactions. Researchers can develop more effective and safer drug-delivery systems by focusing on these key factors, ultimately improving patient outcomes and expanding treatment options for various diseases (4).

Recent advances in nanobiotechnology have built upon the foundational work in the field, highlighting the potential of polymer-based nanocarriers in drug-delivery systems. Current research and development efforts are focused on optimizing these nanocarriers for a broad spectrum of therapeutic applications. Scientists are working diligently to overcome existing challenges to unlock new medical possibilities. By refining the design and functionality of nanocarriers, researchers are paving the way for more effective treatment interventions across various medical conditions. This ongoing innovation promises to revolutionize drug delivery, potentially improving patient outcomes and expanding the reach of targeted therapies.

Nanocarriers have revolutionized drug delivery by improving therapeutics' bioavailability, targeting efficiency, and pharmacokinetics. Various nanocarriers, including liposomes, dendrimers, polymeric nanoparticles, solid lipid nanoparticles, and nanostructured lipid carriers, interact differently with biological systems and exhibit varied delivery efficiencies.

Liposomes, spherical vesicles with a lipid bilayer, mimic cellular membranes, facilitating effective drug delivery and reducing toxicity. Their biocompatibility and ability to encapsulate hydrophilic and hydrophobic drugs make them highly versatile (5). With their branched structure, dendrimers offer precise control over size and surface functionality, allowing for targeted delivery and reduced off-target effects (6). Polymeric nanoparticles are designed for controlled release, thereby providing sustained drug release and improving patient compliance (7). Solid lipid nanoparticles and nanostructured lipid carriers improve the solubility of hydrophobic drugs and offer an alternative to polymeric systems, with advantages in biodegradability and lower cytotoxicity (8).

The interaction of these nanocarriers with biological systems—ranging from cellular uptake mechanisms to biodistribution and clearance—is critical in determining their delivery efficiency. Factors such as size, surface charge, and hydrophobicity/hydrophilicity balance play important roles in these interactions. Optimizing these characteristics can enhance the delivery efficiency of nanocarriers, making them more effective in targeting specific tissues or cells, crossing biological barriers, and releasing their payload at the desired site of action. Polymer-based nanocarriers have emerged as excellent alternate systems for the conventional drug-delivery system and represent revolutionary, transformative advantages leading to improved therapeutic outcomes. Hallmark features of the most celebrated nanocarriers developed with the help of polymers include controlled drug release, improved drug stability, and target specificity.

Controlled release of drugs is the primary application of polymer-based nanocarriers, allowing the control of pharmacokinetics. This allows the drug to be released sustainably, maintaining a therapeutic level in the bloodstream over a long period with minimal requirement for frequent dosing. Such controlled release mechanisms are convenient and important for improving patient adherence to treatment regimens. These nanocarriers also play an important role in enhancing the stability of the drug. Polymer-based nanocarriers coat the drug with active substances to protect it from enzymatic and hydrolytic degradation. Such protection is especially important for sensitive molecules that begin to degrade before reaching their target sites in the body (9).

Adopting polymer-based nanocarriers offers significant advantages beyond those previously discussed, particularly in enhancing drug bioavailability. These nanocarriers excel at improving the solubility of hydrophobic drugs, facilitating their optimal transport across biological barriers. This enhancement is crucial, as many drugs face challenges in their administration due to low solubility, a point emphasized in recent research by Gouthami et al. (10). Perhaps even more promising is the potential for targeted delivery to specific tissues, cells, or pathological sites. Through surface engineering with various ligands or antibodies, these nanocarriers can be designed to bind with specific cellular receptors, enabling precise payload delivery to the intended site of action. This targeted approach contrasts traditional transmembrane methods, offering a more focused therapeutic impact while minimizing systemic side effects. Such precision is especially valuable in treating localized diseases like cancer, as noted by Zhu et al. (11). Combining improved bioavailability with targeted delivery, polymer-based nanocarriers are poised to revolutionize drug administration, potentially increasing treatment efficacy while reducing unwanted effects.

The features of these polymer-based nanocarriers seem much more advanced and better when compared to traditional ones that lack high accuracy and efficiency. Thus, the benefits that came with some specific nanocarriers are, in turn, improving drug therapies' efficacy and, in this way, changing the quality of life for patients.

Polymer-based nanocarriers are revolutionizing biomedical research, particularly in delivering nucleic acids and proteins. These biomolecules, known for their instability in physiological environments, are finding new life through sophisticated carrier systems. Nanocarriers preserve their integrity and functionality by shielding these delicate molecules from enzymatic degradation until they reach their cellular targets. This protective mechanism is crucial for maintaining biological activity during transit through the body, a significant advancement highlighted in recent work by Mashal et al. (12). Moreover, these nanocarriers are adeptly modified to increase cellular uptake and promote the escape of molecules from endosomes, markedly elevating the delivery success of nucleic acids and proteins. Through the strategic addition of specific ligands or alterations to their surface properties, these nanocarriers substantially boost intracellular delivery and transfection success, thereby proving indispensable in gene therapy advancements (13).

The dynamic nature of polymer-based nanocarriers is further demonstrated by their ability to react to physiological stimuli, including pH shifts, temperature changes, or enzymatic actions. Such reactive capabilities facilitate the targeted and controlled release of the enclosed nucleic acids or proteins, effectively reducing side effects and optimizing therapeutic results. This is crucial in advancing precision medicine, as emphasized in an earlier study (14). Additionally, these nanocarriers enhance the pharmacokinetic characteristics of nucleic acids and proteins, extending their circulation within the bloodstream. This prolongation improves the likelihood of the therapeutic agents reaching their intended destinations and enhances their availability, which is essential for successful treatment outcomes (15).

Lastly, polymer-based nanocarriers offer essential protection against the thermal and mechanical challenges that nucleic acids and proteins might face during storage and transport. This protective measure is crucial for preserving the therapeutic potency of these biomolecules until they are ready for clinical deployment, a critical factor highlighted by Yuan and Li in 2017 (16). The comprehensive functionality of polymer-based nanocarriers underscores their transformative impact in biomedicine, especially in gene therapy and protein-based treatments. Their unparalleled ability to protect, deliver, and stabilize therapeutic agents makes them a cornerstone in the evolution of disease treatment methodologies (Figure 4.1).




Figure 4.1 Structural comparison of polymer-based nanocarriers. (A) Dendrimer: Highly branched structure with a core, multiple generations of branching units, internal cavities for cargo, and surface groups amenable for functionalization. (B) Polymeric micelle: Amphiphilic structure with a hydrophobic core (pink) for drug encapsulation and a hydrophilic shell (gray) for stability in aqueous environments. (C) Hydrogel: Cross-linked polymer network forming a porous, water-retaining structure capable of dispersing drug molecules throughout its matrix.

4.2 FUNDAMENTALS OF POLYMER-BASED NANOCARRIERS

4.2.1 Basic Concepts and Definitions

Nanobiotechnology demands a specialized approach to polymer design, tailoring materials to meet the exacting standards of medical applications. These medical-grade polymers distinguish themselves from their industrial counterparts through fundamental properties: biocompatibility, biodegradability, and adaptability for functionalization. Such characteristics ensure optimal performance within biological systems. Biocompatibility is a cornerstone requirement, guaranteeing that these materials can coexist harmlessly within the body without triggering adverse immune responses. This quality sets medical polymers apart from many industrial variants, which often contain substances unsuitable for biological integration. Researchers create materials that seamlessly blend into biological environments by engineering polymers to be inherently compatible with living systems. This fundamental compatibility enables medical polymers to perform their intended functions without disrupting the delicate balance of the body's internal systems. The stark contrast between these specialized polymers and their industrial counterparts underscore the precision and care invested in their development, reflecting the unique demands of medical applications in nanobiotechnology (17).

Polymers used in nanobiotechnology are often designed to be biodegradable, decomposing into non-toxic substances that the body can quickly expel. This characteristic is particularly important for applications such as drug delivery, where removing the polymer after its job is as crucial as its initial function. This contrasts with industrial polymers, which often prioritize durability and cost-effectiveness over environmental and biological safety (18). One of the unique features of nanobiotechnology polymers is their ability to be functionalized. This procedure entails chemically altering the polymers to incorporate precise functional groups, such as targeting agents, imaging markers, or drugs, thereby augmenting their interaction and efficacy within biological systems. This tailor-made approach allows for precision in medical treatments and is vital for successful applications in complex biological environments.

Moreover, these polymers' physical and chemical characteristics, including their solubility, charge, and molecular weight, are carefully adjusted to enhance their effectiveness in biological settings. These parameters are essential for ensuring the polymers' proper distribution within the body, facilitating cellular interactions, and maximizing their effectiveness in roles such as drug delivery (17). Polymers engineered for nanobiotechnology are distinctively crafted to meet the demands of living systems, offering safety, efficacy, and responsiveness that are unparalleled by non-medical polymers. This advanced engineering melds

materials science with biological science, aiming to overcome the complex challenges faced in contemporary medicine.

To function optimally as nanocarriers in medical treatments, polymers must exhibit critical characteristics that ensure their efficiency in drug delivery at the nanoscale. These properties are pivotal for the encapsulation and protection of therapeutic agents and crucial for successfully navigating the intricate biological environments to target affected sites precisely. A primary requirement for polymers utilized as nanocarriers is biocompatibility. These materials must be inherently non-toxic and should not trigger adverse immune reactions upon administration. Ensuring biocompatibility allows these carriers to operate safely within the body, avoiding detrimental effects on surrounding tissues or inducing unwanted inflammatory responses. This aspect is critical for their acceptance and effectiveness (19).

Biodegradability is another essential feature for effective nanocarriers. They should break down into harmless by-products that the body can readily dispose of. This characteristic is especially important for temporary therapeutic measures, ensuring that the carriers do not persist within the body after accomplishing their drug-delivery tasks, thereby minimizing potential long-term side effects and toxicity (20). Maintaining structural integrity in biological fluids is crucial for nanocarriers until they reach their targets. Polymers must be resilient against the physicochemical challenges encountered in the bloodstream or within cellular environments, including resistance to enzymatic breakdown and stability across diverse pH levels and temperature conditions (21).

The ability to control the release of drugs is fundamental for maintaining therapeutic drug levels at the target site for the intended duration. Polymers used in nanocarriers should facilitate precise control over the release kinetics of the encapsulated drugs, often employing stimuli-responsive mechanisms that activate in response to specific biological signals or environmental changes (21). Advanced targeting is a crucial feature for polymers, enabling them to adhere to and affect diseased cells or tissues specifically. This is accomplished by modifying the polymer surface with ligands or antibodies that recognize and bind to cellular receptors, optimizing therapeutic efficacy and minimizing effects on non-target tissues (19).

Together, these characteristics guarantee that polymers utilized as nanocarriers are efficient in transporting drugs and delivering them in a controlled manner and are safely broken down and eliminated by the body once their therapeutic purpose is fulfilled.

4.2.2 Mechanisms of Action

Developing polymer-based nanocarriers that can effectively package and protect biomolecules from premature protease activity during delivery could significantly address therapeutic agents' stability and bioavailability challenges. For this purpose, nanoparticles are engineered for specific properties to allow safe transport and controlled release of the encapsulated bioactive substances, such as proteins, peptides, and nucleic acids. Polymer-based nanocarriers exhibit exceptional efficacy in encapsulating biomolecules. The polymers may then form hydrophobic or hydrophilic interactions with the drug molecules based on their chemical structure, allowing a wide variety of therapeutic agents to be included. Therefore, including various drugs with distinct solubility and stability profiles is crucial.

The process of encapsulation itself ensures protection against premature degradation caused by pH, enzymes, and oxidative stress conditions. This protection safeguards the biological activity within the encapsulated material until it reaches its intended target site (22). Once entrapped, these biomolecules can be protected from the harsh outside environment due to the polymeric matrix. This highlights the significance of safeguarding proteins and nucleic acids, collectively known as biologics, which are often susceptible to degradation by enzymes in the gastrointestinal tract when taken orally or in circulation.

Polymer-based carriers have the ability to enclose these delicate molecules and shield them from enzymatic and hydrolytic breakdown, thereby improving their circulation in the body and increasing their effectiveness in reaching specific tissues (23). Polymeric nanocarriers can be engineered to have controlled release properties by modifying the composition and structure of the polymer. Such systems could react to certain body stimuli, like pH alteration, temperature modification, or many enzymes, for the drug to be secreted only at the site where it will produce its effect. This reduces side effects in the body while increasing therapeutic effectiveness at the target site. Therefore, they are the optimal selection for drug-delivery applications that target specific sites (24).

Nanocarriers must possess biocompatibility and biodegradability to fulfill their intended purpose effectively. The polymers utilized in these systems are predominantly non-toxic and are engineered to gradually break down into harmless substances that can be easily eliminated from the body. This reduces the likelihood of accumulation and long-term toxicity (20). The carriers effectively enclose and safeguard the biomolecules by providing durable protection, shielding encapsulated substances from biological and chemical degradation. Controlled release mechanisms, biocompatibility, and biodegradability features

represent key facets in effectively delivering and transporting therapeutic agents, especially when the target is a complex disease.

Polymer-based nanocarriers are engineered to include sophisticated techniques for the optimal transportation and release of therapeutic agents, resulting in a significant enhancement of effectiveness and safety compared to other drug-delivery systems. Both methods of nanocarriers, namely targeted delivery and controlled release, raise drug administration precision.

There are essentially two strategies for a more precise delivery of these therapies: active and passive. The term “active” describes the requirement for conjugation with specific ligands, such as antibodies, peptides, or small molecules, on the surface of the nanocarriers. These ligands, which bind to receptors or antigens on target cells (specifically cancer cells), result in an elevated drug concentration at the disease site while minimizing its effect on healthy tissues. Their work with this strategy highlights improved targeting efficiency and reduced systemic toxicity toward the target. Passive targeting, on the other hand, exploits the enhanced permeability and retention (EPR) effect, a common occurrence in cancer therapy. Polymeric nanocarriers are typically designed with precise dimensions to facilitate their accumulation in tumor tissues, considering tumor vasculature’s disordered nature and the lymphatic system’s limited drainage capacity. Subhan et al. (2023) discuss how this phenomenon can significantly improve the delivery of anticancer drugs (25).

Controlled release is one of the key aspects of polymer-based nanocarriers that may be under control through pH-responsive, thermo-responsive, or light-responsive systems. The pH-responsive nanocarriers are specifically engineered for release in acidic environments, such as tumor cells or inflamed tissues. Ranjit De et al. (2022) further elaborate that these systems are acid-labile-linked in the polymer structure, and the linkages are destructible in an acidic environment, thus releasing the drug (23). Thermo-responsive systems are based on the use of temperature-change-sensitive polymers. By employing this approach, systems have the capability to focus on elevating tumor temperature levels slightly higher than the average body temperature or react to the influence of an external heat source (26). In their article, Zhang et al. (2021) stated that photoresponsive systems involve photo-sensitive groups integrated into the polymer structure, which specific light wavelengths can trigger to release a drug in a controlled manner (27).

All these systems bring about a fine control of the level of drug release, particularly with the relevance to the localized treatment of cancers—or, literally, with pinpoint precision—in activating photodynamic therapy (PDT). Together, such strategies enable the drug-loaded polymer-based nanocarriers to enhance the drug pharmacokinetics and bio-distribution profoundly. Such a system, in turn, may make it possible for therapeutic agents to be released in a controlled manner right at the site of pathology, ensuring maximum therapeutic efficiency and minimal side effects; potentially, these systems pave the way for more efficient and safe treatment.

4.3 DENDRIMERS

4.3.1 Structure and Synthesis

Dendrimers, a highly branched and star-shaped macromolecular architecture, are outstanding nanocarriers in drug-delivery applications. The architectural features of dendrimers contribute to their functionality in a big way, and therefore, they have found many therapeutic uses in a very effective manner. Dendrimers have a complex structure with multiple branches and multiple terminal groups. These terminal groups can be modified with various therapeutic agents, enabling the attachment of numerous drug molecules to increase the drug load (28).

Dendrimers are synthesized through a sequential and hierarchical process that involves increasing the size and functionality of the molecule in a tree-like structure. This meticulous procedure enables precise control over the dimensions and shape of the dendrimer, which are critical factors in determining their biological interactions and ability to penetrate biological membranes and enter cells (29). The branches of the dendrimers, which form the internal cavities, can also encapsulate guest molecules. Therefore, the nanoparticles described in the study protect drugs from degradation in sensitive environments until they reach their intended targets. Additionally, these nanoparticles enable the controlled release of the drugs, thus ensuring that therapeutic drug concentration is maintained in the body (30).

The surface of the dendrimers brings even more functional advantages. Chemical modification can be applied to most terminal functional groups to enhance solubility, improve biocompatibility, or attach targeting ligands. When appropriately altered, dendrimers become suitable for therapeutic purposes, such as targeting cancer cells or penetrating the blood–brain barrier (BBB) for drug delivery. Chemists are currently researching dendrimers to enhance the biocompatibility and biodegradability of this type of large molecule. This will result in significantly reduced toxicity in the intended area of application. These properties are demonstrated or improved by incorporating biodegradable linkages or using biodegradable materials within the body (31).

Dendrimers possess a distinctive structure with multiple branches and a specific size. They provide a high level of control due to their chemically adjustable surface. Additionally, they have an internal cavity that can encapsulate a drug in a protected environment. Furthermore, dendrimers have a surface compatible with living organisms and are capable of being broken down naturally. Taken together, all these properties suggest that these agents are more effective as nanocarriers. Dendrimers possess properties that enable efficient drug delivery with minimal side effects and maximum therapeutic impact at specific locations.

Dendrimer synthesis for drug delivery in chemistry has proven to be highly challenging, with numerous problematic factors. The intimate development of innovative solutions is essential for advancing the limits of dendrimer technology in therapeutic applications.

A significant challenge in dendrimer synthesis is the inherent complexity of the process, which involves a stepwise iteration toward the formation of the dendrimer. This requires precise control over the conditions to ensure uniformity and prevent structural defects in each generational layer. This then further adds to the production cost and raises significant issues about scalability. On top of that, it is hard to provide that uniform monodispersity in population. Nevertheless, dendrimers' size and surface functionality vary due to incomplete reactions or side reactions that occur during their synthesis, which ultimately negatively affect their performance in drug-delivery applications (32).

These effective chemical methods will be necessary for the efficient placement of drugs onto the dendrimers and for their modification and attachment of the corresponding functional groups or drugs to their surface. As a result, functionalization is unreliable for therapeutic results; hence, therapeutic outcomes are highly variable (31).

Several sophisticated solutions have been developed for this purpose. Recent technological advancements in automated synthesis techniques have eased the scaling up of dendrimer production, with no need to compromise on the consistency of quality. For these techniques, the conditions and timing of the reaction can be well controlled to realize better yields and uniformity of the final product (33). This is where the most current and one of the best ideas being carried out comes in: the development of orthogonal functionalization strategies to enable the modification of dendrimers at different, non-interfering generational layers. The statement suggests that the functionalization process occurs according to the described control, thereby increasing the capacity of dendrimers to achieve accurate deliveries.

The purification process typically involves dialysis, ultrafiltration, and chromatography to ensure the use of precisely defined dendrimers in subsequent studies and applications. These procedures remove unreacted monomers and their by-products to eliminate batch-to-batch variability (31). Microwave-assisted synthesis has been included in the list of novel reaction conditions used in dendrimer synthesis.

They enhance the synthesis rate and simultaneously decrease unwanted reactions, thereby improving the drug loading efficiency. The conditions are carefully adjusted, primarily to enhance the speed of chemical reactions and achieve precise control over the structure of the dendrimer (32). Therefore, by utilizing these advanced and efficient solutions, significant obstacles in the synthesis process of producing dendrimers for drug delivery can be effectively addressed, thus leading to improved production and facilitating the development of more dependable and potent dendrimer-based therapeutic products.

4.3.2 Functionalization and Modification

Hence, modifying dendrimers' surfaces is crucial to augmenting their effectiveness as a drug-delivery system, particularly for precise delivery to specific cells or tissues. Functionalization can occur by attaching various ligands or groups to the surface of the dendrimer. This enables the dendrimer to recognize and bind to a specific receptor or structure on the surface of a target cell.

The surface-modified targeting of the dendrimer works twofold: the targeting of receptors in cells, either cancerous, inflammatory, or infectious type, is only affected by the specific moieties conjugated on the surface of the dendrimer. The dendrimer targets such cells effectively. These may include, but are not limited to, small molecules targeting affinity against a given specific cell surface receptor, such as antibodies, peptides, or even aptamers, depending on the need. Therefore, if used, this approach is likely to have an effective delivery system with less impact only on the cells where the antigen is not targetable, hence fewer side effects and an improved therapeutic index (34).

Surface modification also increases the uptake of cellular dendrimers. The enhanced interaction between modified dendrimers and different components of the cell membrane facilitates more effective endocytosis and uptake, enabling the direct delivery of therapeutic agents to cell targets at elevated levels (35).

Their surface properties can be manipulated in response to specific environmental triggers, such as variations in pH, temperature, or enzymatic activity. Responsive systems are specifically engineered to enable the targeted delivery of drugs at the intended site of action. This design ensures that the drugs are released in a controlled manner, maximizing their therapeutic effectiveness while preventing premature release before the desired time (36). Other designs work on modifying the surface of the dendrimers with hydrophilic polymers,

for example, polyethylene glycol (PEG), to improve circulation time and general stability. The modification decreases opsonization and minimizes the likelihood of early clearance by the reticuloendothelial system, thereby ensuring a more extended duration for dendrimers to reach and accumulate at the intended site, as necessary (37).

Lastly, through this surface modification, the inherent toxicity of dendrimers can be reduced by masking or neutralizing charged surface groups that would interact with any biological component adversely. The paramount importance lies in ensuring the safety of dendrimers when utilized for medical purposes (38). Surface functionalization plays a crucial role in optimizing dendrimers as efficient and safe drug carriers that specifically target disease sites, thereby minimizing side effects and maximizing therapeutic efficacy.

Various successful strategies have been applied to conjugate nucleic acids or proteins in the dendrimers, which are aimed at exploiting the specific features that are related to the dendrimers' highly branched structures and functionalizable surfaces. It is important to note that these techniques help to bring about a higher level of stability and delivery efficiency regarding these biomolecules. The nucleic acids or proteins are bound by a covalent bond with dendrimers. Dendrimers can be covalently linked by utilizing the surface reactive functional groups present on the dendrimer, such as amine, carboxyl, or hydroxyl groups. These functional groups allow biomolecules to form stable covalent bonds. Ensuring a robust and enduring bond is crucial for maintaining the bioactivity of the conjugated molecules during delivery (39).

The second approach is bioorthogonal chemistry. Chemical reactions can be utilized without impacting biological systems. Click chemistry, a widely utilized method in bioorthogonal reaction mechanisms, enables the coupling of azide-functionalized proteins or nucleic acids with alkyne-modified dendrimers. It is generally accepted for its specific, efficient, and mild action, thereby ensuring that the biomolecule of interest remains unmodified without any destruction (40). Supramolecular assembly macromolecules, such as proteins and nucleic acids, bond the dendrimers with the aid of hydrogen bonding, electrostatic interactions, and hydrophobic interactions through non-covalent forces.

Another important advantage of this approach is that the conjugates are easily disassembled at the targeted site for the release of therapeutic agents in the reversible modification strategy (41). Additionally, another option is cholesterol conjugation, a method employed to modify dendrimers to enhance the encapsulation of nucleic acids, particularly plasmid DNA, within dendrimer-based complexes. This pathway was further found to highly increase transfection efficiency due to the interaction of the complex with cell membranes, arising from increased cellular uptake (39). In particular, these approaches made dendrimers applicable as carriers for nucleic acids and proteins, ensuring effective delivery to target cells while preserving the integrity and activity of therapeutic biomolecules.

4.3.3 Applications of Dendrimers in Nucleic Acid and Protein Delivery

Dendrimers, by their own unique structural and functional characteristics, become the best carriers in applications in gene therapy, often prevailing over all other vectors. Basically, dendrimers refer to a highly branched polymer at the nanometer scale, which possess several advantages and come in handy under the complex requirements of successful genetic material delivery.

They offer a high-density surface in surface functional groups, which are able to link or encapsulate many copies of nucleic acids. This, therefore, significantly improves gene delivery, essentially achieving therapeutic levels of gene expression (42). Apart from that, dendrimers also provide desirable release kinetics because genetic material can be encapsulated either within the interior cavities or covalently attached to the surface. It implies controlled release, essential for maintaining genetic stability, as it provides for sustained release at the target site—hence the ability ever so often tested in other nanoparticle systems (43).

Moreover, dendrimers can easily be functionalized by simply attaching targeting ligands to guide the delivery vehicle to particular cells or tissues. This then increases the specificity of gene therapy and is hence more effective as the off-target effects are reduced, and hence a greater therapeutic index is obtained (44). Another great advantage is the reduction of immunogenicity and toxicity through surface modifications like PEGylation, which would make dendrimers far safer than viral vectors, with strong immune responses and possible safety issues (42).

The said synthetic versatility allows dendrimers to reach high control in terms of precise size, shape, and surface chemistry. Thereby, it can be adapted to several gene therapy applications. In addition, dendrimer synthesis has been well-evidenced to readily allow for scaling up, while some biological vectors may exhibit production difficulties at large scales (43).

Furthermore, dendrimers allow greater control over particle properties and behaviors in biological media compared to other non-viral delivery systems, such as liposomes and polymeric nanoparticles. The material easily condenses DNA, stabilizes it against nucleases' degradation, and hence promotes cellular uptake

and endosomal escape, thereby is of particular use in the gene delivery process. Though viral vectors are of high efficacy, dendrimers serve as a secure alternative with less immunogenicity to fill in some of the key limitations associated with the viral systems.

The recent trends toward the use of dendrimers for vaccine delivery increasingly point to very bright fortunes for the application of this new technology in this line. Very importantly, advancement strides have been registered to enhance the effectiveness of dendrimers and broaden the applicability range of vaccine formulations. An incredibly striking development was the design of dendrimers to exhibit multivalency, whereby many copies of either antigens or adjuvants are placed on their surface. In general, with this vaccination approach, the immunogenicity of vaccines will sharply increase due to the enhanced presentation of antigens to immune cells, in such a way strengthening and making the immune response more sustainable (45).

Additionally, dendrimers are being engineered for targeted delivery and controlled release. They can be directed at particular immune cells, such as dendritic cells, which are obligatory in the induction of immune responses. They are capable of being programmed to release their cargo of dendrimers in such a graded way, so there is antigenic exposure for the boosted immune response of longer periods and, possibly, fewer shots (28). The co-delivery of antigens and adjuvants within a single dendrimer system is another innovative approach. In this strategy, the vaccines are more potent as they guarantee that both parts get to the immune cells simultaneously, yielding better activation of the innate and adaptive immune responses (46).

There is increasing interest in the suitability of dendrimers for the delivery of nucleic acid vaccines. Such vaccines, which need protection against degradation until they reach the interior of the target cells, can show their suitability in the flexible and protective environment afforded by dendrimers. This capacity enables the dendrimers to entrap and protect those extremely labile or sensitive molecules when they are delivered (45). With an impact on the formulation, dendrimers help make a more stable formulation of the vaccine with ease in facilitation for storage and transportation. Due to their synthetic creation, they allow scaling up for the production of dendrimers. This is very important in many vaccines and across the globe for economic and sufficient responses.

All these emerging trends underline the sharper role that dendrimers are expected to play in the development of more novel and more effective systems of vaccine delivery, thus pointing toward a revolution in world health.

4.3.4 Challenges and Solutions

One of the major challenges of using dendrimers in delivery and therapeutic applications is the need to devise an innovative solution to make the process successful and free of side effects.

The complex synthesis of dendrimers, which requires precise, multistep processes, can be time-consuming and costly. Critical synthesis needs to be uniform in size and structure with consistent therapeutic outcomes (47). Further, the cytotoxicity expressed by some dendrimers is caused by surface charge and the high density of surface groups. These characteristics may act upon cellular membranes, thereby causing disruption or inducing cytotoxic responses (33). Moreover, the surface and core groups of these dendrimers are the determinants of stability and solubility. Biological fluids would act on any alteration made to the dendrimers and would determine their ability to act as a drug-delivery agent. Lastly, the regulatory standard of dendrimer synthesis to the level required can be met for clinical use and commercial production is cumbersome due to its complex synthesis route (31).

To overcome these challenges, several innovative solutions have been developed. The progress in automated synthesis, along with the investigation of novel chemical methodologies, has enabled the cost-effective production of dendrimers on a large scale (47). Dendrimers that are surface-modified, either by PEGylation or by other biocompatible coatings, bestow a remarkable reduction in toxicity. It functions by effectively blocking the groups of reactivity that are ready to be part of unwanted reactions with cellular components (33).

The addition of dendrimers, made from biocompatible materials, can enhance the stability and solubility of composite nanoparticles and hybrid systems in other biomaterials. These help in controlling the release profiles of such encapsulated drugs for their delivery and therapeutic effectiveness (37). Such development is encouraged to be engaged at an earlier stage by regulatory bodies while, in parallel, conducting preclinical studies comprehensively so as not to cause any potential regulatory hurdles.

It is thus very much essential for collaborative efforts—particularly with academic and industrial partners—to facilitate the transition from laboratory to market dendrimer-based therapies. These approaches, placed in a dynamic and ever-evolving landscape of dendrimer use in therapeutic applications, seek to highlight the potential of these nanomaterials in overcoming different life-threatening challenges posed by drug-delivery systems.

4.4 POLYMERIC MICELLES

4.4.1 Formation and Structural Characteristics

The self-assembly process of the polymeric micelles basically engenders the structural and functional properties that these micelles acquire during the whole process of assembly, something that will have a dramatic effect on the overall drug-delivery efficiency of the system.

Polymeric micelles represent core-shell-type structures formed from the spontaneous interaction of the hydrophobic core with hydrophilic block copolymers in an aqueous environment. The hydrophobic core acts as a storage area for hydrophobic drugs, enhancing the solubility and stability of the pharmaceutical compound. This is particularly beneficial for compounds that would otherwise have low solubility.

This type of encapsulation results in enhanced bioavailability within the body, allowing for more efficient utilization of the administered drug (48). In addition, micelles are stabilized by steric stabilization effects caused by the hydrophilic shell. This is crucial in preventing the micelles from aggregating in the bloodstream. Such stabilization leads to the circulation time of drug-loaded micelles being increased by quite a great percentage to levels where their residency in the bloodstream is guaranteed for longer intervals.

This strategy will prevent the prompt removal of micelles by the mononuclear phagocyte system (MPS) or renal filtration, allowing a greater number of micelles to reach the desired target sites (49). Additionally, hydrophilic outer shells can be surface-modified and functionalized to target specific tissues or cells. Covalent conjugation of targeting ligands includes antibodies or peptides to attain the targeting of cell types or receptors.

The targeted approach suggests a solution not only to losing efficiency but also to the ill effect that originates from the wide distribution of pharmaceuticals within the body (50). In addition, various self-assembled polymeric micelles are supposed to be responsive to environmental triggers such as pH, temperature, and enzymatic conditions. Such stimuli might cause structural changes to the micelles with controlled drug release from the encapsulating medium at the site of action.

For instance, this capacity has been exploited in the therapy of diseases such as cancer, whose tumor microenvironment presents peculiar conditions that can be exploited for therapy (48). Altogether, the self-assembly of polymeric micelles significantly increases their ability in drug delivery, that is, through better solubility of drugs, circulation time, and targeted and controlled drug release.

The design of core-shell polymeric micelles supports drug encapsulation and their release, while assisting further in the development and optimization of the most efficacious and safe drug-delivery system. This hydrophobic core within the polymeric micelles allows it to be a very effective means for both water-insoluble drug encapsulation and drug protection from the physiological aqueous environment and degradation. This characteristic of paramount importance increases the solubility and stability of drugs as it increases transport via the circulation system to the site of required action (51).

The hydrophilic shell in the polymeric micelles stabilizes the structure of the micelle in the bloodstream, thus preventing premature aggregation and uptake by the reticuloendothelial system; hence, it has controlled release. This shell can be further engineered to specifically react to specific environmental stimuli at the target location, such as variations in pH, temperature, or even certain types of enzymes. This enables controlled release of drugs at the right place and time for the encapsulated drug (52).

Polymeric micelles enhance therapeutic effectiveness by significantly improving the solubility and bioavailability of poorly soluble drugs, while also exerting control over their release. This facilitates the provision of an improved pharmacokinetic profile, as well as more precise targeting, enabling more accurate dosage and better management of side effects typically caused by elevated levels of unbound drugs in the body (53).

The core-shell structure also allows for flexibility in functionalization because there are plenty of locations for functionalization in both the core and the shell. This process enables the attachment of particular ligands or signaling molecules to the micelle, guiding the micelles toward specific cells or tissues. As a result, the treatment becomes more targeted and selective (54).

4.4.2 Chemical Composition and Functionalization

Block copolymers are among the most important classes of amphiphilic copolymers due to the special structural features they provide, which lead to improvements in the functional diversity of polymeric micelles and flexibility in designing targeted drug-delivery systems.

Block copolymers are structurally versatile, enabling them to easily undergo self-assembly into micelles with distinct core-shell architectures in aqueous solutions by covalently linking two or more polymer blocks of different properties. This versatility allows for designing specific types of micelles—for example, the balance between hydrophobic and hydrophilic constituents can be varied to effectively protect both kinds of drugs (55).

Core-shell-structured polymeric micelles, formed from diblock copolymers, solubilize poorly soluble drugs more effectively and provide protection from premature degradation by sensitive biological environments. The hydrophobic core entraps a hydrophobic drug, while the hydrophilic shell stabilizes the micelle in aqueous environments, thus preventing the aggregation of micelles and promoting extended circulation time in the bloodstream (56).

Block copolymers can be tuned so that they have functional groups with tissue or cell affinity. Meanwhile, the polymeric micelles can actively accumulate at specific sites in the body due to the presence of ligands or antibodies located on the surface of their outer shell, thereby decreasing the drug's side effects and increasing the efficacy of the encapsulated drug (57).

Stimuli-responsive blocks can also be introduced in copolymers so that the prepared micelles can respond to environmental changes, such as pH, temperature, or enzymatic activity. This response triggers the controlled release of encapsulated drugs at the target site, which is crucial for achieving precise therapeutic outcomes and reducing systemic drug exposure (58).

Finally, micelles of different sizes and morphologies can be designed to optimize drug-loading capacities and release kinetics. This flexibility ensures that therapeutic drugs maintain effective levels over time in the target area (59).

The most recent progress in the development of targeting ligands and stimuli-responsive elements for polymeric micelles has greatly enhanced their functionality as a precision drug-delivery system. Approaches toward improved specificity and controlled drug release have the potential effectiveness in increasing therapeutic efficacy with reduced side effects.

Recent advances have armed the polymeric micelles with very sophisticated targeting ligands that can bring about firm binding to disease-related biomarkers. It is also possible to further modify the surface of the micelles with antibodies, peptides, or small molecules, and thus obtain the possibility of their site-selective targeting toward either the cancer cells, inflamed tissues, or any other pathologically altered location. This consequently magnifies the accumulation and retention of therapeutic agents at targeted foci, hence increasing their treatment effectiveness (60).

Moreover, to provide control over stimuli, responsive groups can be incorporated within the core or corona micellar structures, resulting in the controlled release of drugs in response to specific internal or external stimuli, such as changes in pH, temperature, redox conditions, or specific enzymes that are mostly available in inflamed tissue or tumor environments. The guarantee that this mechanism provides is that the drugs are only being released at the right time and the right site of action. This improves their efficiency while reducing systemic toxicity (61).

Further advances have been made in creating polymeric micelles that respond to more than one stimulus at the same time, thereby controlling drug release. Within this modern framework, signals can originate from both internal factors (such as pH and redox) and external factors (such as light and temperature), enabling accurate and focused administration of drugs within the dynamic homeostatic ranges of the human body (62).

This can also allow for the use of cleavable linkages within the micelle structure to increase control over drug release. These links, designed to be responsive to the chemical conditions of the tumor or infection site, ensure precise and localized control over the release of drugs, thereby delivering medication directly to the specific area where it is most necessary (63).

Besides, polymeric micelles have been adapted to the application of PDT. Compared to delivering photosensitizers independently, this system enables more effective delivery and activation of photosensitizers in tumor tissues when exposed to light. As a result, the efficacy of PDT is enhanced without causing damage to the surrounding normal tissues (64).

These developments suggest that the modern platform of polymeric micelles is going to change in a way that could offer even better drug delivery in many therapeutic settings with an enhanced efficacy and safety profile.

4.4.3 Applications in Therapeutics

Polymeric micelles have been utilized to enhance the delivery of siRNA and proteins, capitalizing on their unique properties to improve therapeutic efficacy and target accuracy.

One of the leading advances includes conjugation with cell-penetrating peptides (CPPs) and polymeric micelles. These CPPs further potentiate the intracellular uptake of macromolecules, such as siRNA and proteins, allowing for better escape of the macromolecule from endosome compartments and, hence, successful gene silencing or protein function inside the target cell. It has improved the remarkably effective delivery, both for systemic and localized applications, including those to challenging targets such as the brain and inflamed tissues (65).

Another important advancement is the development of cross-linkable polyion complex micelles from polypeptide-based ABC-triblock copolymers. These micelles are better stabilized and can be engineered to give off their payload only in response to certain cellular triggers, thereby enabling greater and more site-specific siRNA delivery with fewer off-targeting effects (66).

The advantage of being protein-based micelles also includes the capacity to carry therapeutic proteins. These micelles have been designed to exploit natural protein properties, which include biocompatibility and penetration through biological barriers. The micelles facilitate the precise release and delivery of these proteins, as they operate specifically at the intended location. These particles have therefore been discovered to be highly beneficial in the treatment of various diseases that require targeted delivery and controlled release (67).

Furthermore, polymeric micelles have been designed to have a multifunctional and stimuli-responsive design. That is, these are designed for the co-packaging of proteins and siRNA at the same time, thus having stimuli-responsive drug release. The dual functionality of this approach enhances therapeutic effectiveness, particularly for diseases with complex origins like cancer, where precise and controlled action is crucial (68).

The interaction between polymeric micelles and siRNA has been extensively studied, leading to the development of optimized designs. Often supported by molecular dynamics simulations, these studies help in fine-tuning the micelle formulations so that the required therapeutic response is obtained with minimal side effects (69).

Polymeric micelles have emerged as revolutionary tools for overcoming biological barriers in drug delivery, because of their unique structural characteristics and the innovative use of block copolymers. The core-shell architecture of polymeric micelles significantly enhances the solubility of hydrophobic drugs, which is a major challenge in pharmaceutical development. By encapsulating these drugs within their hydrophobic core, micelles improve not only their solubility but also their bioavailability, facilitating their passage through biological membranes and enhancing therapeutic efficacy (68).

Polymeric micelles can be engineered to target specific tissues or cells. By modifying their surface with ligands that recognize and bind to specific receptors on the target cells, this targeting capability not only improves delivery efficiency but also minimizes the systemic side effects of drugs, ensuring that they act precisely at a site where needed without affecting other parts of the body (70).

Polymeric micelles possess the remarkable capability to traverse challenging biological barriers, including the BBB. Their small size and potential for surface modification make them ideal for delivering therapeutic agents to the brain, a region traditionally difficult to access due to the protective nature of the BBB (71).

Incorporating stimuli-responsive elements into the micelle structure enables controlled drug release in response to specific biological or environmental triggers, such as changes in pH, temperature, or the presence of specific enzymes. This capability ensures that drugs are released only in the desired location and at the right time, enhancing both treatment effectiveness and safety (71).

Lastly, polymeric micelles can optimize the pharmacokinetics of drugs. By altering the interaction dynamics between the drug and the biological environment, they can prolong the circulation time of drugs in the bloodstream, enhance tissue penetration, and reduce rapid clearance, thus maximizing the therapeutic window of the drugs (67).

4.4.4 Challenges and Future Directions

Polymeric micelles have emerged as promising delivery vehicles for drugs, yet their development and application face significant challenges that need to be addressed to fully realize their potential.

One of the primary hurdles is the stability of polymeric micelles in a biological environment. Factors such as temperature, pH, and shear forces in the bloodstream can compromise the structural integrity of the micelles, leading to premature drug release and reduced efficacy. Additionally, the safety profile of polymeric micelles is a concern, particularly regarding their interactions with non-target cells. These toxicological challenges must be rigorously evaluated in both preclinical and clinical settings to prevent adverse effects on the body. Furthermore, the regulatory landscape for nanomedicines is evolving, posing challenges due to the complexity of their design and novel drug-delivery mechanisms. Clear guidelines and standards are necessary to facilitate clinical trials and market approval (72).

Research is progressing toward the development of multifunctional polymeric micelles that can carry multiple types of therapeutic agents, such as drugs, genes, and proteins. This approach aims to improve treatment efficacy by allowing combined therapy modalities (73). Additionally, efforts are being made to create “smart” polymeric micelles that respond to specific biological stimuli for targeted drug release. These include pH-responsive, temperature-sensitive, and redox-responsive micelles that can precisely release their payload at the disease site (74). Moreover, there is a push to expand the applications of polymeric micelles beyond drug delivery to include roles in diagnostics, imaging, and as therapeutic agents themselves. This broadened scope could revolutionize how diseases are diagnosed and treated, making therapies more efficient and less invasive (75).

These insights highlight the ongoing evolution in the field of polymeric micelles, underscoring the complex challenges they face and the innovative directions they are heading toward in medical applications.

4.5 HYDROGELS

4.5.1 Hydrogel Formation and Properties

Selecting cross-linking techniques for hydrogel formation involves considering several critical factors to ensure the hydrogels meet the desired functional and performance criteria for specific applications. One critical factor is biocompatibility. The cross-linking agents and processes must not compromise the biocompatibility of the hydrogel, especially for medical applications. It is essential to select cross-linking techniques that do not release toxic substances or cause adverse reactions in biological environments (76).

Mechanical properties are also paramount. The strength, elasticity, and responsiveness of the hydrogel to mechanical stress are significantly influenced by the cross-linking density and the nature of the cross-linking bonds. Techniques that allow for precise control over cross-link density are preferred to tailor the mechanical properties according to specific needs (77). The degradation rate is crucial for applications where the hydrogel needs to biodegrade. The selected cross-linking technique should allow for the incorporation of degradable linkages that respond to environmental triggers or biological activities, enabling controlled degradation (78).

The choice between physical and chemical cross-linking techniques depends on the application. Physical cross-linking, being reversible and generally less toxic, is suitable for milder conditions. In contrast, chemical cross-linking provides more stable and durable networks suitable for demanding environments (79). Lastly, responsiveness to stimuli is important in many advanced applications. Hydrogels need to respond to specific stimuli, such as pH, temperature, and enzymes. Selecting a cross-linking technique that can incorporate responsive elements into the hydrogel network is essential for developing smart hydrogel systems (80).

The physical and chemical properties of hydrogels significantly influence their performance as drug-delivery systems, playing a critical role in how they encapsulate, protect, and release therapeutic agents. Hydrogels possess a highly hydrophilic network structure, enabling them to absorb and retain substantial amounts of water. This swelling capacity is crucial for drug release rates; hydrogels that swell rapidly and extensively tend to release drugs quickly, while those with restricted swelling provide a slower, more controlled release. This feature is vital for designing hydrogels that match the specific therapeutic goals of drug-delivery systems (81).

The porosity of hydrogels affects both the loading and subsequent release of therapeutic agents. By tailoring the size and connectivity of the pores within hydrogels, it is possible to control the diffusion rates of drugs, which is essential for achieving sustained or targeted drug release (82). The mechanical strength of hydrogels is particularly important in applications where the hydrogel must withstand physiological stresses without degrading or releasing the drug prematurely. Ongoing research aims to improve the mechanical robustness of hydrogels while maintaining their biocompatibility and effective drug-release properties (83).

For biomedical applications, it is critical that hydrogels are biodegradable, and they decompose into non-toxic by-products easily processed by the body. The rate of degradation influences the drug release rates and is a key property of hydrogels used in temporary therapeutic applications (84). Modern hydrogels are often designed to respond to specific stimuli, such as changes in pH, temperature, or the presence of certain enzymes. These stimuli-responsive hydrogels can change their network structure in response to external conditions, triggering drug release as required by specific physiological triggers (83).

Collectively, these properties play a fundamental role in defining the efficacy of hydrogels as drug-delivery systems. It is crucial to consider each property carefully during the design and development stages to ensure that the hydrogels meet the desired therapeutic outcomes effectively.

4.5.2 Modification for Biomedical Applications

The latest innovations in hydrogel technology are propelling their adaptability and efficiency, especially in fields like drug delivery and tissue engineering. These advancements are enhancing the hydrogels' ability to respond to environmental stimuli, making them smarter and more responsive to specific physiological conditions. Advancements have led to the development of hydrogels that can react to various environmental stimuli, such as temperature, pH, and biological signals. These hydrogels adapt their physical properties—like swelling or mechanical strength—in response to external conditions, making them ideal for smart drug-delivery systems that release therapeutic agents precisely when and where needed (85).

Another significant innovation involves integrating hydrogels with other responsive materials, like nanoparticles or conductive polymers. This combination enhances the hydrogels' sensitivity to electrical or magnetic fields, opening new possibilities for controlled drug release and applications in regenerative medicine (86). The introduction of dynamic cross-linking in hydrogels allows for reversible modifications in their network structure in response to environmental stimuli. This adaptability not only provides self-healing

properties but also adjustable mechanical features, making these hydrogels more robust and versatile for use in biomedical fields (87).

There is an increasing focus on developing hydrogels that can specifically respond to biomolecules or changes in the biochemical environment. For instance, glucose-responsive hydrogels that can autonomously regulate insulin release in response to blood sugar levels are being developed for diabetes management, demonstrating the potential for personalized medicine applications (88). Advancements in hydrogel technology have also led to the development of hydrogels capable of undergoing controlled shape changes in response to environmental stimuli. These shape-morphing hydrogels are being explored for use in applications such as soft robotics, wearable devices, and minimally invasive medical devices that can adapt their shape to meet specific needs (89).

Biocompatibility and degradation are essential factors meticulously managed in hydrogel design, particularly for the delivery of nucleic acids and proteins. These properties ensure safety and efficacy through innovative material design and formulation approaches.

For hydrogels used in nucleic acid and protein delivery, the choice of material is paramount. Materials like alginate, chitosan, and hyaluronic acid, which are naturally derived, are commonly used because of their inherent biocompatibility. These materials tend to provoke a minimal immune response upon administration. To further enhance biocompatibility, hydrogel surfaces can be chemically modified. Techniques such as PEGylation are applied to decrease protein adsorption and immune recognition, which helps extend the circulating life of the hydrogels and minimizes potential cytotoxic effects.

The degradation rate of hydrogels is crucially engineered to align with the therapeutic release profile of the payload. This is controlled by choosing appropriate cross-linking agents that can respond to specific environmental triggers like pH changes, temperature shifts, or the presence of certain enzymes. Additionally, certain hydrogels are designed to degrade in response to enzymes present in target tissues. For instance, gelatin-based hydrogels can be engineered to degrade through collagenase action, which is particularly beneficial for applications in tissue engineering.

Recent advancements have led to the development of nanohydrogels specifically designed for nucleic acid delivery. These biocompatible nanohydrogels are synthesized with predefined sizes and high positive zeta potential, enhancing their interaction with negatively charged DNA and RNA molecules. They are crafted to ensure minimal cell toxicity, an essential feature for safe *in vivo* applications (90).

High-strength biohydrogels have also been developed for delivering nucleic acids in treatments for conditions such as intervertebral disc degeneration. These hydrogels demonstrate superior biocompatibility and biodegradability, which is crucial for reducing immunogenicity and enabling integration with host tissues (91). Furthermore, injectable DNA hydrogels are being explored for localized drug delivery and immunotherapy, due to their exceptional biocompatibility. These hydrogels can be enzymatically cross-linked and are designed to be responsive to biological stimuli, ensuring precise degradation and payload release at the necessary time (92).

4.5.3 Role in Nucleic Acid and Protein Delivery

Hydrogels designed as sustained-release systems for nucleic acid and protein delivery have seen significant advancements, with improvements focused on optimizing their physical and chemical properties to enhance therapeutic outcomes.

Hydrogels are intricately engineered to provide controlled and sustained release of nucleic acids and proteins. This is facilitated by their network structure, which allows the gradual diffusion of therapeutic molecules. By fine-tuning the cross-linking density and the polymer composition, release rates can be precisely managed to meet specific therapeutic needs (93). Incorporating stimuli-responsive materials into hydrogel formulations enables these systems to release their payloads in response to specific biological signals, such as changes in pH, temperature, or enzyme concentrations. This targeted release approach not only helps to reduce side effects but also enhances the efficacy of treatments (94).

For sustained release, hydrogels are typically made from biocompatible and biodegradable materials to ensure safety in medical applications. These materials break down into non-toxic by-products that the body can easily metabolize or excrete, aligning with natural healing processes (95). Hydrogels provide protective environments that safeguard nucleic acids and proteins from enzymatic degradation and denaturation within the biological milieu. This protection is crucial for maintaining the functional integrity of these biomolecules until they reach their target sites (96).

Recent research has focused on developing innovative hydrogel systems that are capable of effectively loading and releasing large biomolecules, such as proteins and nucleic acids. Techniques such as embedding nanoparticles or employing hybrid systems that combine different polymeric materials have significantly enhanced the functional capabilities of these hydrogels (97).

Hydrogels are proving indispensable in the realms of tissue engineering and regenerative medicine, offering a versatile platform that supports tissue repair and regeneration across various tissues, including cardiac, bone, and neural tissues. Their unique properties are particularly suited to supporting cell growth and tissue formation, making them ideal for a wide range of medical applications.

Hydrogels provide a three-dimensional scaffold that closely mimics the natural extracellular matrix, which is essential for supporting cell adhesion, proliferation, and differentiation. This scaffolding is crucial for tissue regeneration as it offers not only structural support but also biochemical cues that facilitate tissue development and integration with surrounding tissues (98). Hydrogels can be engineered to release growth factors, cytokines, or other bioactive molecules in a controlled manner. This capability is vital for directing the tissue regeneration process, such as promoting angiogenesis in cardiac tissue engineering or osteogenesis in bone regeneration (99).

The materials used to construct hydrogels are generally biocompatible and designed to degrade at a rate that coincides with new tissue formation. This gradual degradation allows the hydrogel scaffold to be replaced by natural extracellular matrix materials as new tissue forms, which is critical for maintaining the integrity and functionality of the regenerating area (100). Advanced hydrogels can respond to environmental stimuli such as temperature, pH, or mechanical stress, which is particularly beneficial in dynamic tissue environments like the heart. For instance, hydrogels that react to mechanical stimuli can enhance the integration and functionality of engineered cardiac tissue, adapting to the unique demands of the application (101).

Hydrogels can be tailored in terms of mechanical properties, degradation rates, and biochemical functionalities to meet the specific needs of different tissue types. This level of customizability allows for the development of specialized hydrogels optimized for particular applications, such as nerve regeneration or skin repair (102).

4.5.4 Current Limitations and Research Trends

Hydrogels are pivotal in biomedical research, particularly in drug delivery, tissue engineering, and regenerative medicine. Despite their potential, the development of hydrogels encounters various challenges, with ongoing research aimed at addressing these limitations.

A significant challenge with hydrogels is their mechanical strength and stability. Traditional hydrogels often have poor mechanical properties, limiting their use in load-bearing applications where durability is crucial. Enhancing their mechanical strength without losing biocompatibility and bioactivity is a major focus area in current hydrogel research (101). While hydrogels offer potential for controlled drug release, precisely managing release rates and targeting specific tissues or cells remains challenging. Developing sophisticated release mechanisms is critical to ensuring that drugs are delivered efficiently—at the right time, in the right place, and in the correct doses (103).

Controlling the biodegradation rate of hydrogels to match the tissue regeneration pace is essential. Materials that degrade at a predictable and appropriate rate are needed to correspond with new tissue formation, optimizing therapeutic outcomes (104). Research is increasingly focusing on double-network hydrogels, which integrate two polymer networks. This approach enhances mechanical properties while maintaining biocompatibility and hydration, making these materials suitable for high-stress biomedical applications (104).

The development of injectable hydrogels that can be administered in a minimally invasive manner is gaining traction. These hydrogels combine robustness with flexibility, allowing for delivery through a syringe and opening new avenues for localized therapy applications (105). There is a continuous effort to develop hydrogels that respond to specific biological stimuli, such as pH changes, temperature shifts, or enzymatic activities. These responsive systems are particularly promising for creating effective drug-delivery systems that adapt to the body's signals, optimizing therapeutic effects.

4.6 COMPARATIVE ANALYSIS OF POLYMER-BASED NANOCARRIERS

4.6.1 Efficacy in Delivery of Nucleic Acids and Proteins

Evaluating the efficacy of polymer-based nanocarriers for the delivery of nucleic acids and proteins involves assessing several critical criteria that ensure both the efficiency of delivery and the safety of the carrier system. These criteria include encapsulation efficiency, release profile, targeting efficiency, biocompatibility and toxicity, and physicochemical stability. Nanocarriers must efficiently encapsulate nucleic acids or proteins to protect these therapeutic molecules from degradation until they reach their target. This ensures the agents are functional upon arrival at the site of action, which is crucial for the effectiveness of the treatment. Factors such as the capacity to load a high percentage of the therapeutic agent and the stability of these agents within the carrier are key measures of encapsulation efficiency (16).

The release kinetics of nucleic acids and proteins from nanocarriers must be controlled and predictable. A sustained release that aligns with the therapeutic needs of the treatment is essential for effective therapy.

The release profile should ensure that the therapeutic agents maintain their integrity and are active upon release, which is vital for the success of the treatment (13). The ability of nanocarriers to specifically target certain cells or tissues greatly impacts their efficacy. Enhancements such as targeting ligands or modifications that promote receptor-mediated uptake can significantly improve delivery specificity. This targeted approach reduces off-target effects and increases therapeutic efficacy by ensuring that the therapeutic agents are delivered precisely where needed (106).

Nanocarriers must be biocompatible and exhibit minimal toxicity, especially for clinical applications. It is crucial that the nanocarrier does not elicit significant immune responses or cause adverse side effects. Biocompatibility and minimal toxicity are fundamental for the acceptance and success of nanocarriers in medical treatments (107). The physical and chemical stability of nanocarriers under physiological conditions is essential. They must resist the body's varied environments without premature breakdown or aggregation, which could compromise their effectiveness and safety. Stability under physiological conditions ensures that nanocarriers can deliver their payload effectively and safely (106).

These criteria are essential for evaluating the efficacy of polymer-based nanocarriers in drug delivery, highlighting the importance of balancing effective drug delivery with the safety of the carrier system.

4.6.2 Biocompatibility and Safety Profiles

Evaluating the biocompatibility and safety profiles of dendrimers, polymeric micelles, and hydrogels is crucial for determining their suitability for medical applications, especially in drug delivery and tissue engineering. Each of these nanocarriers has unique properties that influence their use in clinical settings.

Dendrimers, characterized by their highly branched, tree-like structures, can be precisely engineered for various medical applications. Their biocompatibility often depends on surface modifications to mitigate the inherent toxicity associated with their cationic surface groups. Techniques like PEGylation or using biodegradable materials help enhance their safety profiles. Despite these modifications, dendrimers' biocompatibility needs careful evaluation due to their potential cytotoxicity, which can vary based on their composition and the specific application (33).

Known for their excellent biocompatibility, polymeric micelles are often made from biodegradable materials such as poly lactic acid-co-glycolic acid or PEG. Their core-shell structure is advantageous for encapsulating drugs, reducing premature interactions with the biological environment, and enhancing delivery efficiency. Although they generally have a favorable safety profile, their stability and potential immunogenic responses must be considered to ensure their safe use in medical scenarios (108).

Hydrogels are highly valued for their biocompatibility due to their hydrophilic nature and ability to mimic the extracellular matrix, which supports cell adhesion and growth. Commonly utilized in tissue engineering, hydrogels can be designed to degrade at rates that coincide with tissue regeneration, enhancing their integration and functionality. Their safety is typically high, provided that the polymers used are non-toxic and the degradation products are harmless (32).

Dendrimers often require significant surface modification to ensure biocompatibility and safety. Polymeric micelles usually offer a more straightforward safety profile but may need specific enhancements for particular applications. Hydrogels provide excellent biocompatibility naturally, but they may need adjustments in their physical properties to meet particular clinical needs.

Ultimately, the choice among dendrimers, polymeric micelles, and hydrogels for a specific medical application depends on balancing these factors against the desired therapeutic outcomes. The decision involves considering each material's unique advantages and limitations in terms of biocompatibility, safety, and the specific needs of the application.

4.6.3 Technological and Economic Considerations

When evaluating the technological and economic factors for producing nanocarriers, it is essential to consider several critical aspects to ensure efficient, cost-effective, and compliant manufacturing processes.

Advanced manufacturing techniques such as high-pressure microfluidization are critical for ensuring high-quality, reproducible production of nanocarriers. These methods must be scalable and capable of maintaining consistent particle size and distribution, which is crucial for the efficacy and safety of nanocarriers. Such approaches support scalability and help achieve uniformity in nanocarrier quality (109). The choice of polymers and their chemical properties is pivotal. Materials must be selected for their stability and ability to form nanocarriers with the desired release characteristics, as well as for their compatibility with industrial-scale synthesis processes. This selection ensures that the nanocarriers function effectively in their intended applications (110).

As production scales up, maintaining stringent quality control becomes increasingly challenging but essential. Effective methods are needed to monitor parameters like particle size, stability, and drug loading capacity consistently throughout the manufacturing process. High standards of quality control are vital for the reliability and performance of nanocarriers (111). The cost of raw materials and their availability on a large

scale significantly influence the economic viability of nanocarrier production. Economies of scale may reduce costs, but the initial investment required for high-quality, medical-grade materials can be substantial. Strategic sourcing and procurement are crucial for managing material costs effectively.

The efficiency of the production process directly affects the overall cost of nanocarriers. Techniques that minimize waste and energy consumption while maximizing output are preferred. Continuous processing modes are increasingly explored as alternatives to batch processes, offering better efficiency and lower costs due to consistent production flow. Complying with regulatory standards is critical but can entail significant costs. Expenses associated with obtaining approval from regulatory bodies like the FDA are considerable, especially for products intended for clinical use. Ensuring compliance in the early stages of product development is crucial to avoid costly revisions and delays in commercialization.

These technological and economic considerations are fundamental in navigating the complex landscape of nanocarrier production, balancing the need for innovative solutions with cost management and regulatory compliance to successfully bring these products to market.

4.7 FUTURE PERSPECTIVES AND EMERGING TRENDS

The field of polymer-based nanocarriers is on the cusp of transformative advancements that promise to revolutionize applications in drug delivery, tissue engineering, and broader medical contexts. These innovations range from smart polymers to high-performance materials, each bringing us closer to more efficient and personalized medical solutions.

Smart polymers are at the forefront of polymer science due to their ability to respond to environmental stimuli like pH, temperature, and light (Figure 4.2).




Figure 4.2 Stimuli-responsive behavior of polymer-based nanocarriers. Dendrimers maintain a compact structure in normal conditions, with pH triggering surface charge changes. They show minimal response to temperature or enzymes. Polymeric micelles exhibit a stable core-shell structure normally. pH changes cause disassembly, temperature affects shell hydration, and enzymes degrade the core, each facilitating controlled drug release. Hydrogels, initially in a swollen state, respond to all stimuli: pH and temperature induce volume changes, while enzymes cause network degradation.

This responsiveness allows for precise control over drug release and targeting, optimizing treatment efficacy and minimizing the side effects typically associated with conventional drug-delivery systems. Such capabilities are crucial in enhancing the precision of medical treatments (112). The development of biodegradable polymers is crucial to addressing the safety profiles of nanocarriers. These polymers decompose into non-toxic by-products, mitigating long-term toxicity concerns and reducing environmental impacts. Research in this area, such as that conducted by Tewari et al. (2022), focuses on ensuring that nanocarriers are not only effective in their therapeutic applications but also safe for long-term use (19).

To enhance the delivery of drugs across complex biological barriers, such as the BBB, researchers are developing high-performance polymers. These materials are designed to overcome physical and biochemical obstacles, ensuring that treatments can reach targeted areas effectively. The work by Ramasundaram et al. (2022) exemplifies efforts to tailor these polymers for specific medical needs, improving access to crucial therapy areas (112). The convergence of polymer-based nanocarriers with other nanotechnologies, such as metal nanoparticles and quantum dots, is fostering the creation of hybrid systems with dual functionalities. These systems, which combine therapeutic and diagnostic capabilities (theranostics), are being explored by researchers like Fernández and Orozco (113). Furthermore, the development of polymer nanocomposites that incorporate graphene or carbon nanotubes is enhancing crucial properties for drug delivery and tissue engineering (114). The use of layer-by-layer assembly techniques is advancing the construction of multifunctional nanocarriers. This method allows for precise control over drug release mechanisms and targeted delivery capabilities, making it a key technique for developing more effective drug-delivery systems (67). These advancements not only promise to enhance targeted and personalized treatment plans, which are tailored to the specific genetic makeup and disease conditions of patients, but also aim to reduce adverse side effects and improve patient compliance. In the field of regenerative medicine, polymer-based nanocarriers are important in providing scaffolds for tissue regeneration and delivering growth factors or genes that promote healing (115).

Collectively, these developments in polymer science and nanotechnology are poised to reshape the future of medicine, ensuring that treatments are not only more effective but also safer, more efficient, and tailored to individual patient needs.

4.8 CONCLUSION

In conclusion, polymer-based nanocarriers, including dendrimers, polymeric micelles, and hydrogels, have demonstrated substantial promise across various sectors of healthcare, such as drug delivery, tissue engineering, and regenerative medicine. Advances in polymer science and nanotechnology have not only augmented the functionality of these carriers but have also significantly improved their biocompatibility and safety profiles, making them increasingly viable for a wide range of biomedical applications.

These nanocarriers are now engineered with advanced functionalities that enable them to respond to environmental stimuli and precisely target specific cells or tissues. Such targeting capabilities markedly enhance the precision and efficacy of therapeutic delivery. Alongside these advanced features, significant improvements in polymer chemistry have boosted the biocompatibility and safety of these carriers, which are essential for their use in sensitive medical treatments.

However, scaling up the production of polymer-based nanocarriers presents substantial technological and economic challenges. Addressing these challenges is essential to ensuring the cost-effectiveness and manufacturability of these carriers on an industrial scale. Moreover, the integration of polymer-based nanocarriers with other nanotechnologies has ushered in innovative approaches to drug delivery, offering opportunities for synergistic effects that could lead to enhanced treatment outcomes.

The impact of these advancements on healthcare is profound, paving the way for more effective, targeted, and personalized treatment options. These developments underscore the critical need for ongoing research and innovation in the fields of polymer science and nanotechnology. By continuing to push the boundaries of these disciplines, we can fully unlock the potential of polymer-based nanocarriers to significantly improve patient outcomes and thus shape the future of medicine.

REFERENCES

1. Napagoda M, Witharana S. Nanotechnology in drug delivery. In: Witharana S, Napagoda MT, editors. *Nanotechnology in Modern Medicine [Internet]*. Springer Nature Singapore; 2023. p. 47–73. Available from: https://doi.org/10.1007/978-981-19-8050-3_3
2. Crossen SL, Goswami T. Nanoparticulate carriers for drug delivery. *Journal of Pharmaceutical and Biopharmaceutical Research [Internet]*. 2022 Apr 20;4(1). Available from: www.syncsci.com/journal/JPBR/article/view/JPBR.2022.01.001

3. Cai X, Jin M, Yao L, He B, Ahmed S, Safdar W, et al. Physicochemical properties, pharmacokinetics, toxicology and application of nanocarriers. *Journal of Materials Chemistry B [Internet]*. 2023;11(4):716–33. Available from: <https://doi.org/10.1039/D2TB02001G>
4. Kumar V, Nair SC. Nano lipid carriers as a promising drug delivery carrier for neurodegenerative disorders—an overview of recent advances. *Recent Patents on Biotechnology*. 2024;18(1):2–21.
5. Chamundeeswari M, Jeslin J, Verma ML. Nanocarriers for drug delivery applications. *Environmental Chemistry Letters [Internet]*. 2019;17(2):849–65. Available from: <https://doi.org/10.1007/s10311-018-00841-1>
6. Madgula K, Peddada LM, Pattathil SD. Biologically synthesized nanocarriers for targeted drug delivery applications. In: Pratap Singh R, RB Singh K, Singh J, Adetunji CO, editors. *Nanotechnology for Drug Delivery and Pharmaceuticals [Internet]*. Academic Press; 2023. p. 43–70. Available from: www.sciencedirect.com/science/article/pii/B9780323953252000092
7. Ho LWC, Liu Y, Han R, Bai Q, Choi CHJ. Nano–cell interactions of non-cationic bionanomaterials. *Accounts of Chemical Research [Internet]*. 2019 Jun 18;52(6):1519–30. Available from: <https://doi.org/10.1021/acs.accounts.9b00103>
8. Shanmugam H, Rengarajan C, Nataraj S, Sharma A. Interactions of plant food bioactives-loaded nano delivery systems at the nano-bio interface and its pharmacokinetics: An overview. *Food Frontiers*. 2022;3(2):256–75.
9. Tiwari S, Gidwani B, Namdeo P, Tripathi A, Pandey RK, Shukla SS, et al. Polymeric nanoparticles as drug delivery system: Basic concepts and applications. *Nanoparticles and Nanocarriers Based Pharmaceutical Formulations*. 2022;26: 26–54.
10. Gouthami K, Lakshminarayana L, Faniband B, Veeraraghavan V, Bilal M, Bhargava RN, et al. Introduction to polymeric nanomaterials. In: Ali N, Bilal M, Khan A, Nguyen TA, Gupta RK, editors. *Smart Polymer Nanocomposites [Internet]*. Elsevier; 2023. p. 3–25. Available from: www.sciencedirect.com/science/article/pii/B9780323916110000086
11. Zhu M, Wang X, Zhou Y, Li M, Wang Y, Wang Y, et al. Breast tumor-targeted drug delivery via polymer nanocarriers: Endogenous and exogenous strategies. *Journal of Applied Polymer Science [Internet]*. 2023;140(31):e54227. Available from: <https://onlinelibrary.wiley.com/doi/abs/10.1002/app.54227>
12. Mashal M, Attia N, Grijalvo S, Eritja R, Puras G, Pedraz JL. Stability of polymeric cationic niosomes and their plasmid DNA-based complexes as gene delivery carriers. *Drug Delivery [Internet]*. 2023 Dec 31;30(1):2219420. Available from: <https://doi.org/10.1080/10717544.2023.2219420>
13. Poudel S, Napit PR, Briski KP, Mattheolabakis G. Oral delivery of nucleic acids with passive and active targeting to the intestinal tissue using polymer-based nanocarriers. *Pharmaceutics [Internet]*. 2021;13(7):1075. Available from: www.mdpi.com/1999-4923/13/7/1075
14. Korovkina O, Polyakov D, Korzhikov-Vlakh V, Korzhikova-Vlakh E. Stimuli-responsive polypeptide nanoparticles for enhanced DNA delivery. *Molecules [Internet]*. 2022;27(23):8495. Available from: www.mdpi.com/1420-3049/27/23/8495
15. Liu J, Bao X, Kolesnik I, Jia B, Yu Z, Xing C, et al. Enhancing the in vivo stability of polycation gene carriers by using PEGylated hyaluronic acid as a shielding system. *BIO Integration*. 2022;3(3):103–11.
16. Yuan W, Li H. Polymer-based nanocarriers for therapeutic nucleic acids delivery. In: Andronesu E, Grumezescu AM, editors. *Nanostructures for Drug Delivery [Internet]*. Elsevier; 2017. p. 445–60. Available from: www.sciencedirect.com/science/article/pii/B9780323461436000142

17. Yoon H. Polymer nanomaterials in biomedicine. *International Journal of Molecular Sciences* [Internet]. 2023;24(8):7480. Available from: www.mdpi.com/1422-0067/24/8/7480
18. Sathasivam T, Gugler MC, Janarthanan P. Polymers in nanomedicine. In: Arivarasan VK, Loganathan K, Janarthanan P, editors. *Nanotechnology in Medicine* [Internet]. Springer International Publishing; 2021. p. 175–98. Available from: https://doi.org/10.1007/978-3-030-61021-0_10
19. Tewari AK, Upadhyay SC, Kumar M, Pathak K, Kaushik D, Verma R, et al. Insights on development aspects of polymeric nanocarriers: The translation from bench to clinic. *Polymers (Basel)* [Internet]. 2022;14(17). Available from: www.mdpi.com/2073-4360/14/17/3545
20. Niculescu AG, Grumezescu AM. Polymer-based nanosystems—a versatile delivery approach. *Materials* [Internet]. 2021;14(22):6812. Available from: www.mdpi.com/1996-1944/14/22/6812
21. Muhammad K, Zhao J, Gao B, Feng Y. Polymeric nano-carriers for on-demand delivery of genes via specific responses to stimuli. *Journal of Materials Chemistry B* [Internet]. 2020;8(42):9621–41. Available from: <https://doi.org/10.1039/D0TB01675F>
22. Markwalter C, Wang L, Sharaf O, Padakanti P, Esposito M, Wilson B, et al. Polymeric nanocarriers co-encapsulating PET probes and protein therapeutics. *Precision Nanomedicine*. 2022;6(1):994–1006.
23. De R, Song YH, Mahata MK, Lee KT. pH-responsive polyelectrolyte complexation on upconversion nanoparticles: A multifunctional nanocarrier for protection, delivery, and 3D-imaging of therapeutic protein. *Journal of Materials Chemistry B* [Internet]. 2022;10(18):3420–33. Available from: <https://doi.org/10.1039/D2TB00246A>
24. Ramírez-Acosta CM, Cifuentes J, Castellanos MC, Moreno RJ, Muñoz-Camargo C, Cruz JC, et al. pH-responsive, cell-penetrating, core/shell magnetite/silver nanoparticles for the delivery of plasmids: Preparation, characterization, and preliminary in vitro evaluation. *Pharmaceutics*. 2020;12(6):561.
25. Subhan MA, Parveen F, Filipczak N, Yalamarty SSK, Torchilin VP. Approaches to improve EPR-based drug delivery for cancer therapy and diagnosis. *Journal of Personalized Medicine*, 2023, 13(3), 389.
26. de Oliveira Cardoso VM, Ferreira LMB, Comparetti EJ, Sampaio I, Ferreira NN, Miranda RR, et al. Stimuli-responsive polymeric nanoparticles as controlled drug delivery systems. In: Gajbhiye V, Gajbhiye KR, Hong S, editors. *Stimuli-Responsive Nanocarriers*. Elsevier; 2022. p. 87–117.
27. Zhang X, Zhang M, Wu M, Yang L, Liu R, Zhang R, et al. Precise controlled target molecule release through light-triggered charge reversal bridged polysilsesquioxane nanoparticles. *Polymers (Basel)*. 2021;13(15):2392.
28. Mishra S. Hyperbranched nanostructure drug delivery carrier: Dendrimer. *Nanoscience and Nanotechnology-Asia*. 2023;13(1):20–5.
29. Rastogi V, Yadav P, Porwal M, Sur S, Verma A. Dendrimer as nanocarrier for drug delivery and drug targeting therapeutics: A fundamental to advanced systematic review. *International Journal of Polymeric Materials and Polymeric Biomaterials*. 2024;73(4):310–32.
30. Sharma S. Dendrimers in nanomedicine: History, concept and properties of dendrimers. In: *Dendrimers in Nanomedicine*. CRC Press; 2021. p. 41–51.
31. Aravind M, Kumar SP, Begum ASK. An overview of dendrimers as novel carriers in drug delivery. *Research Journal of Pharmacy and Technology*. 2023;16(4):2051–6.
32. Wang J, Li B, Qiu L, Qiao X, Yang H. Dendrimer-based drug delivery systems: History, challenges, and latest developments. *Journal of Biological Engineering*. 2022;16(1):18.

33. Li X, Naeem A, Xiao S, Hu L, Zhang J, Zheng Q. Safety challenges and application strategies for the use of dendrimers in medicine. *Pharmaceutics* [Internet]. 2022;14(6):1292. Available from: www.mdpi.com/1999-4923/14/6/1292
34. Singh N, Kumar V. An overview on surface modified dendrimers: Current direction and future perspectives. *Advanced Chemicobiology Research*. 2023;30–41.
35. Jeevanandam J, Tan KX, Rodrigues J, Danquah MK. Target-specific delivery and bioavailability of pharmaceuticals via Janus and dendrimer particles. *Pharmaceutics*. 2023;15(6):1614.
36. Mahmoudi A, Sadi KS, Malaekheh-Nikouei B. Surface engineered dendrimers as novel option for enhanced pharmaceutical and biomedical potential. In: *Dendrimer-Based Nanotherapeutics*. Elsevier; 2021. p. 225–52.
37. Zenze M, Daniels A, Singh M. Dendrimers as modifiers of inorganic nanoparticles for therapeutic delivery in cancer. *Pharmaceutics*. 2023;15(2):398.
38. Prajapati SK, Jain A. Dendrimers for advanced drug delivery. *Advanced Biopolymeric Systems for Drug Delivery*. 2020;339–60.
39. Golkar N, Samani SM, Tamaddon AM. Cholesterol-conjugated supramolecular assemblies of low generations polyamidoamine dendrimers for enhanced EGFP plasmid DNA transfection. *Journal of Nanoparticle Research*. 2016;18:1–20.
40. Gupta K, Singh S, Gupta K, Khan N, Sehgal D, Haridas V, et al. A bioorthogonal chemoenzymatic strategy for defined protein dendrimer assembly. *ChemBioChem*. 2012;13(17):2489–94.
41. Bae J, Kim H, Kim G, Song J, Kim H. Dendrimer-like supramolecular assembly of proteins with a tunable size and valency through stepwise iterative growth. *Advanced Science*. 2021;8(24):2102991.
42. Shetty A, Chikhaliwala P, Suryawanshi J, Chandra S. Understanding physico-chemical interactions of dendrimers with guest molecules for efficient drug and gene delivery. *Current Pathobiology Reports*. 2021;9:57–70.
43. Chis AA, Dobrea CM, Rus LL, Frum A, Morgovan C, Butuca A, et al. Dendrimers as non-viral vectors in gene-directed enzyme prodrug therapy. *Molecules*. 2021;26(19):5976.
44. Baswar D, Devi A, Mishra A. Dendrimers in gene delivery. In: *Dendrimers in Nanomedicine*. CRC Press; 2021. p. 187–99.
45. Kisakova LA, Apartsin EK, Nizolenko LF, Karpenko LI. Dendrimer-mediated delivery of DNA and RNA vaccines. *Pharmaceutics*. 2023;15(4):1106.
46. Bober Z, Bartusik-Aebischer D, Aebischer D. Application of dendrimers in anticancer diagnostics and therapy. *Molecules*. 2022;27(10):3237.
47. Li H, Zha S, Li H, Liu H, Wong K, All AH. Polymeric dendrimers as nanocarrier vectors for neurotheranostics. *Small*. 2022;18(45):2203629.
48. Kuperkar K, Patel D, Atanase LI, Bahadur P. Amphiphilic block copolymers: Their structures, and self-assembly to polymeric micelles and polymersomes as drug delivery vehicles. *Polymers (Basel)*. 2022;14(21):4702.
49. Wang H, Ullah A. Synthesis and evaluation of thermoresponsive renewable lipid-based block copolymers for drug delivery. *Polymers (Basel)*. 2022;14(17):3436.
50. Yoshizaki Y, Yamasaki M, Nagata T, Suzuki K, Yamada R, Kato T, et al. Drug delivery with hyaluronic acid-coated polymeric micelles in liver fibrosis therapy. *ACS Biomaterials Science & Engineering*. 2023;9(6):3414–24.

51. Cheng X, Li Q, Sun X, Ma Y, Xie H, Kong W, et al. Well-defined shell-sheddable core-crosslinked micelles with pH and oxidation dual-response for on-demand drug delivery. *Polymers (Basel)*. 2023;15(9):1990.
52. Varga N, Bélteki R, Juhász Á, Csapó E. Core-shell structured PLGA particles having highly controllable ketoprofen drug release. *Pharmaceutics*. 2023;15(5):1355.
53. Mehandole A, Walke N, Mahajan S, Aalhathe M, Maji I, Gupta U, et al. Core-shell type lipidic and polymeric nanocapsules: The transformative multifaceted delivery systems. *AAPS PharmSciTech*. 2023;24(1):50.
54. Vambhurkar G, Jain N, Srinivasarao DA, Famta P, Singh SB, Srivastava S. Drug solubilization and drug release from polymeric micelles. In: *Polymeric Micelles: Principles, Perspectives and Practices*. Springer; 2023. p. 87–109.
55. Arora V, Bhandari DD, Puri R, Khatri N, Dureja H. Synthesis, self-assembly, and functional chemistry of amphiphilic block copolymers. In: *Polymeric Micelles: Principles, Perspectives and Practices*. Springer; 2023. p. 1–25.
56. Chen Z, Deng S, Tian L. Advances in the preparation and application of polymeric micelles. In: *Eighth International Conference on Energy Materials and Electrical Engineering (ICEMEE 2022)*. SPIE; 2023. p. 45–54.
57. Ali A, Bhadane R, Asl AA, Wilén CE, Salo-Ahen O, Rosenholm JM, et al. Functional block copolymer micelles based on poly (jasmine lactone) for improving the loading efficiency of weakly basic drugs. *RSC Advances*. 2022;12(41):26763–75.
58. Liu T, Lang M. Preparation and characterization of novel functional tri-block copolymer for constructing temperature/redox dual-stimuli responsive micelles. *Journal of Macromolecular Science, Part A*. 2022;59(8):513–25.
59. He Y, Tang Y, Zhang Y, MacFarlane L, Shang J, Shi H, et al. Published under an exclusive license by AIP Publishing. *Applied Physics Reviews*. 2022;9(2).
60. Jin GW, Rejinold NS, Choy JH. Multifunctional polymeric micelles for cancer therapy. *Polymers (Basel)*. 2022;14(22):4839.
61. Jain KK, Kadam AY, Tomar Y, Singhvi G. Stimuli-sensitive polymeric micelles for biomedical applications. *Polymeric Micelles: Principles, Perspectives and Practices*. 2023;125–54.
62. Mahajan D, Soares D, Rachana R, Shetty S. Types of polymeric micelles for controlled drug release. In: Singh SK, Gulati M, Mutalik S, Dhanasekaran M, Dua K, editors. *Polymeric Micelles: Principles, Perspectives and Practices [Internet]*. Springer Nature Singapore; 2023. p. 69–86. Available from: https://doi.org/10.1007/978-981-99-0361-0_4
63. Arafa KK, El-Sherbiny IM. Polymeric micelles with cleavable links for drug delivery. In: Kesharwani P, Greish K, editors. *Polymeric Micelles for Drug Delivery [Internet]*. Woodhead Publishing; 2022. p. 515–30. (Woodhead Publishing Series in Biomaterials). Available from: www.sciencedirect.com/science/article/pii/B9780323898683000203
64. de Santana WMOS, Pochapski DJ, Pulcinelli SH, Fontana CR, Santilli CV. Polymeric micelles-mediated photodynamic therapy. In: Kesharwani P, editor. *Nanomaterials for Photodynamic Therapy [Internet]*. Woodhead Publishing; 2023. p. 105–39. (Woodhead Publishing Series in Biomaterials). Available from: www.sciencedirect.com/science/article/pii/B9780323855952000037
65. Kanazawa T. Cell-penetrating peptide-conjugated polymer micelle for pDNA/siRNA delivery. In: *Cell-Penetrating Peptides [Internet]*. John Wiley & Sons, Ltd; 2023. p. 285–313. Available from: <https://onlinelibrary.wiley.com/doi/abs/10.1002/9783527835997.ch16>

66. Capelôla L, Yazdi M, Zhang H, Chen X, Nie Y, Wagner E, et al. Cross-linkable polyion complex micelles from polypept(o)ide-based ABC-triblock copolymers for siRNA delivery. *Macromolecular Rapid Communications [Internet]*. 2022;43(12):2100698. Available from: <https://onlinelibrary.wiley.com/doi/abs/10.1002/marc.202100698>
67. Mustafai A, Zubair M, Hussain A, Ullah A. Recent progress in proteins-based micelles as drug delivery carriers. *Polymers (Basel) [Internet]*. 2023;15(4):836. Available from: www.mdpi.com/2073-4360/15/4/836
68. Ashique S, Garg A, Hussain A, Bhatt S, Agrawal A, Mishra, N. Polymeric micelles in the delivery of proteins. In: Singh SK, Gulati M, Mutalik S, Dhanasekaran M, Dua K, editors. *Polymeric Micelles: Principles, Perspectives and Practices [Internet]*. Springer Nature Singapore; 2023. p. 231–51. Available from: https://doi.org/10.1007/978-981-99-0361-0_12
69. Marquet F, Stojceski F, Grasso G, Patrulea V, Danani A, Borchard G. Characterization of the interaction of polymeric micelles with siRNA: A combined experimental and molecular dynamics study. *Polymers (Basel) [Internet]*. 2022;14(20):4409. Available from: www.mdpi.com/2073-4360/14/20/4409
70. Jain KK, Kadam AY, Tomar Y, Singhvi G. Stimuli-sensitive polymeric micelles for biomedical applications. In: Singh SK, Gulati M, Mutalik S, Dhanasekaran M, Dua K, editors. *Polymeric Micelles: Principles, Perspectives and Practices [Internet]*. Springer Nature Singapore; 2023. p. 125–54. Available from: https://doi.org/10.1007/978-981-99-0361-0_7
71. Kaur J, Gulati M, Kapoor B, Jha NK, Gupta PK, Gupta G, et al. Advances in designing of polymeric micelles for biomedical application in brain related diseases. *Chemico-Biological Interactions [Internet]*. 2022;361:109960. Available from: www.sciencedirect.com/science/article/pii/S000927972200165X
72. Thirugnanasambandham I, Aasaithambi K, Nizam I, Kuppusamy G. Stability of polymeric micelles and their regulatory status. In: Singh SK, Gulati M, Mutalik S, Dhanasekaran M, Dua K, editors. *Polymeric Micelles: Principles, Perspectives and Practices [Internet]*. Springer Nature Singapore; 2023. p. 277–94. Available from: https://doi.org/10.1007/978-981-99-0361-0_15
73. Wang C, Wang Z, Zhao X, Yu F, Quan Y, Cheng Y, et al. DOX loaded aggregation-induced emission active polymeric nanoparticles as a fluorescence resonance energy transfer traceable drug delivery system for self-indicating cancer therapy. *Acta Biomaterialia [Internet]*. 2019;85:218–28. Available from: www.sciencedirect.com/science/article/pii/S1742706118307451
74. Pérez SE, Haidar ZS. Polymeric micelles: Précis for past, present and future. In: Kesharwani P, Greish K, editors. *Polymeric Micelles for Drug Delivery [Internet]*. Woodhead Publishing; 2022. p. 3–14. (Woodhead Publishing Series in Biomaterials). Available from: www.sciencedirect.com/science/article/pii/B9780323898683000197
75. Chen Z, Deng S, Tian L. Advances in the preparation and application of polymeric micelles. In: Palanisamy T, Han LB, editors. *Eighth International Conference on Energy Materials and Electrical Engineering (ICEMEE 2022) [Internet]*. SPIE; 2023. p. 1259809. Available from: <https://doi.org/10.1117/12.2672920>
76. Bhattacharjee P, Ahearne M. Significance of crosslinking approaches in the development of next generation hydrogels for corneal tissue engineering. *Pharmaceutics [Internet]*. 2021;13(3):319. Available from: www.mdpi.com/1999-4923/13/3/319
77. Gao Y, Peng K, Mitragotri S. Covalently crosslinked hydrogels via step-growth reactions: Crosslinking chemistries, polymers, and clinical impact. *Advanced Materials [Internet]*. 2021;33(25):2006362. Available from: <https://onlinelibrary.wiley.com/doi/abs/10.1002/adma.202006362>

78. Zhang Z, He C, Rong Y, Ren H, Wang T, Zou Z, et al. A fast and versatile cross-linking strategy via o-phthalaldehyde condensation for mechanically strengthened and functional hydrogels. *National Science Review*. 2021 Apr 1;8(4):nwaa128.
79. Maitra J, Shukla VK, Kumar Shukla V. Cross-linking in hydrogels—a review. *American Journal of Polymer Science [Internet]*. 2014;2014(2):25–31. Available from: <https://journal.sapub.org/ajps>
80. Mark T, Elia G. *Crosslinkable Hydrogel Compositions [Internet]*. Available from: <https://lens.org/074-385-178-151-629>
81. Ai Y, Lin Z, Zhao W, Cui M, Qi W, Huang R, et al. Nanocellulose-based hydrogels for drug delivery. *Journal of Materials Chemistry B [Internet]*. 2023;11(30):7004–23. Available from: <https://dx.doi.org/10.1039/D3TB00478C>
82. Kumar A, Patra P, Nutan B, Bhalani DV, Chandel AKS. Polymeric hydrogels as drug delivery vehicles. *Preprints (Basel) [Internet]*. 2023 Jun. Available from: <https://doi.org/10.20944/preprints202306.1118.v1>
83. Thang NH, Chien TB, Cuong DX. Polymer-based hydrogels applied in drug delivery: An overview. *Gels [Internet]*. 2023;9(7):523. Available from: www.mdpi.com/2310-2861/9/7/523
84. Akhtar S, Singh G, Singh SP, Kumar S, Malik JK. Current scenario of hydrogel as drug delivery system. *South Asian Research Journal of Pharmaceutical Sciences*. 2023 Mar 15;5(2):33–7.
85. Serpico L, Dello Iacono S, Cammarano A, De Stefano L. Recent advances in stimuli-responsive hydrogel-based wound dressing. *Gels [Internet]*. 2023;9(6):451. Available from: www.mdpi.com/2310-2861/9/6/451
86. Garcia-Torres J. Hybrid hydrogels with stimuli-responsive properties to electric and magnetic fields. In: Popa L, Ghica MV, Dinu-Pirvu CE, editors. *Hydrogels [Internet]*. IntechOpen; 2022. Available from: <https://doi.org/10.5772/intechopen.102436>
87. Howard E, Li M, Kozma M, Zhao J, Bae J. Self-strengthening stimuli-responsive nanocomposite hydrogels. *Nanoscale [Internet]*. 2022;14(48):17887–94. Available from: <https://doi.org/10.1039/D2NR05408F>
88. Lin Z, Ding J, Chen X, He C. pH- and temperature-responsive hydrogels based on tertiary amine-modified polypeptides for stimuli-responsive drug delivery. *Chemistry: An Asian Journal [Internet]*. 2023;18(8):e202300021. Available from: <https://aces.onlinelibrary.wiley.com/doi/abs/10.1002/asia.202300021>
89. Liu X, Gao M, Chen J, Guo S, Zhu W, Bai L, et al. Recent advances in stimuli-responsive shape-morphing hydrogels. *Advanced Functional Materials [Internet]*. 2022;32(39):2203323. Available from: <https://onlinelibrary.wiley.com/doi/abs/10.1002/adfm.202203323>
90. Eswaran L, Kazimirsky G, Byk G. New biocompatible nanohydrogels of predefined sizes for complexing nucleic acids. *Pharmaceutics [Internet]*. 2023;15(2):332. Available from: www.mdpi.com/1999-4923/15/2/332
91. Chen T, Qian Q, Makvandi P, Zare EN, Chen Q, Chen L, et al. Engineered high-strength biohydrogel as a multifunctional platform to deliver nucleic acid for ameliorating intervertebral disc degeneration. *Bioactive Materials [Internet]*. 2023;25:107–21. Available from: www.sciencedirect.com/science/article/pii/S2452199X23000105
92. Wang Q, Qu Y, Zhang Z, Huang H, Xu Y, Shen F, et al. Injectable DNA hydrogel-based local drug delivery and immunotherapy. *Gels [Internet]*. 2022;8(7):400. Available from: www.mdpi.com/2310-2861/8/7/400

93. Ke L, Wu YL, Tian H. Preparation and evaluation of supramolecular hydrogels for localized sustained gene delivery. In: Tian H, Chen, X, editors. *Gene Delivery [Internet]*. Springer Singapore; 2021. p. 1–16. Available from: https://doi.org/10.1007/978-981-33-6198-0_13-1
94. Ali S, Ranjha NM, Ahmad B, Khan AA, Hassan FU, Aziz T, et al. Sustained release of drug facilitated through chemically crosslinked polyvinyl alcohol-gelatin (PVA-GE) hydrogels. A sustainable biomedical approach. *Polish Journal of Chemical Technology [Internet]*. 2023;25(2):56–65. Available from: <https://doi.org/10.2478/pjct-2023-0017>
95. Nalbadis A, Trutschel ML, Lucas H, Luetzkendorf J, Meister A, Mäder K. Selection and incorporation of siRNA carrying non-viral vector for sustained delivery from gellan gum hydrogels. *Pharmaceutics [Internet]*. 2021;13(10):1546. Available from: www.mdpi.com/1999-4923/13/10/1546
96. del Olmo JA, Martínez VS, González RP, Alonso JM. Sustained drug release from biopolymer-based hydrogels and hydrogel coatings. In: Popa L, Ghica MV, Dinu-Pîrvu CE, editors. *Hydrogels [Internet]*. IntechOpen; 2022. Available from: <https://doi.org/10.5772/intechopen.103946>
97. Rafael D, Guerrero M, Marican A, Arango D, Sarmiento B, Ferrer R, et al. Delivery systems in ocular retinopathies: The promising future of intravitreal hydrogels as sustained-release dcavoids. *Pharmaceutics [Internet]*. 2023;15(5):1484. Available from: www.mdpi.com/1999-4923/15/5/1484
98. Amirthalingam S, Rajendran AK, Moon YG, Hwang NS. Stimuli-responsive dynamic hydrogels: Design, properties and tissue engineering applications. *Materials Horizons [Internet]*. 2023;10(9):3325–50. Available from: <https://doi.org/10.1039/D3MH00399J>
99. Syed Mohamed SMD, Welsh GI, Roy I. Renal tissue engineering for regenerative medicine using polymers and hydrogels. *Biomaterials Science [Internet]*. 2023;11(17):5706–26. Available from: <https://doi.org/10.1039/D3BM00255A>
100. Jurczak P, Lach S. Hydrogels as scaffolds in bone-related tissue engineering and regeneration. *Macromolecular Bioscience [Internet]*. 2023;23(11):2300152. Available from: <https://onlinelibrary.wiley.com/doi/abs/10.1002/mabi.202300152>
101. Fang W, Yang M, Wang L, Li W, Liu M, Jin Y, et al. Hydrogels for 3D bioprinting in tissue engineering and regenerative medicine: Current progress and challenges. *International Journal of Bioprinting*. 2023;9:207–38. AccScience Publishing.
102. Li X, Xu M, Geng Z, Liu Y. Functional hydrogels for the repair and regeneration of tissue defects. *Frontiers in Bioengineering and Biotechnology [Internet]*. 2023;11:1190171. Available from: www.frontiersin.org/journals/bioengineering-and-biotechnology/articles/10.3389/fbioe.2023.1190171
103. Lin KT, Wang A, Nguyen AB, Iyer J, Tran SD. Recent advances in hydrogels: Ophthalmic applications in cell delivery, vitreous substitutes, and ocular adhesives. *Biomedicines [Internet]*. 2021;9(9):1203. Available from: www.mdpi.com/2227-9059/9/9/1203
104. Huang M, Huang Y, Liu H, Tang Z, Chen Y, Huang Z, et al. Hydrogels for the treatment of oral and maxillofacial diseases: Current research, challenges, and future directions. *Biomaterials Science [Internet]*. 2022;10(22):6413–46. Available from: <https://doi.org/10.1039/D2BM01036D>
105. Almwash S, Osman SK, Mustafa G, El Hamd MA. Current and future prospective of injectable hydrogels—design challenges and limitations. *Pharmaceutics [Internet]*. 2022;15(3):371. Available from: www.mdpi.com/1424-8247/15/3/371
106. Sadeqi Nezhad M. Poly (beta-amino ester) as an in vivo nanocarrier for therapeutic nucleic acids. *Biotechnology and Bioengineering [Internet]*. 2023;120(1):95–113. Available from: <https://analyticalsciencejournals.onlinelibrary.wiley.com/doi/abs/10.1002/bit.28269>

107. Singh M. Assessing nucleic acid: Cationic nanoparticle interaction for gene delivery. In: Narayanan K, editor. *Bio-Carrier Vectors: Methods and Protocols [Internet]*. Springer US; 2021. p. 43–55. Available from: https://doi.org/10.1007/978-1-0716-0943-9_4
108. Parshad B, Yadav P, Kerkhoff Y, Mittal A, Achazi K, Haag R, et al. Dendrimer-based micelles as cyto-compatible nanocarriers. *New Journal of Chemistry [Internet]*. 2019;43(30):11984–93. Available from: <https://doi.org/10.1039/C9NJ02612F>
109. Alkanawati MS, Wurm FR, Thérien-Aubin H, Landfester K. Large-scale preparation of polymer nanocarriers by high-pressure microfluidization. *Macromolecular Materials and Engineering [Internet]*. 2018;303(1):1700505. Available from: <https://onlinelibrary.wiley.com/doi/abs/10.1002/mame.201700505>
110. Förster N, Schmidt S, Vana P. Tailoring confinement: Nano-carrier synthesis via Z-RAFT Star Polymerization. *Polymers (Basel) [Internet]*. 2015;7(4):695–716. Available from: www.mdpi.com/2073-4360/7/4/695
111. Singh R, Rhee HW. Chapter 24 – Industrial scale-up: Lab to commercial-scale manufacturing of POSS composites. In: Thomas S, Somasekharan L, editors. *Polyhedral Oligomeric Silsesquioxane (POSS) Polymer Nanocomposites [Internet]*. Elsevier; 2021. p. 499–516. Available from: www.sciencedirect.com/science/article/pii/B9780128213476000196
112. Ramasundaram S, Sobha S, Saravanakumar G, Oh TH. Recent advances in biomedical applications of polymeric nanoplateform assisted with two-photon absorption process. *Polymers (Basel) [Internet]*. 2022;14(23):5134. Available from: www.mdpi.com/2073-4360/14/23/5134
113. Fernández M, Orozco J. Advances in functionalized photosensitive polymeric nanocarriers. *Polymers (Basel) [Internet]*. 2021;13(15):2464. Available from: www.mdpi.com/2073-4360/13/15/2464
114. Shin M, Lim J, Park Y, Lee JY, Yoon J, Choi JW. Carbon-based nanocomposites for biomedical applications. *RSC Advances [Internet]*. 2024;14(10):7142–56. Available from: <https://doi.org/10.1039/D3RA08946K>
115. Zhang W, Hou Y, Yin S, Miao Q, Lee K, Zhou X, et al. Advanced gene nanocarriers/scaffolds in nonviral-mediated delivery system for tissue regeneration and repair. *Journal of Nanobiotechnology [Internet]*. 2024;22(1):376. Available from: <https://doi.org/10.1186/s12951-024-02580-8>