



振石集团东方特钢有限公司  
ZHENSHI GROUP EASTERN  
SPECIAL STEEL CO., LTD

# 产品质量证明书

## INSPECTION CERTIFICATE

公司地址: 浙江省嘉兴市南湖区新丰镇经济开发区  
ECONOMIC DEVELOPMENT ZONE, XINFENG COUNTRY, NANHU  
DISTRICT, JIAXING CITY 314005, ZHEJIANG PROVINCE.

订货单位 CUSTOMER			产品名称 PRODUCT	热轧不锈钢带 HOT-ROLLED STAINLESS STEEL COILS		证书号 CERTIFICATE NO.	170117050														
收货单位 PURCHASER			合同号 CONTRACT NO.	ESS(XS)/XS-YRS20170109-171		交货日期 DATE OF DELIVERY	2017年1月16日														
牌号 GRADE	304		订单号 ORDER NO.			签发日期 DATE OF ISSUE	2017年1月17日														
标准 SPECIFICATION	ASTM A240M-13a		交货状态 SOLUTION TREATED AND PICKLING	NO. 1		ISO9001证书号 CERTIFICATE NUMBER	CN10/21015														
序号	钢卷/板号 COIL/PLATE NO.	炉号 HEAT NO.	规格及重量 MATERIAL DESCRIPTION					化学成分(熔炼分析) % CHEMICAL COMPOSITION (HEAT ANALYSIS) %													
			厚度 THICK	宽度 WIDTH	长度 LENGTH	件数 NUMBER	重量 WEIGHT	C	Si	Mn	P	S	Cr	Ti	Ni	Mo	N				
			mm			件	kg														
1	116165720300	1616572	7.75	1525	C	1	28970	0.038	0.40	1.36	0.026	0.002	18.09		8.04		0.052				
2	116168790200	1616879	11.45	1525	C	1	26385	0.043	0.40	1.27	0.037	0.007	18.08		8.08		0.052				
3	117100660300	1710066	5.75	1520	C	1	25415	0.045	0.42	1.26	0.030	0.004	18.08		8.07		0.059				
4	117100860200	1710086	4.75	1525	C	1	26325	0.034	0.35	1.28	0.031	0.005	18.06		8.05		0.055				
5	117100990100	1710099	5.45	1525	C	1	24510	0.059	0.45	1.27	0.027	0.002	18.04		8.08		0.056				
合计(TOTAL)								5	131605												
序号	钢卷/板号 COIL/PLATE NO.	拉伸试验TENSILE TEST			硬度	弯曲 试验	ISO-V冲击试验 IMPACT TEST						晶间腐蚀								
		抗拉强度 (T.S.)	屈服强度 (Y.S.)	断后伸长 率(EL.)	HARDNESS	方向	宽度	温度	ABSORBED ENERGY (J)			INTERGRANULAR CORROSION TEST									
		Rm	Rp0.2	A50	HR	LR	W	TEM	KV												
		Mpa		%	1	LR	mm	℃	1	2	3										
1	116165720300	676	277	63	86	87															
2	116168790200	729	314	62	88	86															
3	117100660300	696	290	66	86	84															
4	117100860200	686	259	60	85	86															
5	117100990100	690	299	63	88	86															
备注 REMARKS		1. 本产品已通过ISO9001质量认证许可 (THE PRODUCT HAVE PASSED THE ISO9001 QUALITY CERTIFICATION LICENSE.) 2. 谨保证以上所有的内容真实准确 (WE HEREBY CERTIFY THE ABOVE STATEMENT TO BE TRUE AND CORRECT IN EVERY DETAIL.) 3. 热处理 (HEAT TREATMENT): SOLUTION 1050-1100℃ QUENCHING IN WATER 4. The material is free from Radioactive Contamination.																			
注释 NOTES		TR: (Transverse)横向, L: (Longitudinal)纵向, DIR: (Direction)方向, W: (Width)宽度, TEM: (temperature)温度, EL: (Elongation)断后伸长率, Y.S.: (Yield Strength)屈服强度, T.S.: (Tensile Strength)抗拉强度, A.E.: 吸收能量, AVE: 平均值																			

质量负责人  
QUALITY MANAGER

董峰