

Test Report

Documentation of the internal Test



Product / Project	Articlenumber	Testdate	Examiner
R-Tec Liner 550mm EW/EWX 70	83693082	13.12.2017	H. Thaidigsmann

01 Products tested

Articlenumber	Description	Cycles
83693082	R-Tec Liner 550mm EW/EWX 70	17,75 million
83182080	EWX-PAE 70	13,1 million
83692468	KEG-K	17,75 million
83692802	V-ZLT 70	17,75 million
83692688	Feder-Set 56/70 200N	17,75 million
83693020	Slider EW/EWX 70 R-Tec Liner	17,75 million
83693036	TRO R-Tec Liner 50/70	17,75 million
83691502	SH-M 56/70-M	17,75 million

02 Pictures / Documentation

Start of test |



Test Setup


H. Thaidigsmann

murrplastik
Simply Smart Systems

Murrplastik Systemtechnik GmbH
Dieselstraße 10 | D-71570 Oppenweiler
+49(0)7191482-0 | murrplastik.de

Internal Documentation

End of test |



Test Setup after 219 days and 17.755.473 Cycles

03 Result / Conclusion

Result	Over 17 million cycles, one conduit break after 13,1 million.
Abnormalities	After 17 million cycles the test was still running, but there were distinct "knocking" noises audible, caused by excessive play
Rating	System was still running, replacing the slider would easily fix the noises. Test was concluded by the product management team and deemed very successful

7.02