Valkov PG 70-22

Product Data Sheet | Polymer Modified Asphalt Binder

Applications

Enhanced high-temperature performance for heavier traffic and tougher service conditions.

Specification Summary

Characteristics	Unit	Limits	Actual Result	Test Methods
Average 7-day maximum pavement design temperature	deg C	<70	68.9	
Minimum pavement design temperature	deg C	>-22	-22	
Flash Point	deg C	Min. 230	318	AASHTO T48
Viscosity @135 deg C	Pa.s	Max. 3.0	0.78	AASHTO T316
Dynamic Shear, original binder at 70 deg C	kPa	Min. 1.0	1.38	AASHTO T315
Mass change, RTFO residue	%Wt	Max. 1.0	0.21	AASHTO T240
Dynamic Shear, RTFO residue at 70 deg C	kPa	Min. 2.2	2.67	AASHTO T315
PAV Temperature	deg C	100	100	AASHTO R28
Dynamic Shear, PAV residue at 28 deg C	kPa	Max. 5000	3180	AASHTO T315
Creep Stiffness, S value	MPa	Max. 300	168	AASHTO T313
Creep Stiffness, M value		Min. 0.30	0.34	AASHTO T313
Direct Tension failure strain	%	Min. 1.0	2.8	AASHTO T314

Actual results shown are representative batch-result values and may be replaced by certified COA values for each shipment.