SHAMS POWER COMPANY

ENGINEERING DIVISION

INSPECTION & CORROSION SECTION

SHAMS 1

LOCATION: R1HAN50BB010

KKS: R1HAN50BB010

GRADE & CLASSIFICATION: 2

CERTIFICATE OF INSPECTION

The equipment detailed below was examined in accordance with the SHAMS code of practice for plant inspection,

ITEM: blowdown tank LOCATION: SHAMS Plant

TYPE OF INSPECTION: Major DATE OF INSPECTION: March, 2020

PLACE OF INSPECTION: IN-SITU DATE OF LAST INSPECTION: Jan, 2019

REPORT:

1.0. SUMMARY

The above pressure vessel was taken off line, isolated, opened, vented & cleaned for major external & internal inspections.

2.0. SUBJECT

2.1. This is a horizontal, cylindrical, carbon steel tank with one inlet and outlet of condensate water.

Size	
Design pressure	
Design temperature	
Operation pressure	90barg
Operation temperature	310c
Fluid characteristics @	
Flanges	A314
Piping	A314
Shell minimum thickness	
Head minimum thickness	

The above equipment is/ is not considered suitable for further service under the present operating conditions

NEXT MAJOR INSPECTION DUE: March 2024 INSPECTED: Osman Ismail

ENDORSEMENT: 48 MONTHS

REVIEWED: Ali Al Masabai

3.0 HISTORY

This tank was commissioned in 2013. Periodical inspection records since Oct.'2014 are available.

4.0. SCOPE OF INSPECTION

- 4.1. Visual Inspection
- 4.2 Ultrasonic Thickness survey

5.0. CONDITIONS FOUND

5.1. External

- 5.1.1 All painting and insulation found intact without any evidence of painting peel off or blistering and no evidence of any damage for insulation or insulation cover aluminum sheet.
- 5.1.2 All ladders, stairways and handrails found in satisfactory condition.
- 5.1.3 All concrete support found in satisfactory condition without evidence of cracking or spalling.
- 5.1.4 All external piping insulation found in satisfactory condition.
- 5.1.5 All earthling lugs found in satisfactory condition.

5.2. Internal

- 5.2.1 All internals found in satisfactory condition without evidence of fallen down, damage or corrosion.
- 5.2.2 All internal surfaces of shell and heads found in satisfactory condition, apart from normal carbon steel very thin hydroxide layer.

6.0 NDT

- Ultrasonic thickness measurement was carried out on the internal shell courses and heads found satisfactory. See attached thickness measurement report.

6.0. Recommendations

Blow down tank should be open for inspection after four years as per SHAMS code of practice.

10. Inspection Grade and Interval


In accordance with the latest revision of SHAMS Code of Practice, this **Deaerator was** endorsed for 48 months under class 2, for next Major Inspection.

FREQUENCY : 48 MONTHS. ENDORSEMENT : 48 MONTHS,

GRADE : 2

Next Major Insp. due : March, 2024

Photos





International Inspection Services Ltd. NON DESTRUCTIVE TESTING/HEAT TREATMENT/ADVANCED INSPECTION SERVICES, CALIBRATION SERVICES AND MECHANICAL & METALLURGICAL LAB SERVICES

intertek.com

Form No.: IN-QSF-36 Rev. 05E Dtd.: 20-10-2018

		ULT	RASONIC THICK	NESS GAUGIN	G REPOR	T	
Client: S	HAMS POWER CO	OMPANY	HERMINGS THE WAY CASES AND AND TO RESPOND				
Date:	03.03.2020		- Anna ann an Beatann an Inglia ann an an an Anna an ann an Anna an Anna an Anna an Anna an Anna an Anna an An	Report No.:		AD / 453	
roject:	SHAMS OUTAGE MARCH 2		ICH 2020	Job No. :		N/A	
ocation:			VED				
el la companya de la				Drawing No.:			
em ID:	CONTINIOUS BLOW DOWN TANK - R1		NK - R1HAN50 BB010	Material:		CS	
			/001 Rev.10	Ref. Standard:		ASME SEC V	
ITG Equipment Model/ Nanufacturer: USM 3		X DAC / GE	Serial No.:		7292a		
		E, IIW V2 BLOCK	-	n Certificate	ertificate & Due INS/UT/CAL-043/19/AL		
Probe Type/ WK TR 0° PROF		WK TR 0° PROBE	10mm DIA / 5 MHz	Date: Couplant Branc	Name & Tyn		POLYCELL + WATER
onnecting Cable Type &				Special Attachn			
ength: LEMO TO		LEMO 10 MIC	RODOT & 2 MTR	Equipment/ Blo		STEP WEDGE BLOCK (SL NO: AZB270)	
est Temperature:		AN	IBIENT	Surface Condition:		AS CLEANED	
nspection Date:		03.0	03.03.2020		of	The state of the s	2
scription	1:			The state of the s			
CATION	ORIENTATION MEASURED THICKNESS (mm)						
1	12 0'	CLOCK	15.80				***************************************
1	3 0'0	CLOCK	15.90				
1		CLOCK	15.70				
1	9 O'CLOCK 15.93				***************************************		
2	12 O'CLOCK		13.23				
2	3 O'CLOCK		13.01		***************************************		
2		CLOCK	13.00 12.60			***************************************	
			12.00				

·						1	
	<u> </u>	/	ORT FORMAT APPLICAB		FUJ FACILITY		
me :	LEVEL II TEC	HNICIAN ARI & SHYMAL PAUL	CLIENT Name :	REPRESENTATIVE		lama.	AI / TPI
ne. n:	Theirested in Nache Print Time	STEP AL PAUL	Sign:			Name :	
	Level II No.		=			Sign :	
e:	660 c	3.03.2020	Date : Tel: 04 3241955	Fax: 04 3241957		Date :	
ah Branch Dhabi Branch rah Branch n Branch	: P O Box: 5130, Sharja : P O Box: 41227, Abu : P O Box: 2907, Fujain : P O Box: 193, P.C: 13	h, U.A.E Dhabi, U.A.E ih, U.A.E , Sultanate of Oman	Tel: 06 5361300 Tel: 02 6225820 Tel: 09 2238754 Tel: 09968 2448 2391	Fax: 06 5361173 Fax: 02 6225830 Fax: 09 2238754 Fax: 00968 2448 5855	Email: Inspec.s Email: Inspec.a Email: Inspec.fr	xbcoor@intertek.com hlcoor@intertek.com dhcoor@intertek.com ulcoor@intertek.com nuscat@intertek.com	INSPECIS PART OF INTERFECT GROUP For Complaints & Suggestions.
ered Office	:33-37 Athol Stree	t, Douglas, IM1, 1LB, Isle of Man. Comp	pany Number 010728V.				Please email to:suggestions.inspec@inte

★ UTG LOCATION **Date :-** 03.03.2020 **Report No.:-** AD-453 Page No. :- 2 OF 2 ULTRASONIC THICKNESS SCANNING DRAWING SHEET International Inspection Services Ltd **CONTINIOUS BLOW DOWN TANK** MAN WAY BOTTOM Intertek.com Name:-SigHYMALRAULE AFZAL ANSARI intertek inspec LEVER II TECHNICIAN -Sign : Date :- 03 03 2020