
## Anti-Spall Films for TPU

Madico Anti-Spall films are designed to improve ballistic glass and security glass products. These films offer an excellent solution for reducing weight, adding strength and increasing the safety of glazing. Madico Anti-Spall films are PET-based films made of various constructions designed to combine anti-spall properties with an excellent scratch resistant hard coat on the interior (air) side of the final product construction.

## Material Construction - CL 700 SRB TPU:

Total laminate thickness......7 mil All thicknesses are based on nominal data.



#### Benefits:

- Spall protection
- Weight reduction
- Chemically resistant
- Excellent optical performance
- Similar to laminated glas
- Superior scratch-resistant hard coat

#### **Available Widths:**

- 91 cm / 36"
- 120 cm / 48"
- 150 cm / 60"
- 182 cm / 72"

## **Applications:**

#### Automotive:

- Sunroofs
- Windshields

#### Defense/Security:

- Bullet-resistant glazing
- Forced entry-resistant glazing
- Side and rear lites
  Detention center glazing
  - Blast-resistant glazing

#### **Transportation:**

- Rail car windscreens
- Mass transit vehicles
- Marine vessels

### Architectural Glazing:

- Skylights
- Curtain walls
- Security doors









Visible Light:

# Anti-Spall Films for TPU

Madico's Anti-Spall films are used with TPU interlayers to produce a lighter weight product construction and improved spall protection on glazing systems.

#### Performance Measurements

**Chemical Resistance:** 

| Transmitted>90%   | AlcoholsResistant               |
|---|---------------------------------|
| Reflected Exteror10%                                    | AldehydesResistant              |
|   | HydrocarbonsResistant           |
| Physical Properties:                                    | Chlorinated SolventsResistant   |
| Tensile Strength28,500 PSI Average MD/TD                |                                 |
| Elongation at Break160% / 85% (MD/TD)                   | Acids:                          |
| Scratch Resistance<1.0% Delta Haze ASTM D-1044-85       | Diluted (<10%)                  |
| Peel Strength (ASTM D-3167 Results)>130lb / in.         | (Includes Hydrofluoric Acid)    |
| Mounting AdhesiveNone                                   | ConcentratedLimited Resistance  |
| Haze:   | Alkalies:                       |
| Pre-processing (film only)≤0.50%                        | Diluted (<10%)Resistant         |
| Post-autoclaving (on 1/4" glass with 30 mil PVB) ≤0.40% | Concentrated Limited Resistance |
|   |                                 |
| Cross-hatch Adhesion:                                   |                                 |

The representations of performance and suitability for use contained in this datasheet are guidelines. Since only the user is aware of the specific conditions in which the product is to be used, responsibility to determine whether the product is suitable for that intended need belongs to the purchaser.





