

Special Purpose Cement

<u>Class</u>	<u>Clinker</u>	<u>Slag</u>	<u>Gypsum</u>
CEM III/A	35 -- 64	36 -- 65	0 -- 5
CEM III/B	20 -- 34	66 -- 80	0 -- 5
CEM III/C	5 -- 19	81 -- 95	0 -- 5

	<u>Clinker</u>	<u>Slag</u>	<u>Gypsum</u>	<u>2 Days(N)</u>	<u>28 Days(N)</u>	<u>SPC-kW/T</u>
<i>Ruby Cement</i> <u>Trying to Sell in Local Market - Capacity Reduced to 40%</u>						
CEM III/A	50	45	5	10 -- 12	48 -- 50	>85
<i>Shah Cement</i> <u>For Matarbari Atomic Power Plant, produced in Ball Mill- Capacity Reduced to 40%</u>						
CEM III/A	44	51	5	7 -- 9	30 -- 32	>85