

A Novel Approach on Micro Sponges Drug Delivery System: Method of Preparations, Application, and its Future Prospective

Suraj Mandal*, Km. Bhumika, Mukesh Kumar, Jiyaul Hak, Prabhakar Vishvakarma, Umesh Kumar Sharma

Department of Pharmacy, IIMT College of Medical Sciences, IIMT University, O-Pocket, Ganga Nagar, Meerut, Uttar Pradesh, INDIA.

ABSTRACT

Microsponges are porous microspheres ranging in size from 5 to 300 micrometers used in a polymeric delivery system. They have been studied for biomedical applications, including targeted medicine delivery, transdermal drug delivery, anticancer drug delivery, and bone substitutes. This research aims to conduct a detailed examination of existing trends and future prospects for a microsphere-based medicine delivery system. The current study investigates the Microsphere Delivery System's design, operation, and possible therapeutic uses (MDS). The therapeutic potential of microsphere-based formulations, as well as patent data, were thoroughly investigated. The authors discuss several efficient methods for producing microsponges, including liquid-liquid suspension polymerization, quasi-emulsion solvent diffusion, water-in-oil-in-water (w/o/w) emulsion solvent diffusion, oil-in-oil emulsion solvent diffusion, the lyophilization method, the porogen addition method, the vibrating orifice aerosol generator method, the electrohydrodynamic atomization method, and the ultrasound-assisted microsphere. Microsphere may reduce undesired side effects and increase drug stability by boosting drug release. Hydrophilic and hydrophobic drugs can be loaded into a microsphere and transported to a specific target. When compared to traditional distribution methods, microsphere delivery technology offers numerous advantages. Microsponges, which are spherical, sponge-like nanoparticles with porous surfaces, can help increase drug stability. They efficiently alter drug release while also reducing adverse effects.

Keywords: Microsphere, Microsphere delivery system, Novel drug delivery system, Quasi emulsion solvent diffusion, Vibrating orifice aerosol generator, Electrohydrodynamic atomization.

Correspondence:

Mr. Suraj Mandal

Department of Pharmacy, IIMT College of Medical Sciences, IIMT University, O-Pocket, Ganga Nagar, Meerut-250001, Uttar Pradesh, INDIA.

Email: sk8006721807@gmail.com

ORCID: 0000-0001-5080-7855

Received: 18-04-2023;

Revised: 28-06-2023;

Accepted: 14-08-2023.

INTRODUCTION

Drug delivery technology is rapidly evolving when numerous medication delivery technologies are used to boost the effectiveness and cost-effectiveness of treatment procedures (Figure 1).¹ Microparticulate drug carriers were developed as a result of these endeavors to provide innovative drug carrier systems.² Multiparticulate systems are important because they are simple to build and can control drug release in various ways, such as rate control, site control, or both.³ Multiparticulate systems are expected to improve drug absorption because they are more likely to be distributed uniformly throughout the absorption site. Microspheres, microbeads, or microcapsules, microballoons, and microsponges are some of the microparticulate systems developed and explored for this purpose.^{4,5} Microsponges protect

the entrapped pharmaceutical substance, which are porous microspheres with a stiff and/or pliable matrix that range in size from 5-300 m and are made of physiologically inert organic polymers.^{6,7} 2.5x10⁵ pores, which are present in a particle with a size of 25 m and are connected to the interconnecting channels by these pores, generate an inner pore space with a length of around 3 m and a volume of 1 mL/g of the particle.⁸ Won and colleagues developed microsphere technology for the first time in 1987, to integrate a broad spectrum of medicinal chemicals in nanotechnology-based formulations.⁹

The microsphere-like spherical particles have a massive, porous surface, and hundreds of interior voids encased in a non-collapsible framework.¹⁰ However, they are commonly used as a carrier strategy because their non-collapsible structures and porous surfaces can entrap various active pharmaceutical compounds and allow for controlled release. Drug-entrapped microsphere can be used to make a variety of formulations, including tablets, gels, capsules, powders, lotions, and creams.¹¹ This microsphere drug delivery technique provides enhanced drug entrapment and stability, allowing for greater formulation



DOI: 10.5530/ijper.58.1.5

Copyright Information :

Copyright Author (s) 2023 Distributed under
Creative Commons CC-BY 4.0

Publishing Partner : EManuscript Tech. [www.emanuscript.in]

flexibility and a significant reduction in unwanted side effects.¹² Substantial amounts of active chemicals can be put into the center or incorporated onto the surface of these microparticles.¹³ Microsponge delivery systems improve the safety, effectiveness, and visual appeal of a variety of over-the-counter and other personal care items. The benefits of the microsponge formulation are summarized in Figure 2. The active component is progressively released from the microsponge through a series of phases as it is trapped and introduced into the medium. The dynamic can readily move between the particles and the medium because to the open structure of the microsponge particles until equilibrium is reached, which normally occurs when the medium is saturated.¹⁴ When the medium becomes partially depleted or absorbed, a dynamic flow occurs from the microsponge ingredient component into the medium and then from the medium to the skin.

This desired method of operation emphasizes the significance of creating a vehicle that can be used with microsponge entrapments.¹⁴ Microsponges are patented polymeric delivery systems that can transport a variety of active chemicals, including emollients, fragrances, essential oils, sunscreens, anti-infectives, antifungals, and anti-inflammatory medicines. Because the microsponge particles are too big to be absorbed by the skin, they are considered harmless.¹⁵ Notwithstanding the numerous advantages described above, there is a major risk of bacterial contamination of the trapped material; however, due to the lower hole width, bacteria with pore sizes ranging from 0.007 to 0.2m are unable to enter the microscope tunnel structure.¹⁶

Microsponges are also the most explored carrier particles due to their numerous advantages over other microparticulate systems, such as ease of manufacture, improved drug loading, and rate control.^{17,18}

METHODS FOR PREPARING MICROSPONGES

Some of the methods used to develop microsponge-based drug delivery systems include liquid-liquid suspension polymerization, quasi-emulsion solvent diffusion, water-in-oil-in-water (w/o/w) emulsion solvent diffusion, oil-in-oil emulsion solvent diffusion, the addition of porogen method, vibrating orifice aerosol generator method, electro-hydrodynamic atomization method, and ultrasound-assisted production method. Table 1 covers the various microsponge formation procedures that have been used, as well as the merits and downsides of each methodology.¹⁹⁻³³

Lyophilization Method

This method was utilized to transform the microspheres into porous microspheres. At this step, the microspheres were grown in a chitosan hydrochloride solution before being lyophilized. The rapid removal of the solvent resulted in the formation of pores in the microspheres. Microsponges may be made fast, simply, and frequently with this process. This process is simple and efficient,

but it produces microparticles that are fractured or shrunken because the solvent is withdrawn too quickly.

Addition of Porogen Method

In this method, the internal aqueous stage of the water-in-oil-in-water (w/o/w) emulsion was replaced with a porogen, such as hydrogen peroxide or sodium bicarbonate. The porogen was distributed throughout the polymeric solution to provide a consistent dispersion framework. This framework was then redispersed in a PVA-containing aqueous phase. The organic solvent was removed from the w/o/w emulsion after the addition of an initiator, leaving the microparticles behind. Hydrogen peroxide inclusion resulted in equally spaced and overlapping holes ranging in size from 5 to 20 m.³⁴ While it may be damaged, this porous architecture featured regularly distributed and linked pores.

Liquid-liquid Suspension Polymerization Technique

Microsponges are created (in a single step) via polymerization in suspension in liquid-liquid systems.^{19,20} Before being stirred into the aqueous phase, the active components (non-polar medication) and monomers are first dissolved in an appropriate solvent solution of the monomers. In the aqueous phase, for instance, suspending agents such as surfactants and dispersants are often used to aid in suspension production. After creating a suspension with droplets of the right size, polymerization is begun by adding a catalyst or increasing temperature and radiation. In addition, this polymerization results in the formation of a reservoir system with surface-opening holes. In other cases, the pore network is generated during polymerization using an inert solvent that is entirely miscible with the monomer but completely immiscible with water. When the polymerization process is complete, the liquid is drained, leaving behind microsponges that serve as topical carriers for several active chemicals, including antifungals, rubefacients, anti-acne, and anti-inflammatory agents, among others. In some instances, it may be feasible to utilize a solvent to ensure that the functional compounds are integrated quickly and efficiently. If the medication is susceptible to polymerization, a two-step process is adopted; the polymerization is performed using a different porogen, and the functional molecule is subsequently substituted under mild circumstances.³⁵ Medication loading may be completed in one or two phases, which is one of the method's main advantages. This method has various disadvantages, including the need for two-step processes for thermodynamically sensitive drugs and a restricted drug loading capacity. Since monomers need considerable time to react with non-uniform structures, unreacted monomers and solvent traces may get trapped.³⁶

Quasi-emulsion Solvent Diffusion Method

The most popular approach for designing microsponges is the quasi-emulsion solvent diffusion method. A quasi-emulsion

solvent diffusion technique with an exterior and interior phase was used to manufacture all micro-sponges.³⁷ The internal organic phase is made up of ethyl alcohol, polymer, and triethyl citrate/trichloromethane, which were injected at a concentration of 20% of the polymer to increase plasticity.³⁸ The external phase is mostly made up of distilled water and PVA. It was initially produced at 600°C before being applied to the exterior phase at ambient temperature. The liquid was continuously stirred for 2 hr after emulsification.³⁹ After filtering the mixture to remove the microsponges, the finished product was washed and dried for 24 hr at 400°C.⁴⁰ This method offers several advantages, such as producing spherical particles, little or no monomer trapping, low solvent traces, high drug loading, no medicine exposure to the environment, and the ability to simply alter the swirling to change the size of the micro-sponges. The possibility of trapping unreacted monomers and solvent traces, an unpredictable structure, slowly occurring monomer reactions, and a two-step process with poor drug loading efficiency for temperature-sensitive medications are some drawbacks of this technique.

Water-in-oil in Water (w/o/w) Emulsion Solvent Diffusion

This technique for producing biodegradable porous microspheres is simple. This approach separated an emulsifying agent such as span, polyethyleneimine, or spaced repetition from an organic polymeric solution utilizing an internal aqueous phase.⁴¹ The w/o emulsion was then dispersed in an external PVA-containing aqueous process to create a double emulsion. Entanglement is a benefit of this method.⁴² Several investigations have identified xanthan gum as an emulsifier that stabilizes the internal water-in-oil emulsion.⁴³ While this technique has the benefit of entrapping both water-soluble and water-insoluble compounds, the use of water-insoluble surfactants, which might retain residues inside the microsponges, is a major drawback.

Oil-in-oil Emulsion Solvent Diffusion Method

The oil-in-oil (o/o) emulsion was made by using a volatile organic liquid as the internal stage, instead of the w/o/w method, which involved letting the water slowly evaporate while stirring.⁴⁴ Dichloro-methane was the internal phase, polylactic glycolic acid was the polymer, and span-85, which is a mixture of fixed oil (Corn or Mineral) and dichloro-methane, was the external phase. To make the microsponges, the internal step was slowly added to the dispersion medium while stirring constantly.⁴⁵ hydroxyzine HCl-loaded Eudragit RS-100 microsponges were made using this method, with acetone as the dissolver and liquid paraffin as the continuous medium.⁴⁶ The physicochemical properties of the drug and the polymer used to make the microsponges affect the choice of an organic solvent and an outer phase.⁷ No surfactant residues were found in the microsponges, which is a big plus for this method. The main problems with this method are that you must eliminate all traces of alcohol and use organic solvents.

Vibrating Orifice Aerosol Generator Method (VOAG)

The initial use of a vibrating orifice aerosol generator was producing lipid-bi-layered mesoporous silica particles (VOAG). Surfactant microdroplet evaporation-driven thermal deposition generated porous particles using the VOAG technique. Initially, a stock solution for the core particle was made by refluxing a hydro-ethanolic mixture of tetra-ethyl-orthosilicate in diluted HCl. This stock solution was diluted with a surfactant-containing solvent and stirred to generate monodisperse droplets, encased in microsponges.⁴⁷

Ultrasound-assisted Production Method

This technique was developed to produce the nano-sponge by modifying liquid-liquid suspension polymerization to employ -cyclodextrin as a monomer and di-phenyl carbonate as a cross-linking agent. To control the range of the microparticles, the reaction mixture was heated and sonicated. The reaction mixture was allowed to cool before being pulverized to generate particles that were first rinsed with distilled water and then ethanol.⁴⁸ Cross-linked-CD permeable microparticles molar medications effectively load medications. The results are easily reproducible, and no solvent residues were found. Nevertheless, this approach has the disadvantage of trapping potentially hazardous cross-linking agent residues.⁷

Electrohydrodynamic Atomization Method

Pancholi *et al.* created porous chitosan microspheres using this approach in 2009.⁴⁹ The chitosan solution was ultrasonified to generate bubbles. A steel capillary was then perfused with the bubble solution using a syringe pump, and the suspension was electro-hydrodynamically vaporized. The diameter of the capillary was meticulously chosen to ensure that every suspension bubble stayed intact as it passed through. The sole factor in determining the voltage was the amount of chitosan present in the test solution. With the exception of the maximum concentration, which proved challenging to electrospray, the flow rate and applied voltage generated the stable cone-jet mode in each case. The chitosan microspheres were cross-linked using a 4% weight-volume solution of sodium hydroxide in water.⁷ There is the potential for the therapeutic molecule to combine with the monomer. Controlling the particle and pore size of the microsponges generated by this approach also requires experience.

FACTORS AFFECTING THE RELEASE OF DRUG FROM MICROSPONGE

In the design and manufacture of these multifunctional microcarriers, the physicochemical characterization of the microsphere is a crucial step. Several complementary techniques, such as HPLC, FTIR, DSC, PXRD, and SEM, are used to study the morphological features and porosity of microsponges.⁵⁰

Considering the physicochemical properties of any carrier play a key role in affecting drug loading and release behaviors at a specific target, scientists must analyze the numerous physicochemical components of microsponges using the right approaches, as seen in Figure 3. Yet, this concept contradicts the standard formulation principles used in topical treatments. Improving the solubility of the active medicine in the vehicle is generally recommended for these classic systems.⁵¹ When using microsphere entrapment, it is highly recommended that the active chemicals be sufficiently soluble in the vehicle so that the vehicle can deliver the final loading dose of the substances before releasing them from the microsphere. This is possible by altering the equilibrium between the polymer and the carrier.⁵² Producing the microsphere polymer with both free and trapped active ingredients, resulting in a pre-saturated vehicle, is another strategy for minimizing the unintended leaching of the active components. In addition to the partition coefficient between the polymer and the vehicle, diffusion or other stimuli, such as steam, pH, friction, or temperature, may influence the release rate.^{9,53} Depicts a variety of factors that may influence the drug release from the microsphere.

Temperature

Some encapsulated active substances may be too viscous to transfer rapidly from microsponges to the skin at normal temperatures. Enhanced release is a result of the higher flow rate generated by a rise in skin temperature.

Pressure

By rubbing or applying pressure on microsponges, the active chemical may be released onto the skin. The strength of the microsphere determines the amount of release.

Solubility

Microsponges that contain untargeted substances such as antiseptics and deodorants release their contents upon contact with water. The release may also be initiated via diffusion, but the partition coefficient between the microsponges and the external system must be considered.

pH triggered systems

Microsponges that contain untargeted substances such as antiseptics and deodorants release their contents upon contact with water. The release may also be initiated via diffusion, but the partition coefficient between the microsponges and the external system must be considered.

USE OF DRUG DELIVERY SYSTEM RELYING ON MICROSPONGES

In recent years, there has been more interest in making medicines that can be given to specific parts of the body. Microsponges are flexible polymeric delivery systems that contain porous

microspheres. They can contain a wide range of active chemicals, such as emollients, perfumes, essential oils, sunscreens, anti-infectives, anti-fungal, and anti-inflammatory agents. It also has a lot of benefits, such as better control over drug loading and rate, uniform distribution, and easy production.⁵⁴

The Role of Microsponges in the Delivery of Anticancer Drugs

A colon-specific drug delivery system is one type of drug delivery system that aims to improve effectiveness and reduce side effects by putting high concentrations of medication in the colon.⁵⁵⁻⁵⁷ Microsponges can also be used to give drugs by mouth so that they last longer and are less harmful. 5-fluorouracil can be used to treat many different types of solid tumors, and its ability to treat cancer can be improved by making it build up more in tumor areas. The solvent diffusion method for oil-in-oil emulsions was used to make microsponges with 5-FU. Pure 5-FU was found to get out in about 20 min, while microsponges slowly let out the drug for up to 5 hr after a quick release.⁵⁸ Table 2 is a list of more examples of microsphere delivery systems that contain anticancer drugs.⁵⁸⁻⁶⁰ Grimes *et al.* made microsponges with 0.15% retinol and 4% hydroquinone to treat post-inflammatory hyperpigmentation and melanoma. People with hyperpigmentation were given hydroquinone for a longer time, even though it made their skin less sensitive. An open-label trial was done to see how bad pigmentation was, and the area of the lesion got a lot better and the number of sick people got a lot less. One person dropped out of the study because of a mild allergic reaction, which showed that the formulation was safe.¹³ In a different study, Jain and his colleagues used the quasi-emulsion solvent diffusion technique in ethyl cellulose and Eudragit RL 30 D to make 5-Fluorouracil-loaded microsponges. They found that 5-FU 5-FU was five times as effective as usual.⁵⁸⁻⁶⁰

Microsphere used in the topical administration

Topical medications are often used to treat skin conditions and even in cosmetics, even though they can cause severe skin irritation, especially in people with sensitive skin.⁶¹ The Transdermal Delivery System (TDS), which uses the epidermis as its primary site, has been used to develop a number of reliable and predictable systems for systemic medications.⁶² In this method, the medicine is slowly injected into the epidermis in the hope that it will stay mostly localized, have little effect on the skin, and not have a big effect on the circulation throughout the body.^{63,64} Numerous topical products with microsphere bases that have undergone testing for protection and efficacy in the treatment of dermatological disorders⁶⁵ are now available in the United States. Acne, psoriasis, dandruff, eczema, scleroderma, hair loss, skin cancer, and other terrible conditions can be treated effectively with microsponges that can be turned into creams, lubricants, and moisturizers (Table 3). Benzoyl peroxide, retinoic acid, HQ + retinol, and 5-FU-based formulations are a few examples

Table 1: A combined list of various techniques of microsphere formation with advantages and disadvantages of each technique.

Sl. No.	Techniques name	Advantages	Disadvantages	Excipients	References
1	Liquid-liquid suspension polymerization technique.	Modifications to one-step or two-step drug-loading procedures are possible.	Un-reacted monomers and solvent particles may be trapped. For thermo-sensitive medicines with limited drug loading efficiency. Particles are not uniform. A two-step technique is required.	Surfactants like peroxides, benzo- yl,t-butyl, diacetyl and lauroyl peroxides, and dispersants such as methyl and ethyl cellulose.	19,20
2	Quasi-emulsion solvent diffusion technique.	No trapping of monomers. Solvent traces are minimal. High drug loading. There is no exposure of the medication to the environment. Controlling the stirring can readily control the size of microspheres. Sphere structured particle.	Unable to load water soluble medicine. Long monomer's reaction. Volatile water-soluble solvent dissolves the drug.	Eudragit RS-100, Dichloromethane, plasticizer, piroxicam, and Tri-Ethylcitrate (TEC).	21,22
3	w/o/w emulsion solvent diffusion technique.	Load water-soluble medicines. Entrap proteins and peptides.	Water-insoluble surfactants are used, which can leave residues in the microspheres.	Span, polyethylene imine, stearyl amine.	23
4	Addition of the porogen method.	Pores are well dispersed and inter- linked.	Structure disturbed.	Hydrogen peroxide and/or sodium carbonate.	24,25
5	Oil-in-oil emulsion solvent diffusion method.	Surfactant traces not found.	To get rid of the residues of alcohol, need to wash it well. Organic materials solvents.	Methocel 10000cps, eudragit-S100, eudragit-L100, eudragit-RL100, eudragit-RS100, acetone, Liquid paraffin.	26,27
6	Lyophilization method.	Simple, rapid, and repeatable outcomes.	Microparticles may break or shrink.	Hydrogen peroxide solution (30%), Polyethylene Glycol (PEG) 200, PEG-400, PEG-600, Dimethyl Formamide (DMF), Dimethyl Sulphoxide (DMSO), ethylene glycol.	7,28
7	Ultrasound-assisted production.	No solvents residues. Easily repeatable	Not quite right structure. Use of potentially hazardous cross-linking agents.	Beta-cyclodextrin (BCD), Diphenyl carbonate.	29,32
8	Vibrating orifice aerosol generator method.	Targeted drug delivery.	Presence of acid reflux.	Tetraethyl orthosilicate and other surfactants.	26
9	Electro hydrodynamic atomization method.	Easily repeatable results.	Medication molecule will bond to the monomer. Controlling particle and pore size necessitates experience.	Hydroxypropyl Methylcellulose (HPMC) and lactose monohydrate, Span 20.	33

Table 2: Microsponge drug delivery for anticancer agents.

Sl. No.	Active Drug	Formulation Type	Method of Preparation	Polymer Used	Application	References
1	Prednisolone	Colon target MSP tablets to treat ulcerative colitis.	Quasi- emulsion solvent diffusion.	Eudragit S 100 (ES)	Inflammatory Bowel Disease (IBD) and other colon illnesses are managed.	59
2	Meloxicam (MLX)	Erosion-based colon-targeted matrix tablet.	Quasi- emulsion solvent diffusion.	Eudragit RS 100	Developing a calcium-pectinate matrix pill for colon-targeted distribution with the potential to be used as a colorectal cancer adjuvant therapy.	60
3	5-Fluorouracil	--	Quasi-emulsion, solvent diffusion.	Ethyl cellulose and Eudragit RL 30 D	Increasing the efficiency of 5-FU.	58

of frequently used topical active substances.⁶⁶ When applied to the skin, microsponges have several advantages over traditional formulations, such as causing little or no irritation to people with acne, skin that is sensitive to light, or skin that is too dark.⁶⁷ Additionally, microscopic microspheres known as microsponges can absorb skin secretions and reduce skin oiliness Oral Drug Delivery System Microsponges: Encasing poorly water-soluble medications in a microsponge capillary system may make them more soluble and oral. The first microsponges-based oral medicine delivery trial was undertaken by A.P. Pharma, Inc. in the US. Because microsponge particles entangle with the rough intestinal mucosa, these carrier systems may increase bioavailability by speeding adsorption and dissolution.⁷ A controlled oral distribution microsponge delivery device may safeguard active chemicals.⁷² Colonic enzymes release them into the lower gastrointestinal tract. The microsponge medication delivery device will benefit if the method works.⁷⁶ Mohammad Jafar and colleagues created a luteolin-entrapped gastric floating microsponge for *Helicobacter pylori*. Luteolin-based microsponges had double the anti-*Helicobacter pylori* activity of pure luteolin.⁷⁷ In another investigation, oil-in-oil emulsion solvent diffusion caught albendazole on Eudragit RS100 microsponges. Albendazole microsponges showed a greater AUC than albendazole suspension against *Haemonchus contortus* in parasite-infected goats.⁷⁸ This shows that albendazole may be used orally as a sustained-release microsponge for parasitic worms. Table 4 lists other oral medicine microsponge formulations.⁷⁷⁻⁸¹

Microsponges as a Bone Replacement Technique

Bone replacement compounds were made from pre-polymerized poly-methyl-methacrylate granules and liquid MMA. The monomer was mixed with calcium-deficient hydroxyapatite powder and tri-calcium phosphate grain aqueous dispersions. As the composites were porous, fresh trabecular bone formed in the

pores where the inorganic particles were inserted. The material was biocompatible, osteogenic, and osteointegrated.⁸²

Cardiovascular system treating microsponges

Cardiovascular engineering and several cardio-selective drugs also use microsponge technology (Table 5). Seeding biodegradable hematopoietic cells is a complex, invasive procedure that exposes patients to infection. Biodegradable collagen microsponge can regenerate autologous vascular tissue.⁸³ Histological investigation showed an endothelial cell monolayer, smooth muscle cells in parallel, and a repaired vascular wall with proteolysis and collagen fibres.⁸⁴ After six months, the patch's cellular and extracellular components matched real tissue. This patch may also be employed for *in situ* cellularization and allogeneic tissue formation in cardiovascular surgery, as illustrated in Table 5.⁸⁵⁻⁹⁰

Microsponge for Sustained Release Drug Delivery

Tablets and capsules take 30 min to start working and last 47 hr. The body eliminates the medication within 5-7 hr after oral administration in healthy people. Nifedipine's short half-life ($t_{1/2}$, 2 hr) requires regular doses, although it may alleviate cardiovascular disorders. For clinical application and patient acceptance, sustained-release microsponges containing nifedipine were made into tablets.⁹¹ Domperidone is another possibility for sustained-release formulation since it needs long-term therapy and substantial doses. Prolonged-release domperidone microsponge-based capsules minimize side effects and increase release kinetics and effectiveness for gastroparesis, emesis, and other illnesses.^{11,92} Table 6 lists sustained-release microsponge formulations for diverse uses.⁹³⁻¹⁰¹

Diagnostic agent delivery using microsponges

Microsponges solubilize poorly soluble hydrophobic medicines in a hydrophobic core to enhance cancer-specific combination medication administration and pharmacokinetics. Subhan and

Table 3: Brand/Trademark for micro sponge products used in dermatology and cosmetics.

Sl. No.	Brand Name	Manufactured Name	Active Drug	Formulation Type	Method of Preparation	Polymer Used	Application	References
1	Clozole gel 15 g	Psyco Remedies	Fluconazole	Gels	Quassi emulsion diffusion method.	Ethyl Cellulose (EC) and Eudragit RS 100.	Anti-fungal infection treatment.	69
2	Ertaczo	Glenmark Pharmaceuticals Ltd.	Sertaconazole nitrate	Gel	Quasi-emulsion solvent diffusion method.	Eudragit RS100, polyvinyl alcohol.	Anti-fungal	70
3	Carbopol gel	Scott Paper Company.	Miconazole	Cream	Quassi emulsion solvent diffusion method.	Ethyl cellulose, Polyvinyl alcohol and dichloro-methane.	Diaper dermatitis, use a micro- sponge gel. Dermatitis, acne and other topical infections.	71
4	Brevoxyl	Unicare India Pvt. Ltd.,	Benzoyl peroxide	Gels, lotions, cream	Quasi-emulsion solvent diffusion method.	Ethyl cellulose and dichloromethane.	Reduced skin irritation and sensitization, Anti-acne.	72
5	EpiQuin Micro	SkinMedica, Inc. USA.	Hydroquinone and retinol	Gel, lotion, cream	Quassi-emulsion solvent diffusion method Liquid-Liquid Suspension Polymerization.	Polyvinyl Alcohol (PVA), ethyl alcohol.	Enhanced oxidation resistance, effectiveness, and visual appeal. Hyper pigmentation.	35
6	Carac Cream, 0.5%	Dermik Laboratories, Inc. USA.	5-Fluoracil	Gel, Cream, Solid particles	Quassi emulsion solvent diffusion method.	Eudragit-L100 (Ed-L100) and/or Eudragit-S100 (Ed-S100).	Lesion reduction, Actinic keratosis Treatment of colon cancer.	37
7	Salicylic Peel 20 and 30	Biophora Medical Skin Care, Ontario, Canada.	Salicylic acid	Gel, Ointment	Quasi-emulsion solvent diffusion method.	Eudragit RS100, dimethacrylate, ethyl cellulose, polystyrene and PHEMA.	Excellent exfoliation.	73
8	Line Eliminator Dual Retinol Facial Treatment	Avon Products, Inc. UK.	Retinol	Cream	Suspension polymerization technique.	methyl methacrylate/ glycol di-methacrylate.	Anti-Wrinkles.	73
9	Retin A Micro	Ortho-McNeil Pharmaceutical, Inc. USA.	Tretinoin	Gel	Quasi emulsion solvent diffusion method.	-	Acne vulgaris.	72
10	Retinol 15 Night cream	Biomedical IMPORIUM, South Africa.	Retinol	Creams, gel	Liquid suspension polymerization method.	methyl methacrylate/ glycol di-methacrylate.	Anti-wrinkles Skin supplement.	73
11	Oil-free matte block SPF 20	Dermalogica, LLC, USA.	Zinc gluconate	Lotion	Quasi-emulsion solvent diffusion method.	Eudragit RS 100.	Sunscreen	50

Sl. No.	Brand Name	Manufactured Name	Active Drug	Formulation Type	Method of Preparation	Polymer Used	Application	References
12	Melanin Microsponge	Advanced Polymer System Inc., US.	Melanin	Gel	Emulsion solvent evaporation method.	-	Hyperpigmentation disorders.	-
13	Ultra Guard	Scott Paper Company, USA.	Dimethicone	Cream, lotion	Liquid-liquid suspension polymerization.	Eudragit RS100, Dimethacrylate, Ethyl Cellulose, Polystyrene and PHEMA.	Protective for babies.	50,74,75
14	Lactrex 12% Moisturizing Cream	SDR Pharmaceuticals Pvt. Ltd., India.	Ammonium lactate.	Cream	Quassi emulsion diffusion method.	Ethyl Cellulose, Eudragit RS100, Polystyrene and PHEMA.	Moisturizes, 12% lactic acid, ammonium lactate and also contain water and glycerine.	50

Table 4: A list of the medications used in the formulation of the microsponge for oral drug administration.

Sl. No.	Active Drug	Formulation Type	Method of Preparation	Polymer Used	Application	References
1	Domperidone	MSP loaded capsules	Quasi-emulsion solvent diffusion.	Eudragit RS-100	Anti-emetic treatment of gastroparesis, emesis, and other stomach disorders.	11
2	Famotidine	Floating MSP	Quasi-emulsion solvent diffusion.	Polyvinyl alcohol Eudragit RS-100.	Anti-ulcer	79
3	Pantoprazole sodium	Tablet	Quasi-emulsion solvent diffusion method.	Eudragit RS 100), Polyvinyl alcohol.	For the management of Gastroesophageal Reflux Disease (GERD).	80
4	Luteolin	Gastric floating microsponge	Quasi-emulsion method.	-	For targeting <i>H. pylori</i> infections.	77
5	Albendazole	-	Oil-in-oil emulsion solvent diffusion method.	Eudragit RS100	To target parasitic worms in both humans and animals.	78
6	Lansoprazole	Delayed release MSP	Quasi-emulsion diffusion technique.	Eudragit L 100 and Eudragit S 100.	Proton pump inhibitor, used as a delivery system for acid labile drug lansoprazole to avoid its degradation in acidic media of the stomach.	81

Torchilin, explain how these micro-sponges self-assemble to create dense siRNA concentrations in nanoparticles with lower poly-cation concentrations.¹⁰² They also report a polymeric siRNA that self-assembles into RNA interference (RNAi) microsponge structures. Polyplexes may be changed to change the therapeutic potential of microsponges.


As Vehicles for Diabetes Treatment

Chronic hyperglycemia, which may lead to life-threatening complications, makes diabetes a major health risk.

Microsponge-based medication delivery may revolutionize diabetes therapy since it requires frequent dosing and 40–50% of patients have trouble following treatment regimens. A controlled-release gastro-retentive microsponge formulation of miti-glinide calcium, a new anti-diabetic, was created in research. *In vivo*, it reduces the requirement for frequent delivery, improving diabetic patients' adherence and diabetes management.¹⁰³ Meenakshi and colleagues generated floating microsponges of glipizide for an inquiry. The formulation allowed for longer drug release at the site of absorption, which may enhance diabetes

Table 5: Microsponge drug delivery systems for the treatment of cardiovascular disease.


Sl. No.	Active Drug	Formulation Type	Method of Preparation	Polymer Used	Application	References
1	Candesartan cilexetil	MSP	-	Eudragit RS 100, RL 100, S 100	Anti-hypertensive, Enhanced solubility and dissolution rate.	86
2	Metoprolol succinate	Colon-specific MSP tablet	Emulsion solvent evaporation method.	Ethyl cellulose, HPMC	Anti-hypertensive	87
3	Nicorandil	MSP sustained release tablet	Quasi-emulsion solvent diffusion.	Eudragit - RSPO and HPMC K100M.	Potassium channel opener. It is used to treat heart problems.	88
4	Temisartan	Tablet	Quasi-emulsion solvent diffusion.	Eudragit E or eudragit L in organic solution as the internal phase and aqueous solution of polyvinyl povidone as the external phase.	When compared to commercialized (Micardis®) tablet formulations, tablet formulations had a better release profile in all categories.	89
5	Valsartan	-	Quasi-emulsion solvent diffusion.	Ethyl cellulose, Polyvinyl alcohol.	Stability enhancement, reduce side effects.	90

**Figure 1:** Ordinary diagram of microsponge.

treatment by reducing plasma medication concentration variance. The formulation is expected to lower blood sugar levels longer than the quick-release version of glipizide and enhance diabetes circumstances for disease management (Table 7).¹⁰³⁻¹⁰⁵ Floating microsponges are a unique way to make gastro-retentive diabetic medicines, which must reside in the upper GIT for optimal therapeutic action.¹⁰⁴

Anti-allergic and anti-inflammatory drug delivery via microsponge

Anti-allergic drugs treat inflammatory diseases by limiting the generation and release of inflammatory mediators like histamine at the targeted location. NSAIDs alleviate pain, inflammation, and fever despite gastrointestinal side effects. Allergic areas are testing many reliable and cutting-edge medication delivery systems.

**Figure 2:** Advantages of Microsponge.

Lately, topical anti-inflammatory gels containing naproxen encapsulated in a Eudragit-based microsponge delivery system have been created to solve some of the physicochemical difficulties and limits of traditional pharmaceutical formulations (e.g., poor solubility and absorption, skin permeation, stability). Naproxen microsponges were made using Eudragit RS-100, carbopol, and PVA in a quasi-emulsion.¹⁰⁶ Microsponge delivery technology aids many allergy problems by continually spreading drugs (Table 8). A microsponge containing diclofenac diethylamine was tested against arthritis and musculoskeletal diseases. It released medication slowly, unlike the standard formulation.¹² Flurbiprofen microsponges placed to the epidermis release bioactive compounds on a schedule and react better to friction, temperature, and pH.¹⁰⁷ Microsponge entrapment of medicines offers several benefits beyond managing release and drug

Table 6: Several formulations of sustained-release microsphere.

Sl. No.	Active Drug	Formulation Type	Method of Preparation	Polymer Used	Application	References
1	Dicyclomine	-	Quasi-emulsion solvent diffusion.	Eudragit S-100	New colon-specific medication delivery method. Polysaccharides derived from nature (pectin) for the treatment of irritable bowel syndrome.	93
2	Silver sulfadiazine	Gel	w/o/w emulsion solvent evaporation.	Carbopol 934 and Ethyl cellulose (18–22 cps viscosity grade) (EC).	Reduce application frequency, reduce skin irritation, low cytotoxicity on dermal cell lines.	94
3	Levonorgestrel	-	Quasi-emulsion solvent diffusion.	Carbopol 934	Improve the bioavailability of the drug.	95
4	Indomethacin	Gel Cream	Quasi-emulsion solvent diffusion.	Eudragit RS 100	Reduces the number of doses required, improve the pharmacological action.	68
5	Paeonol	Cream	Quasi-emulsion solvent diffusion.	Ethyl cellulose-M70	Enhance paeonol permeation rate while minimizing transdermal drug penetration into the body, resulting in increased drug bioavailability.	96
6	Cinnarizine	Tablet	Quasi-emulsion solvent diffusion	Ethyl cellulose, PEG-8 caprylic,	Sustained targeted delivery system for treatment of vertigo, motion sickness, and vomiting.	97
7	Mupirocin	Emugel	Emulsion solvent diffusion method.	Ethyl cellulose and di-chloromethane as a solvent which contained PVA as an emulsifying agent.	Increased skin retention for treating skin infections.	98
8	Loratadine	Liqui-gel	Quasi-emulsion solvent diffusion.	Ethyl cellulose and PVA.	Controlled-release bioadhesive floating microsponges.	99
9	Carbamazepine	Tablet	Quasi-emulsion solvent diffusion technique.	Ethyl cellulose and Polyvinyl Alcohol (PVA).	Better encapsulation and sustained release of CBZ for oral administration.	100
10	Acetazolamide	Topical MSP <i>in situ</i> ocular gel	Liquid-liquid suspension polymerization methods. Water-in-oil-in-water (w/o/w) emulsion solvent diffusion.	Ethyl cellulose polymer.	Anti-glaucoma agent.	101




Figure 3: Physicochemical characterization of microsponges.

Table 7: The microsphere delivery technique incorporated anti-diabetic medicines.

Sl. No.	Active Drug	Formulation Type	Method of Preparation	Polymer Used	Application	References
1	Nateglinide	-	w/o/o double emulsion solvent diffusion.	Ethyl cellulose and hydroxy propyl methyl cellulose.	Type-2 diabetes treatment (non-insulin-dependent).	-
2	Nebivolol	Gel	Oil in oil emulsion solvent diffusion.	Eudragit RS 100 and Carbopol 934.	Diabetic rats healed wounds faster.	105
3	Mitiglinide calcium	-	Quasi-emulsion solvent diffusion method.	Eudragit RS100, ethyl cellulose, and polyvinyl alcohol.	Gastroretentive MSP improves diabetes treatment by eliminating frequent dosages.	103
4	Glipizide	Floating micro- sponge	Quasi-emulsion solvent diffusion method.	Polyvinyl alcohol, triethyl citrate.	Gastro-retentive diabetes medicines.	104

loading, including less side effects, higher stability, formulation attractiveness, and formulation flexibility.¹⁰⁸⁻¹¹⁹

Antimicrobial Drug Entrapment Microsponge

Most bacteria acquire multidrug resistance, making treating microbial illnesses difficult. Antibiotic delivery techniques improve effectiveness and lower costs to fight MDR. Microspheres, nanoparticles, microsponges, and liposomes may be used to better disperse active medicines.⁶⁶ The pharmaceutical industry's biggest issue is regulating active medicine distribution to a specific body area. The microsponge delivery system is easy

to build and may regulate drug release through rate, location, or both.¹²⁰ Table 9 lists microsponge delivery method antibacterial medicines.¹²¹⁻¹³⁰

SCOPE AND FUTURE PROSPECTIVES OF MICROSPONGE DELIVERY SYSTEMS

MDS has a promising future in the pharmaceutical industry due to its unique properties, which include enhanced product performance and refinement, extended release, less irritation, increased physical, chemical, and thermal stability, and the ability to create innovative product morphologies. MDS is designed to

Table 8: Anti-allergic and anti-inflammatory medication contained inside a microsphere delivery mechanism.

Sl. No.	Active Drug	Formulation Type	Method of Preparation	Polymer Used	Application	References
1	Hydroxyzine hydrochloride	-	Oil-in-oil emulsion solvent diffusion.	Methocel 10000 cps and in combination with Eudragit -S 100, Eudragit-L 100, EudragitRL 100 and Eudragit-RS 100.	Anti-allergic	46
2	Curcumin	MSP in oral capsule and topical drug delivery	Quasi-emulsion solvent diffusion.	Ethyl cellulose and Eudragit S 100.	Anti-inflammatory. Treatment of gastric cancer.	108
3	Celecoxib	Topical MSP gel	Quasi emulsification solvent diffusion.	Eudragit L-100, Ethyl cellulose, Polyvinyl Alcohol.	NSAID (Arthritis), Excellent trapping efficiency and regulated drug release <i>in vitro</i> .	109
4	Diclofenac sodium	Colon targeted MSP	Quasi-emulsion solvent diffusion.	Xanthan gum-facilitated ethyl cellulose microsponges p.	NSAID	110
5	Ketoprofen	MSP	Quasi-emulsion solvent diffusion.	Eudragit RS 100	NSAID (arthritis) creams cure superficial skin mycoses.	111
6	Lornoxicam	Cellulosic-microsphere gel	Quasi-emulsion solvent diffusion.	Polyvinyl alcohol (PVA), Tween80, Gelucire 48/16 and Gelucire 50/13.	NSAID (rat rheumatoid arthritis) provides rapid and persistent anti-inflammatory effects.	112-113
7	Mesalamine	Colon-specific MSP tablet	Quasi-emulsion solvent diffusion.	Eudragit RS100, Eudragit S-100 and Eudragit L100.	IBD anti-inflammatory.	114
8	Betamethasone	Controlled release gel	Quasi-emulsion solvent diffusion.	Eudragit RS 100	Skin-anti-inflammatory gel.	115
9	Flurbiprofen (FLB)	-	Quasi-emulsion solvent diffusion.	Eudragit RS 100	Colon medicine administration.	95
13	Paracetamol	MSP tablet	Quasi-emulsion solvent diffusion.	Eudragit RS 100	PCM-based colon-specific medication delivery.	116
14	Diclofenac diethylamine	Gel	Quasi-emulsion solvent diffusion.	Eudragit RS 100	Treating arthritis and musculoskeletal disorders.	12
15	Piroxicam	MSP topical gel for transdermal delivery	Quasi-emulsion solvent diffusion.	Eudragit RS100, RL100, S100	NSAID (Arthritis).	117
16	Ibuprofen	-	Quasi-emulsion solvent diffusion.	Acrylic and Eudragit RS	After compression, microsponges released a lot of tension, making them compressible.	118
17	Fenoprofen	-	Quasi-emulsion solvent diffusion.	Eudragit RS 100 and Chitosan and HPMC for tablet preparation	For colon-targeted, long-term medication.	119
18	Naproxen	Gel	Quasi-emulsion solvent diffusion.	Eudragit RS-100, carbopol, and PVA	Anti-allergic.	106

Table 9: List of anti-microbial agents entrapped in a microsphere delivery system.

Sl. No.	Active Drug	Method of Preparation	Polymer Used	Applications	References
1	Econazole nitrate	Quasi-emulsion solvent diffusion	Eudragit RS100	Anti-fungal	121
2	Ritonavir	Quasi-emulsion solvent diffusion	Eudragit® RS100 in combination with Polycaprolactone triol 300 (NPR-300) or Polycaprolactone triol 900 (NPR-900).	Antiviral agent	122
3	Mupirocin	Emulsion solvent diffusion	Ethyl cellulose in dichloromethane	Dermatological antibiotic. Topical administration devices for greater skin drug deposition and longer release.	98
4	Metronidazole	w/o/w emulsion solvent evaporation	Ethyl cellulose	Skin infections.	123
5	Ketoconazole	Quasi-emulsion solvent diffusion	Carbapol 940 and Eudragit RS 100	It decreased fungal gel usage on fungal-induced guinea pig skin.	124
6	Eberconazole nitrate (EB)	Quasi-emulsion solvent diffusion	Ethyl cellulose, Polyvinyl alcohol and Dichloromethane.	Topical fungal treatment may carry EB.	125
7	Tolnaftate	Quasi-emulsion solvent diffusion technique, the liquid-liquid polymerization method	Eudragit RS 100, Eudragit RL 100, Hydroxy propyl methyl cellulose (HPMC) and Carbopol 934.	Anti-fungal.	126
8	Dapsone	Quasi-emulsion solvent diffusion technique	Ethylcellulose	Spherical, homogeneous, and spongy microparticles with good encapsulation efficiency.	127
9	Flutrimazole	Quasi-emulsion solvent diffusion	Eudragit RS 100	Medication release control and topical treatment of superficial mycoses.	128
10	Clotrimazole	Quasi-emulsion solvent diffusion	Ethyl cellulose and PVA	Long-term medication release from carbopol-loaded clotrimazole microsphere.	129
11	Miconazole (MCZ)	Quasi-emulsion solvent diffusion	Eudragit RS 100	Miconazole (MCZ) vaginal candidiasis microspheres intrigue.	70
12	Babchi Essential Oil (BEO)	Quasi-emulsion solvent diffusion	Encapsulate BEO in Ethyl Cellulose (EC).	Babchi oil may cure dermatological conditions and skin irritation by reducing skin contact.	130

deliver topical antifungal, anti-inflammatory, and anti-dandruff medications. The list of granted patents for the microsphere industry, which spans the years 1985 to 2021, includes a vast array of innovations. Modifying polymer ratios is essential for the advancement of core/shell microsphere delivery systems for oral peptide administration. In addition, it can be used for tissue engineering and biopharmaceutical delivery of colon-specific pharmaceuticals. Because of the development of novel pharmaceuticals and biopharmaceuticals, drug delivery systems are advancing significantly (peptides, proteins, and DNA-based

therapeutics). Micro-sized delivery systems are now obsolete, and the search for nanosized carriers is currently intensifying. Micron-sized particles have a much lower ratio of specific surface area to size and a lower capacity to alter active release than nano-sized particles. Although inorganic nanospheres have numerous applications in electronics, more research is required before they can be utilized effectively in medicine. Nanospheres will undoubtedly continue to be popular in the future.¹³¹⁻¹³⁴ Several articles also discuss the use of microsphere-based catalysts for the degradation of environmental contaminants in water and

Table 10: Patent databases related to medication delivery systems using microsponges

Sl. No.	Title of Patent (Description)	Inventors	Patent Number	Publication Year	References
1	Compositions and methods of manufacture of compressed powder medicaments.	Theodore H. Stanley and Brian Hague	US5855908A	1985	140
2	Weighted microsphere for immobilizing bioactive material.	Robert, <i>et al.</i>	WO1986005811A1	1986	141
3	Method for delivering an active ingredient by controlled time release utilizing a novel delivery vehicle which can be prepared by a process utilizing the active ingredient as a porogen.	Won R (Palo Alto, CA)	US 4,690,825	1987	142
4	Production of microsphere.	Hiroshi Sakadou and Sueo Kida	JPS63170436A	1988	143
5	Weighted collagen microsphere for immobilizing bioactive materials.	Dean, <i>et al.</i>	US4863856	1989	68
6	Wet wipes.	Ho-ward J. Yoh	US4904524A	1990	
7	Two-step method for preparation of controlled release formulations.	Won R (Palo Alto, CA)	US 5,145,675	1992	144
8	Microsphere reservoirs for controlled release application.	Ray, <i>et al.</i>	US5725869	1996	145
9	Retinoid formulations in porous microspheres for reduced irritation and enhanced stability.	Forix, <i>et al.</i>	US5851538	1998	146
10	Percutaneous delivery system.	Tomlinson, <i>et al.</i>	US6211250	2001	147
11	Stabilized retinol for cosmetic dermatological and pharmaceutical compositions, and use thereof.	Shefer, <i>et al.</i>	US20030232091	2002	148
12	Analgesic cream comprising salicylate dispersed in silicone oil and microsphere for sustained delivery of counterirritants like menthol.	Koral Embil	WO2004014397A1	2003	149
13	Chitosan microparticles for the topical delivery of water- insoluble active agents.	Cattaneo and Maurizio	US20040247632	2004	150
14	Topical pharmaceutical and/or cosmetic dispense systems.	Koral Embil and Sergio Nacht	WO2004064803A1	2004	151
15	Drug delivery polymer with hydrochloride salt of clindamycin.	Halliday	US20080160065	2008	152
16	Nonwoven towel with microsponges.	Franklin, <i>et al.</i>	US7426776	2008	153
17	Method of removing ticks from the epidermal tissue of humans and other mammals.	Kariyon Inc.	US7604814	2009	154
18	Topical anti-acne preparations containing retinoid (tazarotene or adapalene), antibiotic (clindamycin phosphate) and/or keratolytic (microsphere benzoyl peroxide).	Fernando Ahumada Ayala	US20090318371A1	2010	155

Sl. No.	Title of Patent (Description)	Inventors	Patent Number	Publication Year	References
19	Topical administration carrier composition and therapeutic formulations comprising the same.	Celmatrix Corporation	US7749489	2011	156
20	Method of removing ticks from the skin and reducing the risk of bites.	Karykion Corporation	US8323672	2012	157
21	Nucleic acid particles, methods and use thereof.	Hammond, <i>et al.</i>	WO2014134029A1	2014	158
22	Gel composition for the treatment of common acne comprising a combination of benzoyl peroxide and adapalene and/or adapalene salt.	Galderma Research and Development	US8936800	2015	159
23	Method and apparatus for acne treatment using low-intensity light therapy.	David H. McDaniel	US9227082B2	2016	160
24	Mesalamine loaded microsponges formulation.	Dr. Rohitas Deshmukh, <i>et al.</i>	202211031794	2022	166
25	A topical gel formulation comprising microsponges of basil oil and process of preparation thereof.	Ritu Rathi, <i>et al.</i>	202211024801	2022	167
26	Microsponges drug delivery system of polyherbal drug for hepato-protective disorder.	Kishori Sunil Jagtap, <i>et al.</i> ,	202221023987	2022	168

soil samples.¹³⁵⁻¹³⁹ In 2012, Francisco Trotta *et al.* developed cyclodextrin-based nanosponges, which have been heralded as a revolutionary nanosized delivery system (Table 10).^{140-159, 161-187}

CONCLUSION

Microsponges are polymeric delivery system that employ spherical nanoparticles. These systems are made up of porous microspheres varying in size from 5 to 300 micrometers, depending on the degree of flattening or after-feel needed in the final formulation. Polymeric delivery systems are made up of porous microspheres that may contain a wide range of active ingredients, including emollients, perfumes, essential oils, sunscreens, anti-infectives, antifungals, anti-inflammatory medicines, and certain antibiotics. These adaptive microsphere systems are made of polymeric materials. The pace of medicine release may be adjusted by choosing the appropriate polymer for injection. As a result, the Microsphere Delivery System (MDS) is a cutting-edge and evolving technology for regular medicine delivery that is now being studied. The microsphere delivery technology, which uses bio erodible polymers and tissue engineering, was initially created for topical distribution but is now used for controlled oral administration. Drug release from microsphere may be regulated, as with other new drug carriers, by altering the medium's polymer solubility, pH, and temperature. Moreover, they may increase medication stability, reduce unwanted effects, and change drug release in a good

way. Because of its many benefits, the microsphere method is a trustworthy approach for giving medicine. Moreover, because to its beneficial properties such as continuous release, reduced irritancy, small size, self-sterility, and interoperability with many vehicles and components, MDS has a promising future in a range of therapeutic formulations.

ACKNOWLEDGEMENT

The authors are thankful to their parents.

CONFLICT OF INTEREST

The authors declare that there is no conflict of interest.

ABBREVIATIONS

5-FU: 5-Fluorouracil; **API:** Active Pharmaceutical ingredient; **BCD:** Beta-cyclodextrin; **BEO:** Babchi Essential Oil; **DMF:** Dimethyl Formamide; **DMSO:** Dimethyl Sulphoxide; **DSC:** Differential Scanning Calorimetry; **EC:** Ethyl Cellulose; **FTIR:** Fourier Transform Infrared Spectroscopy; **GIT:** Gastro-intestinal Tract; **HPLC:** High-pressure Liquid Chromatography; **HPMC:** Hydroxypropyl Methylcellulose; **IBD:** Inflammatory Bowel Disease; **LBL:** Layer-by-layer; **MDS:** Microsphere Delivery System; **MIC:** Minimum Inhibitory Concentration; **MLX:** Meloxicam; **MSP:** Microsphere; **NSAID:** Non-steroidal anti-inflammatory drugs; **PCM:** Paracetamol; **PEG:** Polyethylene

Glycol; **pHEMA**: Poly (2-hydroxyethyl Methacrylate); **PVA**: Polyvinyl Alcohol; **PXRD**: Powder X-ray Diffraction; **RNAi**: RNA Interference; **SEM**: Scanning Electron Microscopy; **iRNA**: Small Interfering RNA; **TDS**: Transdermal Delivery System; **TEC**: Triethylcitrate; **VOAG**: Vibrating Orifice Aerosol Generator.

AUTHOR'S CONTRIBUTIONS

Conceptualization: Suraj Mandal, Km. Bhumika.

Writing Original Draft: Suraj Mandal, Mukesh Kumar, Jiyaul Hak.

Writing-review and Editing: Suraj Mandal

Supervision: Prabhakar Vishvakarma, Umesh Kumar Sharma.

REFERENCES

- Patra JK, Das G, Fraceto LF, Campos EVR, Rodriguez-Torres MDP, Acosta-Torres LS, *et al.* Nano based drug delivery systems: recent developments and future prospects. *J Nanobiotechnology*. 2018;16(1):71. doi: 10.1186/s12951-018-0392-8, PMID 30231877.
- Kita K, Ditttrich C. Drug delivery vehicles with improved encapsulation efficiency: taking advantage of specific drug-carrier interactions. *Expert Opin Drug Deliv*. 2011;8(3):329-42. doi: 10.1517/17425247.2011.553216, PMID 21323506.
- Singh K, Biharee A, Vyas A, Thareja S, Jain AK. Recent advancement of polymersomes as drug delivery carrier. *Curr Pharm Des*. 2022;28(20):1621-31. doi: 10.2174/1381612828666220412103552, PMID 35418282.
- Asghar LF, Chandran S. Multiparticulate formulation approach to colon specific drug delivery: current perspectives. *J Pharm Pharm Sci*. 2006;9(3):327-38. PMID 17207416.
- Jose S, Prema MT, Chacko AJ, Thomas AC, Souto EB. Colon specific chitosan microspheres for chronotherapy of chronic stable angina. *Colloids Surf B Biointerfaces*. 2011;83(2):277-83. doi: 10.1016/j.colsurfb.2010.11.033, PMID 21194900.
- Simonoska Crcarevska M, Dimitrovska A, Sibinovska N, Mlade-Novska K, Slavevska Raicki R, Glavas Dodov M. Implementation of quality by design principles in the development of microsponges as drug delivery carriers: identification and optimization of critical factors using multivariate statistical analyses and design of experiments studies. *Int J Pharm*. 2015;489(1-2):58-72. doi: 10.1016/j.ijpharm.2015.04.038, PMID 25895722.
- Srivastava R, Pathak K. Microsponges: A futuristic approach for oral drug delivery. *Expert Opin Drug Deliv*. 2012;9(7):863-78. doi: 10.1517/17425247.2012.693072, PMID 22663167.
- Nokhodchi A, Jelvehgari M, Siahi MR, Mozafari MR. Factors affecting the morphology of benzoyl peroxide microsponges. *Micron*. 2007;38(8):834-40. doi: 10.1016/j.micron.2007.06.012, PMID 17692528.
- Kaity S, Maiti S, Ghosh AK, Pal D, Ghosh A, Banerjee S. Microsponges: A novel strategy for drug delivery system. *J Adv Pharm Technol Res*. 2010; 1(3): 283-90. doi: 10.4103/0110-5558.72416, PMID 22247859.
- Ravi R, Kumar SS, Parthiban S. Formulation and evaluation of the microsponges gel for an anti-acne agent for the treatment of acne. *Indian J PharmSci Res*. 2013;3:32-8.
- Osmani RAM, Aloorkar NH, Thaware BU, Kulkarni PK, Moin A, Hani U, *et al.* Microsponge based drug delivery system for augmented gastroparesis therapy: formulation development and evaluation. *Asian J Pharm Sci*. 2015;10(5): 442-51. doi: 10.1016/j.ajps.2015.06.003.
- Osmani RAM, Aloorkar NH, Ingale DJ, Kulkarni PK, Hani U, Bhosale RR, *et al.* Microsponges based novel drug delivery system for augmented arthritis therapy. *Saudi Pharm J*. 2015;23(5):562-72. doi: 10.1016/j.jsps.2015.02.020, PMID 26594124.
- Grimes PE. A microsphere formulation of hydroquinone 4% and retinol 0.15% in the treatment of melasma and post-inflammatory hyperpigmentation. *Cutis*. 2004;74(6):362-8. PMID 15663072.
- Abioye A. Polymer-drug nanoconjugate—an innovative nanomedicine: challenges and recent advancements in rational formulation design for effective delivery of poorly soluble drugs. *Pharm Nano- Technol*. 2016;4(1):38-79. doi: 10.2174/2211738504666160213001714.
- Osmani RA, Aloorkar NH, Kulkarni AS, Harkare BR, Bhosale RR. A new cornucopia in topical drug delivery: microsphere technology. *Asian J Pharm Sci Technol*. 2014;4:48-60.
- Nacht S, Katz M. The microsphere: A novel topical programmable delivery system. *Drugs Pharm Sci*. 1990;42:299-325.
- Shivakumar HN, Suresh S, Desai BG. Design and evaluation of controlled onset extended release multi-particulate systems for chronotherapeutic delivery of ketoprofen. *Indian J Pharm Sci*. 2006; 68(1): 76. doi: 10.4103/0250-474X.22969.
- Sharma S, Pawar A. Low density multi-particulate system for pulsatile release of meloxicam. *Int J Pharm*. 2006;313(1-2):150-8. doi: 10.1016/j.ijpharm.2006.02.001, PMID 16540268.
- Khramtsov P, Burdina O, Lazarev S, Novokshonova A, Bochkova M, Timanova V, *et al.* Modified desolvation method enables simple one-step synthesis of gelatin nanoparticles from different gelatin types with any bloom values. *Pharmaceutics*. 2021;13(10):1537. doi: 10.3390/pharmaceutics13101537, PMID 34683829.
- Saboktakin M, Saboktakin A. Novel Thermal Insulations for Architecture.
- Vishwakarma P, Microsponges CR. A novel strategy to control the delivery rate of active agents with reduced skin irritancy. *J Drug Deliv Ther*. 2019;9(6S):238-47. doi: 10.22270/jddt.v9i6-s.3757.
- Zhang X, Xing H, Zhao Y, Ma Z. Pharmaceutical dispersion techniques for dissolution and bioavailability enhancement of poorly water-soluble drugs. *Pharmaceutics*. 2018;10(3):74. doi: 10.3390/pharmaceutics10030074, PMID 29937483.
- Oberholzer ID. Peroral and nasal delivery of insulin with Pheroid™ technology. North-West University; 2009.
- Johnson T, Bahrampourian R, Patel A, Mequanint K. Fabrication of highly porous tissue-engineering scaffolds using selective spherical porogens. *Bio Med Mater Eng*. 2010;20(2):107-18. doi: 10.3233/BME-2010-0621, PMID 20592448.
- Zhang G, Li G, Wang K. Wave structure of oblique detonation disturbed by an expansion wave from a bended tunnel. *Appl Therm Eng*. 2020;180:115856. doi: 10.1016/j.applthermaleng.2020.115856.
- Hari K, Prathyusha SS, Vasavi G. Microsponges: A de novo method for colon targeted oral drug delivery. *Int J Pharm Investig*. 2020;10(3):237-45. doi: 10.5530/ijpi.2020.3.44.
- Crinnion W. AARP Clean, Green, and Lean: get rid of the toxins that make you fat. John Wiley and Sons; 2011.
- Cao Y, Feng J, Wu P. Preparation of organically dispersible graphene nanosheet powders through a lyophilization method and their poly(lactic acid) composites. *Carbon*. 2010;48(13):3834-9. doi: 10.1016/j.carbon.2010.06.048.
- Thanh LT, Okitsu K, Sadanaga Y, Takenaka N, Maeda Y, Bandow H. Ultrasound-assisted production of biodiesel fuel from vegetable oils in a small scale circulation process. *Bioresour Technol*. 2010;101(2):639-45. doi: 10.1016/j.biortech.2009.08.050, PMID 19736002.
- Moussa M, Martinet V, Trimeche A, Tainturier D, Anton M. Low density lipoproteins extracted from hen egg yolk by an easy method: cryoprotective effect on frozen-thawed bull semen. *Their- ogenesis*. 2002;57(6):1695-706. doi: 10.1016/S0093-691X(02)00682-9, PMID 12035979.
- Zhang W, Ning S, Zhang S, Wang S, Zhou J, Wang X, *et al.* Synthesis of functional silica composite resin for the selective separation of zirconium from scandium. *Micropor Mesopor Mater*. 2019;288:109602. doi: 10.1016/j.micromeso.2019.109602.
- Takeshita S, Zhao S, Malfait WJ, Koebel MM. Chemistry of Chitosan Aerogels: three-dimensional pore control for tailored applications. *Angew Chem Int Ed Engl*. 2021;60(18):9828-51. doi: 10.1002/anie.202003053, PMID 32270894.
- Bohr A, Boetker JP, Rades T, Rantanen J, Yang M. Application of spray-drying and electrospraying/electrospinning for poorly water-soluble drugs: A particle engineering approach. *Curr Pharm Des*. 2014;20(3):325-48. doi: 10.2174/1381612811319990399, PMID 23651398.
- Bae SE, Son JS, Park K, Han DK. Fabrication of covered porous PLGA microspheres using hydrogen peroxide for controlled drug delivery and regenerative medicine. *J Control Release*. 2009;133(1): 37-43. doi: 10.1016/j.jconrel.2008.09.006, PMID 18838089.
- Aloorkar N, Kulkarni A, Ingale D, Patil R. Microsponges as innovative drug delivery systems. *Int J PharmSci Nanotechnol*. 2012;5(1):1597-606.
- Li Q, Shen HX, Liu C, Wang C-F, Zhu L, Chen S. Advances in frontal polymerization strategy: from fundamentals to applications. *Prog Polym Sci*. 2022;127:101514. doi: 10.1016/j.progpolymsci.2022.101514.
- Singhvi G, Manchanda P, Hans N, Dubey SK, Gupta G. Microsphere: an emerging drug delivery strategy. *Drug Dev Res*. 2019;80(2): 200-8. doi: 10.1002/ddr.21492, PMID 30456763.
- Dua JS, Prasad D, Hans M, Sharma R, Kumari S. Novel Strategy: microsponges for topical drug delivery. *J Drug Deliv Ther*. 2019; 9(3-s):1025-31.
- Shi A, Feng X, Wang Q, Adhikari B. Pickering and high internal phase Pickering emulsions stabilized by protein-based particles: a review of synthesis, application and prospective. *Food Hydrocoll*. 2020;109:106117. doi: 10.1016/j.foodhyd.2020.106117.
- Arya P, Pathak K. Assessing the viability of microsponges as gastro retentive drug delivery system of curcumin: optimization and pharmacokinetics. *Int J Pharm*. 2014;460(1-2):1-12. doi: 10.1016/j.ijpharm.2013.10.045, PMID 24184218.
- Rosenhek I 2008.
- Rawat A, Majumder QH, Ahsan F. Inhalable large porous micro- spheres of low molecular weight heparin: *in vitro* and *in vivo* evaluation. *J Control Release*. 2008;128(3):224-32. doi: 10.1016/j.jconrel.2008.03.013, PMID 18471921.
- Maiti S, Kaity S, Ray S, Sa B. Development and evaluation of xanthan gum-facilitated ethyl cellulose microsponges for controlled percutaneous delivery of diclofenac sodium. *Acta Pharm*. 2011; 61(3): 257-70. doi: 10.2478/v10007-011-0022-6, PMID 21945905.

44. Giri TK, Choudhary C, Ajazuddin AA, Alexander A, Badwaik H, Tripathi DK. Prospects of pharmaceuticals and biopharmaceuticals loaded microparticles prepared by double emulsion technique for controlled delivery. *Saudi Pharm J*. 2013;21(2):125-41. doi: 10.1016/j.jsps.2012.05.009, PMID 23960828.
45. Mandal TK, Bostanian LA, Graves RA, Chapman SR, Idodo TU. Porous biodegradable microparticles for delivery of pentamidine. *Eur J Pharm Biopharm*. 2001;52(1):91-6. doi: 10.1016/S0939-6411(01)00150-3, PMID 11438428.
46. Zaki Rizkalla CM, Latif Aziz R, Soliman II. *In vitro* and *in vivo* evaluation of hydroxyzine hydrochloride microsponges for topical delivery. *AAPS PharmSciTech*. 2011;12(3):989-1001. doi: 10.1208/s12249-011-9663-5, PMID 21800216.
47. Ramaia A. Detecting torsional motion of kinesin motor proteins using birefringent microspheres and high-resolution optical tweezers. *Universität Tübingen*; 2018.
48. Trotta F, Cavalli R, Tumiatti W, et al. Ultrasound-assisted synthesis of cyclodextrin-based nanosponges. *WO2006002814A1*, 2008.
49. Gan Y, Zhang Y, Cheng D, Shetty A, Rathi P, Katarki N, et al. editors. An open-source benchmark suite for microservices and their hardware-software implications for cloud and edge systems. In: *Proceedings of the Twenty-Fourth International Conference on Architectural Support for Programming Languages and Operating Systems*; 2019:3-18. doi: 10.1145/3297858.3304013.
50. Mahant S, Kumar S, Nanda S, Rao R. Microsponges for dermatological applications: perspectives and challenges. *Asian J Pharm Sci*. 2020;15(3):273-91. doi: 10.1016/j.ajps.2019.05.004, PMID 32636947.
51. Pifferi G, Santoro P, Pedrani M. Quality and functionality of excipients. *Farmaco*. 1999;54(1-2):1-14. doi: 10.1016/S0014-827X(98)00101-3, PMID 10321025.
52. Tekade R. *Drug delivery systems*. Academic Press; 2019.
53. Embil K, Nacht S. The Microsponge® Delivery System (MDS): A topical delivery system with reduced irritancy incorporating multiple triggering mechanisms for the release of actives. *J Microencapsul*. 1996;13(5):575-88. doi: 10.3109/02652049609026042, PMID 8864994.
54. Srivastava R, editor. *Microsponges for drug delivery*. Taylor: CRC Press and Francis Group; 2017.
55. Bussemer T, Otto I, Bodmeier R. Pulsatile drug-delivery systems. *Crit Rev Ther Drug Carrier Syst*. 2001;18(5):433-58. doi: 10.1615/CritRevTherDrugCarrierSyst.v18.i5.10, PMID 11763497.
56. Jain D, Bar-Shalom D. Alginate drug delivery systems: application in context of pharmaceutical and biomedical research. *Drug Dev Ind Pharm*. 2014;40(12):1576-84. doi: 10.3109/03639045.2014.917657, PMID 25109399.
57. Jain A, Gulbake A, Shilpi S, Jain A, Hurkat P, Jain SK. A new horizon in modifications of chitosan: syntheses and applications. *Crit Rev Ther Drug Carrier Syst*. 2013;30(2):91-181. doi: 10.1615/critrevtherdrugcarriersyst.2013005678. PMID 23510147.
58. Jain SK, Kaur M, Kalyani P, Mehra A, Kaur N, Panchal N. Microsponges enriched gel for enhanced topical delivery of 5-fluorouracil. *J Microencapsul*. 2019;36(7):677-91. doi: 10.1080/02652048.2019.1667447, PMID 31509035.
59. Kumari A, Jain A, Hurkat P, Tiwari A, Jain SK. Eudragit S100 coated microsponges for colon targeting of prednisolone. *Drug Dev Ind Pharm*. 2018;44(6):902-13. doi: 10.1080/03639045.2017.1420079, PMID 29260916.
60. Srivastava R, Kumar D, Pathak K. Colonic luminal surface retention of meloxicam microsponges delivered by erosion based collagen-targeted matrix tablet. *Int J Pharm*. 2012;427(2):153-62. doi: 10.1016/j.ijpharm.2012.01.036, PMID 22306039.
61. Farris PK. *Cosmeceuticals and cosmetic practice*. John Wiley and Sons; 2013. doi:10.1002/9781118384824.
62. Kydonieus AF, Berner B. *Transdermal delivery of drugs*. CRC Press; 1987.
63. Dimatteo R, Darling NJ, Segura T. *In situ* forming injectable hydrogels for drug delivery and wound repair. *Adv Drug Deliv Rev*. 2018;127: 167-84. doi: 10.1016/j.addr.2018.03.007, PMID 29567395.
64. Lammers T, Aime S, Hennink WE, Storm G, Kiessling F. Theranostic nanomedicine. *Acc Chem Res*. 2011;44(10):1029-38. doi: 10.1021/ar200019c, PMID 21545096.
65. Chadawar V, Shaji J. Microsponge delivery system. *Curr Drug Deliv*. 2007;4(2):123-9. doi: 10.2174/156720107780362320, PMID 17456031.
66. Kumar R, Bhowmick M, Dubey B. Polymeric microsponge technology—an overview on highly cross-linked porous spherical particles for topical delivery. *Inventi Impact NDDS*. 2012;2012(2):1-7.
67. Jelvehgari M, Siahi-Shadbad MR, Azarmi S, Martin GP, Nokhodchi A. The microsponge delivery system of benzoyl peroxide: preparation, characterization and release studies. *Int J Pharm*. 2006;308(1-2):124-32. doi: 10.1016/j.ijpharm.2005.11.001, PMID 16359833.
68. Gangadharappa HV, Gupta NV, Prasad M SC, Shivakumar HG. Current trends in microsponge drug delivery system. *Curr Drug Deliv*. 2013;10(4):453-65. doi: 10.2174/1567201811310040010, PMID 22974222.
69. JAIN R. A study on physical fitness and psycho social parameters of adolescent school students; 2018.
70. Salah S, Awad GEA, Makhlof AIA. Improved vaginal retention and enhanced antifungal activity of miconazole microsponges gel: formulation development and *in vivo* therapeutic efficacy in rats. *Eur J Pharm Sci*. 2018;114:255-66. doi: 10.1016/j.ejps.2017.12.023, PMID 29288706.
71. Shukla A, Garg A, Garg S. Application of microsponge technique in topical drug delivery system. *Asian J Biomater Res*. 2016;2(4):120-6.
72. Pradhan SK. Microsponges as the versatile tool for drug delivery system. *Int J Res Pharm Chem*. 2011;1(2):243-58.
73. Kumari A, Jain A, Hurkat P, Verma A, Jain SK. Microsponges: A pioneering tool for biomedical applications. *Crit Rev Ther Drug Carrier Syst*. 2016;33(1):77-105. doi: 10.1615/CritRevTherDrugCarrierSyst.v33.i1.40, PMID 27279339.
74. Verma NK, Dru M. *J Chem Pharm Sci*. 2015;3(5):1617-23.
75. Pawar AP, Gholap AP, Kuchekar AB, Bothiraja C, Mali AJ. Formulation and evaluation of optimized oxybenzone microsponge gel for topical delivery. *J Drug Deliv*. 2015; 2015:1-9. doi: 10.1155/2015/261068.
76. Çomoglu T, Gönül N, Baykara T. The effects of pressure and direct compression on tableting of microsponges. *Int J Pharm*. 2002; 242(1-2): 191-5. doi: 10.1016/S0378-5173(02)00155-2, PMID 12176245.
77. Jafar M, Salahuddin M, Khan MSA, Alshehry Y, Alrwaili NR, Alzahrani YA, et al. Preparation and *in vitro-in vivo* evaluation of luteolin loaded gastroretentive micro-sponge for the eradication of *Helicobacter pylori* infections. *Pharmaceutics*. 2021;13(12):2094. doi: 10.3390/pharmaceutics13122094, PMID 34959375.
78. Abdellatif AAH, Yayed GM, Kamel HH, Mohamed AG, Arafa WM, Khatib AM, et al. A novel controlled release microsponges containing albendazole against *Haemonchus contortus* in experimentally infected goats. *J Drug Deliv Sci Technol*. 2018;43:469-76. doi: 10.1016/j.jddst.2017.10.022.
79. Charagonda S, Puligilla RD, Ananthula MB, Bakshi V. Formulation and evaluation of famotidine floating microsponges. *Int Res J Pharm*. 2016; 7(4): 62-7. doi: 10.7897/2230-8407.07440.
80. Agarwal A, Shukla T, Jain N, et al. Formulation and development pantoprazole loaded microsponges for management of GERD. *World J Pharm Pharm Sci*. 2015;4(12):1114-26.
81. Tadwee I, Shahi S. Formulation development of microsponge based delayed release dosage form of lansoprazole. *Int J Pharm Sci Res*. 2018;9(2):824-31.
82. Martin A, Swarbrick J, Cammarrata A. 527.
83. Tatterton MR. Development of tissue engineered blood vessels using cell-seeded acellular porcine arterial scaffolds. *University of Leeds*; 2015.
84. Bou-Gharios G, Ponticos M, Rajkumar V, Abraham D. Extra-cellular matrix in vascular networks. *Cell Prolif*. 2004; 37(3): 207-20. doi: 10.1111/j.1365-2184.2004.00306.x, PMID 15144498.
85. D'Emanuele A, Dinarvand R. Preparation, characterisation, and drug release from thermoresponsive microspheres. *Int J Pharm*. 1995;118(2):237-42. doi: 10.1016/0378-5173(94)00384-H.
86. Abd Alhammid SN. Enhancement of the solubility and the dissolution rate of candesartan cilexetil using microsponge technology. *Asian J Pharm Clin Res*. 2018;11(9):385-90. doi: 10.22159/ajpcr.2018.v11i9.26816.
87. Jain P, Darwehkar G, Khan F, Kukde D, Sharma V. Formulation and evaluation of colon specific tablet containing microsponges of metoprolol succinate. *Int J Pharm Life Sci*. 2015;6(12).
88. Patel SS, Patel MR, Patel MJ. Formulation and evaluation of microsponge based nitorandil sustained released tablet. *J Sci Res*. 2017;9(3):285-96. doi: 10.3329/jsr.v9i3.31193.
89. Haydar AL M. Formulation of telmisartan microsponge tablets and *in vitro* evaluation of dissolution profile. *Karbala J PharmSci*. 2015;6(9):91-104.
90. Desavathu M, Pathuri R, Chunduru M. Design, development and characterization of valsartan microsponges by quasi emulsion technique and the impact of stirring rate on microsponge formation. *J App Pharm Sci*. 2017;7(1):193-8. doi: 10.7324/JAPS.2017.070128.
91. Maheshwari R, Sharma P, Tekade M, et al. Microsponge embedded tablets for sustained delivery of nifedipine. *Pharm nanotech*. 2017;5(3):192-202. PMID 28933273.
92. Junqueira MV, Bruschi ML. A review about the drug delivery from microsponges. *AAPS Pharm Sci Tech*. 2018;19(4):1501-11. doi: 10.1208/s12249-018-0976-5, PMID 29484616.
93. Rajurkar V, Gosavi Y. Sustain release microsponge based drug delivery system for the plasmodium treatment: formulation development and *in vitro-in vivo* evaluation. *Anal Chem Lett*. 2018;8(2):205-16. doi: 10.1080/22297928.2018.1429304.
94. Kumar PM, Ghosh A. Development and evaluation of silver sulfadiazine loaded microsponge based gel for partial thickness (second degree) burn wounds. *Eur J Pharm Sci*. 2017;96:243-54. doi: 10.1016/j.ejps.2016.09.038, PMID 27697504.
95. Madane MA, Shinde AD. Formulation and evaluation of microsponge based drug delivery system of levonorgestrel. *Pharmacophore*. 2016;7(4):292-308.
96. Li SS, Li GF, Liu L, Jiang X, Zhang B, Liu ZG, et al. Evaluation of paeonol skin-target delivery from its microsponge formulation: *in vitro* skin permeation and *in vivo* microdialysis. *PLOS ONE*. 2013;8(11):e79881. doi: 10.1371/journal.pone.0079881, PMID 24278204.
97. Raghuvanshi S, Pathak K. Bioadhesive floating microsponges of cinnarizine as novel gastroretentive delivery: Capmul GMO bio-adhesive coating versus acconon MC 8-2 EP/NF with intrinsic bioadhesive property. *Int J Pharm Investig*. 2016; 6(4): 181-93. doi: 10.4103/2230-973X.195923, PMID 28123987.
98. Gangwar A, Kumar P, Singh R, Kush P. Recent advances in mupirocin delivery strategies for the treatment of bacterial skin and soft tissue infection. *Future Pharmacol*. 2021;1(1):80-103. doi: 10.3390/futurepharmacol1010007.

99. Singh S, Pathak K. Assessing the bio adhesivity of Acconon MC 8-2 EP/NF for gastroretention of floating microsponges of loratadine and achieving controlled drug delivery. *Pharm Biomed Res.* 2016;2(2):58-74. doi: 10.18869/acadpub.pbr.2.2.58.
100. Abdalla KF, Osman MA, Nouh AT, El Maghraby GM. Microsponges for controlled release and enhanced oral bioavailability of carbamazepine. *J Drug Deliv Sci Technol.* 2021;65:102683. doi: 10.1016/j.jddst.2021.102683.
101. Obiedallah MM, Abdel-Mageed AM, Elfaham TH. Ocular administration of acetazolamide microsponges *in situ* gel formulations. *Saudi Pharm J.* 2018;26(7):909-20. doi: 10.1016/j.jsps.2018.01.005, PMID 30416345.
102. Subhan MA, Torchilin VP. Efficient nanocarriers of siRNA therapeutics for cancer treatment. *Transl Res.* 2019;214:62-91. doi: 10.1016/j.trsl.2019.07.006, PMID 31369717.
103. Mahmoud DBED, Shukr MH, ElMeshad AN. Gastroretentive microsphere as a promising tool for prolonging the release of mitoglinide calcium in type-2 diabetes mellitus: optimization and pharmacokinetics study. *AAPS Pharm Sci Tech.* 2018; 19(6): 2519-32. doi: 10.1208/s12249-018-1081-5, PMID 29948984.
104. Bhavesh Patel M, Shaikh F, Patel VB, Surti N. Application of experimental design for framing gastroretentive microsponges of glipizide: screening of critical variables by plackett-burman de- sign and optimization by box-Behnken design. *Indian J Pharm Educ Res.* 2021;55(4):966-78. doi: 10.5530/ijper.55.4.197.
105. Pandit AP, Patel SA, Bhanushali VP, Kulkarni VS, Kakad VD. Nebivolol-loaded microsphere gel for healing of diabetic wound. *AAPS Pharm Sci Tech.* 2017;18(3):846-54. doi: 10.1208/s12249-016-0574-3, PMID 27357423.
106. Tambe A, Deshmukh V. Topical anti-inflammatory gels of naproxen entrapped in eudragit based microsphere delivery system. *J Adv Chem Eng.* 2015;5(2):1-6.
107. Kadhim ZM, Mahmood HS, Alayyedi M, Ghareeb MM. Formulation of flurbiprofen as microsphere drug delivery system. *Int J Pharmacol Res.* 2020;12(3):748-53.
108. Sareen R, Nath K, Jain N, Dhar KL. Curcumin loaded microsponges for colon targeting in inflammatory bowel disease: fabrication, optimization, and *in vitro* and pharmacodynamic evaluation. *BioMed Res Int.* 2014; 2014:340701. doi: 10.1155/2014/340701, PMID 25093165.
109. Kadam V, Patel VS, Karpe M, Kadam V. Design, development and evaluation of celecoxib-loaded microsphere-based topical gel formulation. *Appl Clin Res Clin Trials Regul Aff.* 2016;3(1):44-55. doi: 10.2174/2213476X03666160308000647.
110. Hussain H, Dhyani A, Juyal D, Bahuguna A. Formulation and evaluation of gel-loaded microsponges of diclofenac sodium for topical delivery. *J Pharm Innov.* 2014;(10 Part B):3:58.
111. Çomoğlu T, Savaşer A, Özkan Y, Gönül N, Baykara T. Enhancement of ketoprofen bioavailability by formation of microsphere tablets. *Pharmazie.* 2007;62(1):51-4. PMID 17294814.
112. He Y, Majid K, Maqbool M, Hussain T, Yousaf AM, Khan IU, et al. Formulation and characterization of lornoxicam-loaded cellulosic-microsphere gel for possible applications in arthritis. *Saudi Pharm J.* 2020;28(8):994-1003. doi: 10.1016/j.jsps.2020.06.021, PMID 32792844.
113. Panday P, Shukla N, Sisodiya D, Jain V, Mahajan S. Design and characterization of microsphere loaded controlled release epicutaneous gel of lornoxicam. *Appl Med Res.* 2015;1(1):16-21. doi: 10.5455/amr.20150127052147.
114. Janakidevi S, Ramanamurthy KV. Development of colon-targeted microsponges for the treatment of inflammatory bowel disease. *Indian J Pharm Sci.* 2018;80(4):604-9. doi: 10.4172/pharmaceutical-sciences.1000399.
115. Mohanty D, Bakshi V, Rashid MA, et al. Design and *in vitro* characterization of betamethasone microsphere loaded topical gel. *Int J Pharm Res Health Sci.* 2016;4(2):1124-9.
116. Jain V, Singh R. Design and characterization of colon-specific drug delivery system containing paracetamol microspheres. *Arch Pharm Res.* 2011; 34(5): 733-40. doi: 10.1007/s12272-011-0506-4, PMID 21656358.
117. Rajab NA, Jawad MS. Formulation and *in vitro* evaluation of piroxicam microsphere as a tablet. *Int J Pharm Pharm Sci.* 2016;8(2):104-4.
118. Kawashima Y, Niwa T, Takeuchi H, Hino T, Ito Y. Control of prolonged drug release and compression properties of ibuprofen microspheres with acrylic polymer, eudragit RS, by changing their intraparticle porosity [corrected]. *Chem Pharm Bull (Tokyo).* 1992;40(1):196-201. doi: 10.1248/cpb.40.196, PMID 1576674.
119. Shinde A, Paithane M, Sawant S. Development and evaluation of fenoprofen microsponges and its colonic delivery using natura I polysaccharides. *Am J Pharm Sci Nanotechnol.* 2014;1:27-42.
120. Rashid M, Ahmad QZ. Trends in nanotechnology for practical applications of targeted Nano drugs and delivery systems. *Elsevier;* 2019. p. 297-325. doi: 10.1016/B978-0-12-814029-1.00011-9.
121. Rajeswari S, Swapna V. Microsponges as a neoteric cornucopia for drug delivery systems. *Int J Curr Pharm Res.* 2019;11(3):4-12. doi: 10.22159/ijcpr.2019v11i3.34099.
122. Patil N, Tadavi S, Pawar S. A research on formulation and evaluation of microsphere loaded in topical gel of ritonavir. *World J Pharm Pharm Sci.* 2018;7:855-96.
123. Mahesh Kumar P, Ghosh A. Development and evaluation of metronidazole loaded microsphere based gel for superficial surgical wound infections. *J Drug Deliv Sci Technol.* 2015;30:15-29. doi: 10.1016/j.jddst.2015.09.006.
124. Hussien AA. Preparation and evaluation of oral microsphere drug delivery system of ketoconazole. *J Pharm Sci.* 2014; 14(1): 1-8. doi: 10.32947/ajps.v14i1.119.
125. Bothiraja C, Gholap AD, Shaikh KS, Pawar AP. Investigation of ethyl cellulose microsphere gel for topical delivery of eberconazole nitrate for fungal therapy. *Ther Deliv.* 2014;5(7):781-94. doi: 10.4155/tde.14.43, PMID 25287385.
126. Kumari P, Misra S, Pandey S. Formulation and evaluation of tolinaftate microsponges loaded gels for treatment of dermatophytosis. *Eur J Pharm Res.* 2017;4(06):326-35.
127. Jakhar S, Kadian V, Rao R. Dapsone-loaded microsphere gel for acne management: preparation, characterization and anti-microbial activity. *Micro Nanosyst.* 2021;13(2):211-22. doi: 10.2174/1876402912999200630130442.
128. Bargal J, Dhawale S, Landage S, Kulkarni R. Formulation and evaluation of Eudragit RS 100 Loaded microsponges of Flutrimazole. *Int J Pharm Sci Res.* 2013;4(8):3039.
129. Mehta M, Panchal A, Shah VH, Upadhyay U. Formulation and *in vitro* evaluation of controlled release microsphere gel for topical delivery of clotrimazole. *Int J Adv Pharm.* 2012;2(2):93-101.
130. Wadhwa G, Kumar S, Mittal V, Rao R. Encapsulation of babchi essential oil into microsponges: physicochemical properties, cyto-toxic evaluation and antimicrobial activity. *J Food Drug Anal.* 2019;27(1):60-70. doi: 10.1016/j.jfda.2018.07.006, PMID 30648595.
131. Hasan MN, Salman MS, Hasan MM, Kubra KT, Sheikh MC, Rehan AI, et al. Assessing sustainable lutetium (III) ions adsorption and recovery using novel composite hybrid nanomaterials. *J Mol Struct.* 2023; 1276:134795. doi: 10.1016/j.molstruc.2022.134795.
132. Awual MR. Novel ligand functionalized composite material for efficient copper (II) capturing from wastewater sample. *Compos B Eng.* 2019;172:387-96. doi: 10.1016/j.compositesb.2019.05.103.
133. Awual MR, Yaita T, Kobayashi T, Shiwaku H, Suzuki S. Improving cesium removal to clean-up the contaminated water using modified conjugate material. *J Environ Chem Eng.* 2020;8(2):103684. doi: 10.1016/j.jece.2020.103684.
134. Awual MR, Hasan MM, Rahman MM, Asiri AM. Novel composite material for selective copper (II) detection and removal from aqueous media. *J Mol Liq.* 2019;283:772-80. doi: 10.1016/j.molliq.2019.03.141.
135. Talreja N, Ashfaq M, Chauhan D, Mera AC, Rodríguez CA, Mangalaraja RV. A Zn-doped BiOI microsphere-based photocatalyst material for complete photodegradation of environmental Contaminants. *New J Chem.* 2021;45(39):18412-20. doi: 10.1039/D1NJ03415D.
136. Naushad M, Alqadami AA, Al-Kahtani AA, Ahamad T, Awual MR, Tatarchuk T. Adsorption of textile dye using para-aminobenzoic acid modified activated carbon: kinetic and equilibrium studies. *J Mol Liq.* 2019;296:112075. doi: 10.1016/j.molliq.2019.112075.
137. Kubra KT, Salman MS, Hasan MN, Islam A, Teo SH, Hasan MM, et al. Sustainable detection and capturing of cerium (III) using ligand embedded solid-state conjugate adsorbent. *J Mol Liq.* 2021;338:116667. doi: 10.1016/j.molliq.2021.116667.
138. Awual MR. Novel conjugated hybrid material for efficient lead (II) capturing from contaminated wastewater. *Mater Sci Eng C Mater Biol Appl.* 2019;101: 686-95. doi: 10.1016/j.msec.2019.04.015, PMID 31029362.
139. Trotta F, Zanetti M, Cavalli R. Cyclodextrin-based nanospheres as drug carriers. *Beilstein J Org Chem.* 2012;8(1):2091-9. doi: 10.3762/bjoc.8.235, PMID 23243470.
140. Stanley TH, Hague B. Compositions and methods of manufacture of compressed powder medicaments; 1989. p. CA1339190C.
141. Dean RC Jr, Cahn F, Phillips PG. Weighted microsphere for immobilizing bioactive material. WO1986005811A1, 1992.
142. Bhanse Najuka D, Shah C, Shah D. Novel and innovative strategy: microsponges drug delivery system. *Pharm Sci Monit* 2016;7(2):90-8.
143. Hiroshi Sakadou SK. Production of microsphere. JPS63170436A, 1988.
144. Kumar S, Tyagi L, Singh D. Microsphere Delivery System (MDS): A unique technology for delivery of active ingredients. *Int J Pharm Sci Res.* 2011;2(12):3069-80.
145. Lo RJ. Microsphere reservoirs for controlled release application; 1998:US5725869.
146. Froix M, Pukhansky M, Nacht S. Retinoid formulations in porous microspheres for reduced irritation and enhanced stability; 1998:US5851538.
147. Tomlinson R, Davey G. Percutaneous delivery system. AU723143B2, 2001.
148. Shefer A, Shefer S. Stabilized retinol for cosmetic dermatological, and pharmaceutical compositions, and use thereof. US20030232091A1; 2003.
149. Embil K. Analgesic cream comprising salicylate dispersed in silicone oil and microsphere for sustained delivery of counterirritants like menthol. WO2004014397A1, 2004.
150. Cattaneo M. Chitosan microparticles for the topical delivery of water insoluble active agents. US20040247632, 2004.
151. Embil K, Nacht S. Topical pharmaceutical and/or cosmetic dispense systems. WO2004064803A1, 2004.
152. Halliday JA, Carr DA, Boyd L, et al. Drug delivery polymer with hydrochloride salt of clindamycin. US20080160065, 2008.
153. Taylor TS, Meeks RG, Alexander JL, Stavrakas KH. Nonwoven towel with microsponges. US20080260990A1; 2008.
154. Schaffner CP, Griesinger WK. Method of removing ticks from the epidermal tissue of humans and other mammals. US7604814B2, 2009.
155. Ayala FA. Topical antiacne preparations containing retinoid (tazarotene or adapalene), antibiotic (clindamycin phosphate) and/or keratolytic (microsponged benzoyl peroxide). US20090318371A1; 2009.

156. Malek S. Topical administration carrier composition and therapeutic formulations comprising same. US7749489B2, 2010.
157. Schaffner CP, Griesinger WK. Method of removing ticks from the skin and reducing the risk of bites; 2012:US7604814.
158. Hammond PT, Lee JB, Roh YH. Nucleic acid particles, methods and use thereof. WO2014134029A1, 2014.
159. Orsoni S, Willcox N. Gel composition for once-daily treatment of common acne comprising a combination of benzoyl peroxide and adapalene and/or adapalene salt. US7820186B2, 2010.
160. Mcdaniel DH. Method and apparatus for acne treatment using low intensity light therapy. US9227082B2, 2016.
161. Kharlampieva EP, Yancey B. Biodegradable photocatalytic nanocomposite microsponges of polyactic acid; 2017. p. US9764316.
162. Dos Santos IR, Sournac M. Transdermal device including porous microparticles. WO2013127929A1, 2018.
163. Tamarkin D, Gazal E, Hazot Y, Schuz D, Papiashvili I. Compositions, gels and foams with rheology modulators and uses. US20190240239A1; 2019.
164. Tamarkin D, Gazal E, Hazot Y, Schuz D, Papiashvili I. Compositions, gels and foams with rheology modulators and uses thereof. US10835613B2, 2020.
165. Caso MF, Carotenuto F, Di Nardo P, Migliore A, Aguilera A, Lopez CM, *et al.* Nanoporous microsphere particles (NMP) of polysaccharides as universal carriers for biomolecules delivery. *Nanomaterials* (Basel). 2020;10(6):1075. doi: 10.3390/nano10061075, PMID 32486448.
166. Dr. Deshmukh R, *et al.* Mesalamine loaded microsponges formulation, 202211031794; 2022.
167. Rathi R, *et al.* A topical gel formulation comprising microsponges of basil oil and process of preparation thereof, 202211024801; 2022.
168. Jagtap KS, *et al.* Microsponges drug delivery system of polyherbal drug for hepatoprotective disorder, 202211023987; 2022.
169. Pal N, Mandal S, Shiva K, Kumar B. Pharmacognostical, phytochemical and pharmacological evaluation of *Mallotus philippensis*. *J Drug Deliv Ther*. 2022;12(5):175-81. doi: 10.22270/jddt.v12i5.5675.
170. Singh A, Ajwain MS (*Trachyspermum ammi* Linn): A review on Tremendous Herbal Plant with Various Pharmacological Activity. *Int J Recent Adv Multidiscip Top*. 2021;2(6):36-8.
171. Mandal S, Jaiswal V, Sagar MK, Kumar S. Formulation and evaluation of *Carica papaya* nanoemulsion for treatment of dengue and thrombocytopenia. *Plant Arch*. 2021;21:1345-54.
172. Mandal S, Shiva K, Kumar KP, Goel S, Patel RK, Sharma S, *et al.* Ocular drug delivery system (ODDS): exploration the challenges and approaches to improve ODDS. *J Pharm Biol Sci*. 2021;9(2):88-94. doi: 10.18231/j.jpbs.2021.012.
173. Ali SA, Pathak D, Mandal S. A review of current knowledge on airborne transmission of COVID-19 and their relationship with environment. *Int J Pharm Prof's Res (IJPPR)*. 2023;14(1):1-5.
174. Shiva K, Mandal S, Kumar S. Formulation and evaluation of topical antifungal gel of fluconazole using aloe vera gel. *Int J Sci Res Develop*. 2021;1:187-93.
175. Vishvakarma P, Mandal S, Verma A. A review on current aspects of nutraceuticals and dietary supplements. *Int J Pharm Prof's Res (IJPPR)*. 2023;14(1):78-91.
176. Ali S, Farooqui NA, Ahmad S, Salman M, Mandal S, ROSEUS C (SADABAHAR). A brief study on medicinal plant having different pharmacological activities. *Plant Arch*. 2021;21(2):556-9.
177. Mandal S, Jaiswal DV, Shiva K. A review on marketed *Carica papaya* leaf extract (CPLE) supplements for the treatment of dengue fever with thrombocytopenia and its drawback. *Int J Pharm Res*. 2020;12(3).
178. Mandal S, Vishvakarma P, Verma M, Alam MS, Agrawal A, Mishra A. *Solanum nigrum* Linn: an Analysis of the Medicinal Properties of the Plant. *J Pharm Neg Results*. 2023;1595-600.
179. Vishvakarma P, Mandal S, Pandey J, Bhatt AK, Banerjee VB, Gupta JK. An analysis of the most recent trends in flavoring herbal medicines in today's market. *J Pharm Neg Results*. 2022;9189-98.
180. Mandal S, Pathak D, Rajput K, Khan S, Shiva K. Thrombophob-induced acute urticaria: a case report and discussion of the case. *Int J Pharm Prof's Res (IJPPR)*. 2022;13(4):1-4.
181. Mandal S, Shiva K, Yadav R, Sen J, Kori R. Leiomyosarcoma: a case report on the preoperative diagnostic criteria. *Int J Pharm Prof's Res (IJPPR)*. 2022;13(4):1-4.
182. Mandal S, Vishvakarma P, Mandal S. Future aspects and applications of Nanoemulgel formulation for topical lipophilic drug delivery. *Eur J Mol Clin Med*. 2023;10(01):2023.
183. Chawla A, Mandal S, Vishvakarma P, Nile NP, Lokhande VN, Kakad VK, *et al.* Ultrapformance liquid chromatography (Uplc).
184. Mandal S, Raju D, Namdeo P, Patel A, Bhatt AK, Gupta JK, *et al.* Development, characterization, and evaluation of *Rosa alba* L extract-loaded phytosomes.
185. Mandal S, Goel S, Saxena M, Gupta P, Kumari J, Kumar P, *et al.* Screening of *Catharanthus roseus* stem extract for anti-ulcer potential in Wistar rat. *ijhs*:2138-70. doi: 10.53730/ijhs.v6nS9.12889.
186. Shiva K, Kaushik A, Irshad M, Sharma G, Mandal S. Evaluation and preparation: herbal gel containing *Thuja occidentalis* and *Curcuma longa* extracts.
187. Vishvakarma P, Mohapatra L, Kumar NN, Mandal S, Mandal S. An innovative approach on microemulsion: a review.

Cite this article: Mandal S, Bhumika K, Kumar M, Hak J, Vishvakarma P, Sharma UK. A Novel Approach on Micro Sponges Drug Delivery System: Method of Preparations, Application, and its Future Prospective. *Indian J of Pharmaceutical Education and Research*. 2024;58(1):45-63.