Protective Coatings

Product / Application	BIS	ISO	ASTM	DIN	Other Standards(SSPC,AMPP, REACH, FDA)
Anti-Corrosive Coating	IS 14182	ISO 12944 (Corrosion Protection); ISO 8501 (Surface Preparation); ISO 9227 (Salt Spray); ISO 4628 Series,ISO 15013; ISO 2808	ASTM B117 (Salt Spray Corrosion Testing); ASTM D610 (Evaluation of Degree of Rusting); ASTM D714 (Evaluation of Blistering); ASTM D1654 (Evaluation of Painted or Coated Specimens Subjected to Corrosive Environments); ASTM D7091 (Non-Destructive Measurement of Dry Film Thickness); ASTM D4541 (Pull-Off Strength of Coatings),ASTM D4060; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 12944 Series (Corrosion Protection by Protective Paint Systems); DIN EN ISO 9227 (Salt Spray); DIN EN ISO 4628 Series (Rust, Blistering, Cracking Evaluation); DIN EN ISO 2409 (Adhesion); DIN EN ISO 4624 (Pull-Off Adhesion); DIN EN ISO 8501-1 (Preparation Grades)	AMPP: SP 1; AMPP: SP 5/NACE No.1; AMPP: SP 6/NACE No.3; AMPP: SP 10/NACE No.2; AMPP coating system requirements; REACH: Regulation (EC) No. 1907/2006 (anticorrosive pigments, heavy metals, solvents)
Zinc Rich Protective Coating	IS 14589:1999; IS 14182	ISO 12944 (Corrosion Protection); ISO 8501 (Surface Preparation); ISO 9227 (Salt Spray Testing); ISO 2808 (Film Thickness),ISO 15013	ASTM D520 (Zinc Dust Pigment Specification); ASTM B117 (Salt Spray); ASTM D1654 (Corrosion Evaluation); ASTM D610 (Rust Rating); ASTM D7091 (Dry Film Thickness); ASTM D4541 (Adhesion Strength),ASTM D4060; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 12944-5 (Protective Paint Systems); DIN EN ISO 12944-6 (Laboratory Performance Testing); DIN EN ISO 9227 (Salt Spray); DIN EN ISO 2808 (Dry Film Thickness); DIN EN ISO 2409 (Adhesion); DIN EN ISO 4628 Series (Corrosion Evaluation)	AMPP: SP 5/NACE No.1; AMPP: SP 6/NACE No.3; AMPP: SP 10/NACE No.2; AMPP Paint 20 (Zinc-Rich Primers); REACH: Regulation (EC) No. 1907/2006 (zinc compounds, restricted substances)
Epoxy Protective Coating	IS 14182	ISO 12944 (Protective Paint Systems); ISO 9227 (Salt Spray); ISO 4624 (Pull-Off Adhesion); ISO 2812 Series (Chemical Resistance),ISO 15013; ISO 2808	ASTM D5144 (Guide for Use of Protective Coating Systems); ASTM D4541 (Pull-Off Adhesion); ASTM B117 (Salt Spray); ASTM D4060 (Abrasion Resistance); ASTM D1308 (Chemical Resistance); ASTM D5162 (Discontinuity/Holiday Testing),ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 12944 Series; DIN EN ISO 4624 (Pull-Off Adhesion); DIN EN ISO 2812 Series (Resistance to Liquids); DIN EN ISO 9227 (Salt Spray); DIN EN ISO 7784 Series (Abrasion Resistance); DIN EN ISO 8501 Series (Surface Preparation)	AMPP: SP 1; AMPP: SP 5/NACE No.1; AMPP: SP 6/NACE No.3; AMPP: SP 10/NACE No.2; REACH: Regulation (EC) No. 1907/2006 (epoxy resins, curing agents, VOC, SVHC)
Polyurethane Protective Coating	IS 16719:2022 (for steel pipe exteriors); IS 14182	ISO 12944 (Corrosion Protection); ISO 11507 (Weathering); ISO 4624 (Adhesion); ISO 2813 (Gloss),ISO 15013; ISO 2808	ASTM D4541 (Pull-Off Adhesion); ASTM D4060 (Abrasion Resistance); ASTM G154 (UV Weathering); ASTM G155 (Xenon Arc Weathering); ASTM D1308 (Chemical Resistance); ASTM B117 (Corrosion Resistance),ASTM D7091; ASTM G14; ASTM G20	DIN EN ISO 12944 Series; DIN EN ISO 2409 (Adhesion); DIN EN ISO 4624 (Pull-Off Strength); DIN EN ISO 16474 (Artificial Weathering); DIN EN ISO 2812 (Chemical Resistance); DIN EN ISO 9227 (Corrosion Resistance)	AMPP: SP 1; AMPP: SP 6/NACE No.3; AMPP: SP 10/NACE No.2; REACH: Regulation (EC) No. 1907/2006 (isocyanates, solvents, additives); REACH Annex XVII (diisocyanates)
Fusion Bonded Epoxy (FBE) Coating	IS 14182	ISO 21809-1 (External Pipeline Coatings); ISO 8501 (Surface Preparation); ISO 4624 (Adhesion); ISO 21809-2 (Fusion Bonded Epoxy Qualification),ISO 15013; ISO 2808	ASTM A775/A775M (Fusion Bonded Epoxy Coated Steel Reinforcing Bars where applicable); ASTM D7091 (Dry Film Thickness); ASTM G62 (Holiday Detection of Pipeline Coatings); ASTM D4541 (Adhesion); ASTM B117 (Salt Spray); ASTM D3359 (Adhesion),ASTM D4060; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 21809 Series (External Coatings for Pipeline Transport Systems); DIN EN ISO 12944 Series (Corrosion Protection); DIN EN ISO 4624 (Adhesion); DIN EN ISO 2808 (Coating Thickness); DIN EN ISO 8501-1 (Surface Preparation); DIN EN ISO 21809-1 (Polyolefin and FBE Pipeline Coatings)	AMPP: SP 10/NACE No.2 (Near White Blast Cleaning); AMPP: SP 5/NACE No.1; AMPP pipeline coating practices; REACH: Regulation (EC) No. 1907/2006 (epoxy resins, curing agents, additives)
Coal Tar Epoxy Coating	IS 14182	ISO 12944 (Protective Coating Systems); ISO 2812 Series (Chemical Resistance); ISO 9227 (Salt Spray Testing),ISO 15013; ISO 2808	ASTM D714 (Blister Evaluation); ASTM D610 (Rust Evaluation); ASTM B117 (Salt Spray); ASTM D4541 (Adhesion); ASTM D5162 (Electrical Discontinuity Testing of Protective Coatings),ASTM	DIN EN ISO 12944 Series; DIN EN ISO 9227 (Salt Spray); DIN EN ISO 4628 (Blister/Rust Evaluation); DIN EN ISO 2409 (Adhesion); DIN EN ISO 2812 (Chemical Resistance)	AMPP: SP 1; AMPP: SP 5/NACE No.1; AMPP: SP 6/NACE No.3; AMPP: SP 10/NACE No.2; REACH: Regulation (EC) No. 1907/2006 (coal tar substances, PAHs, restricted

Product / Application	BIS	ISO	ASTM	DIN	Other Standards(SSPC,AMPP, REACH, FDA)
			D4060; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20		chemicals)
Intumescent Fire Protection Coating	IS 14182	ISO 834 (Fire Resistance Testing); ISO 1182 (Non-Combustibility); ISO 1716 (Heat Release); ISO 12944 where corrosion protection is required,ISO 15013; ISO 2808	ASTM E84 (Surface Burning Characteristics); ASTM E119 (Fire Resistance Tests of Building Construction Materials); ASTM E605 (Thickness and Density of Sprayed Fire-Resistive Materials); ASTM E736 (Cohesion/Adhesion of Fire-Resistive Materials); ASTM E2924 (Application of Fire-Resistive Materials); ASTM E937 (Corrosion Resistance of Steel Components),ASTM B117; ASTM D4060; ASTM D4541; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN 4102 Series (Fire Behaviour of Building Materials); DIN EN 13501-1 (Fire Classification); DIN EN 13381-8 (Fire Resistance Contribution of Reactive Protection Applied to Steel Members); DIN EN ISO 11925-2 (Ignitability); DIN EN 13823 (Single Burning Item Test)	AMPP: SP 6/NACE No.3; AMPP: SP 10/NACE No.2 for steel structures; REACH: Regulation (EC) No. 1907/2006 (flame retardants, additives, SVHC substances)
Fire Resistant Coating	IS 14182	ISO 834 (Fire Resistance); ISO 1182 (Non-Combustibility); ISO 1716 (Heat Release),ISO 15013; ISO 2808	ASTM E84 (Surface Burning Characteristics); ASTM E119 (Fire Resistance); ASTM E162 (Surface Flammability of Materials Using Radiant Heat Energy Source); ASTM E662 (Smoke Density); ASTM D3806 (Small-Scale Evaluation of Intumescent Coatings where applicable),ASTM B117; ASTM D4060; ASTM D4541; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN 4102 Series (Fire Behaviour); DIN EN 13501 Series (Reaction to Fire Classification); DIN EN ISO 11925-2 (Ignitability); DIN EN 13823 (SBI Test); DIN EN ISO 1716 (Heat of Combustion)	REACH: Regulation (EC) No. 1907/2006 (flame retardants, binders, additives); AMPP: surface preparation standards where applied as protective steel coating
Marine Protective Coating	IS 14182	ISO 12944 (Corrosion Protection); ISO 20340 (Performance Requirements for Offshore Protective Paint Systems); ISO 9227 (Salt Spray),ISO 15013; ISO 2808	ASTM B117 (Salt Spray); ASTM D5894 (Cyclic Salt Fog/UV Exposure); ASTM D610 (Rust Evaluation); ASTM D714 (Blister Evaluation); ASTM D4541 (Pull-Off Adhesion); ASTM D5162 (Holiday Detection),ASTM D4060; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 12944 Series; DIN EN ISO 9227 (Salt Spray); DIN EN ISO 4628 Series (Coating Failure Evaluation); DIN EN ISO 2409 (Adhesion); DIN EN ISO 2812 (Chemical Resistance); DIN EN ISO 16474 (Weathering)	AMPP: SP 1; AMPP: SP 5/NACE No.1; AMPP: SP 6/NACE No.3; AMPP: SP 10/NACE No.2; REACH: Regulation (EC) No. 1907/2006 (biocides, antifouling substances, VOC)
Offshore Protective Coating	IS 14182	ISO 20340 (Offshore Protective Coating Systems); ISO 12944 (Corrosion Protection); ISO 8501 (Surface Preparation),ISO 15013; ISO 2808	ASTM B117 (Salt Spray); ASTM D5894 (Cyclic Corrosion/Weathering); ASTM D1654 (Corrosion Evaluation); ASTM D4541 (Adhesion); ASTM D610 (Rust Rating); ASTM D714 (Blister Rating),ASTM D4060; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 12944-9 (Offshore and Related Structures); DIN EN ISO 9227 (Salt Spray); DIN EN ISO 12944-6 (Performance Testing); DIN EN ISO 4628 Series; DIN EN ISO 2409	AMPP: SP 5/NACE No.1; AMPP: SP 10/NACE No.2; AMPP offshore coating practices; REACH: Regulation (EC) No. 1907/2006 (anticorrosive pigments, solvents, additives)
Pipeline Coating	IS 10221,IS 14182	ISO 21809 Series (Petroleum and Natural Gas Pipeline Coatings); ISO 8501 (Surface Preparation); ISO 12944 (Protective Coating Systems),ISO 15013; ISO 2808	ASTM G62 (Holiday Detection of Pipeline Coatings); ASTM D7091 (Dry Film Thickness); ASTM D4541 (Pull-Off Adhesion); ASTM D3359 (Adhesion); ASTM B117 (Salt Spray); ASTM D5162 (Discontinuity Testing),ASTM D4060; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 21809 Series (Pipeline Coatings); DIN EN ISO 12944 Series; DIN EN ISO 2808 (Thickness Measurement); DIN EN ISO 4624 (Adhesion); DIN EN ISO 21809-3 (Field Joint Coatings); DIN EN ISO 8501 Series (Surface Preparation)	AMPP: SP 5/NACE No.1; AMPP: SP 10/NACE No.2; AMPP pipeline coating requirements; REACH: Regulation (EC) No. 1907/2006 (epoxy systems, additives, restricted substances)
Tank Lining Coating	IS 14182	ISO 2812 Series (Resistance to Liquids); ISO 4624 (Pull-Off Adhesion); ISO 12944 (Protective Coatings),ISO 15013; ISO 2808	ASTM D5162 (Electrical Discontinuity Testing of Protective Coatings); ASTM D4541 (Adhesion); ASTM D1308 (Chemical Resistance); ASTM B117	DIN EN ISO 12944 Series; DIN EN ISO 2812 Series (Liquid Resistance); DIN EN ISO 4624 (Adhesion); DIN EN ISO 5162 (Discontinuity/Holiday	AMPP: SP 5/NACE No.1; AMPP: SP 10/NACE No.2; AMPP: SP 11; REACH: Regulation (EC) No. 1907/2006 (epoxy, phenolic, chemical-resistant

Product / Application	BIS	ISO	ASTM	DIN	Other Standards(SSPC,AMPP, REACH, FDA)
			(Corrosion Resistance); ASTM D4060 (Abrasion Resistance),ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	Detection where applicable); DIN EN ISO 8501 Series	systems); FDA: 21 CFR 175.300 where food-contact tank lining is required
Concrete Protection Coating	IS 14182	ISO 4624 (Pull-Off Adhesion); ISO 1062 Series (Coating Performance for Concrete); ISO 6270 (Humidity Resistance),ISO 15013; ISO 2808	ASTM C1583 (Tensile Strength of Concrete Surfaces); ASTM D7234 (Pull-Off Adhesion Strength of Coatings on Concrete); ASTM D4541 (Adhesion); ASTM D1308 (Chemical Resistance); ASTM D4259 (Preparation of Concrete Surfaces),ASTM B117; ASTM D4060; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN 1504-2 (Products and Systems for Protection and Repair of Concrete Structures); DIN EN 1542 (Adhesion by Pull-Off); DIN EN ISO 4624 (Pull-Off Strength); DIN EN ISO 7783 (Water Vapour Transmission); DIN EN 1062 Series (Coating Materials for Mineral Substrates)	AMPP: SP 13/NACE No.6 (Surface Preparation of Concrete); REACH: Regulation (EC) No. 1907/2006 (epoxy, acrylic, PU systems)
Bridge Protective Coating	IS 14182	ISO 12944 (Corrosion Protection of Steel Structures); ISO 8501 (Surface Preparation); ISO 9227 (Salt Spray Testing),ISO 15013; ISO 2808	ASTM B117 (Salt Spray); ASTM D610 (Rust Evaluation); ASTM D714 (Blister Evaluation); ASTM D4541 (Adhesion); ASTM D5894 (Cyclic Corrosion and UV Exposure); ASTM D7091 (Thickness Measurement),ASTM D4060; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 12944 Series; DIN EN ISO 9227 (Salt Spray); DIN EN ISO 4628 Series; DIN EN ISO 2409 (Adhesion); DIN EN ISO 4624 (Pull-Off Adhesion); DIN EN ISO 2808 (Thickness)	AMPP: SP 1; AMPP: SP 5/NACE No.1; AMPP: SP 6/NACE No.3; AMPP: SP 10/NACE No.2; REACH: Regulation (EC) No. 1907/2006
Industrial Floor Coating	IS 14182	ISO 4624 (Adhesion); ISO 7784 Series (Abrasion Resistance); ISO 2813 (Gloss),ISO 15013; ISO 2808	ASTM D4060 (Abrasion Resistance); ASTM D4541 (Pull-Off Adhesion); ASTM D2047 (Slip Resistance); ASTM D4259 (Surface Preparation of Concrete); ASTM C1583 (Concrete Surface Tensile Strength); ASTM D1308 (Chemical Resistance),ASTM B117; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN 1504-2 (Concrete Surface Protection); DIN EN ISO 7784 Series (Abrasion Resistance); DIN EN ISO 4624 (Adhesion); DIN 51130 (Slip Resistance); DIN EN ISO 2812 (Chemical Resistance); DIN EN ISO 2409	AMPP: SP 13/NACE No.6 (Concrete Surface Preparation); REACH: Regulation (EC) No. 1907/2006 (epoxy, PU resins, VOC, additives)
Chemical Tank Coating	IS 14182	ISO 2812 Series (Chemical Resistance); ISO 4624 (Adhesion); ISO 12944 (Protective Coatings),ISO 15013; ISO 2808	ASTM D1308 (Chemical Resistance); ASTM D543 (Chemical Resistance of Plastics where applicable); ASTM D5162 (Holiday Detection); ASTM D4541 (Adhesion); ASTM B117 (Corrosion Resistance),ASTM D4060; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 2812 Series (Resistance to Liquids); DIN EN ISO 12944 Series; DIN EN ISO 4624 (Adhesion); DIN EN ISO 9227 (Corrosion); DIN EN ISO 2409	AMPP: SP 5/NACE No.1; AMPP: SP 10/NACE No.2; REACH: Regulation (EC) No. 1907/2006 (chemical-resistant resins, additives)
Waterproof Protective Coating	IS 14182	ISO 6270 (Humidity Resistance); ISO 12944 (Protective Coating Systems); ISO 4624 (Adhesion),ISO 15013; ISO 2808	ASTM D6083 (Liquid Applied Acrylic Coating for Roof Applications); ASTM D870 (Water Immersion Resistance); ASTM D2247 (Water Resistance at 100% Relative Humidity); ASTM D4541 (Adhesion); ASTM D4060 (Abrasion Resistance),ASTM B117; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN 1504-2 (Concrete Protection Systems); DIN EN ISO 7783 (Water Vapour Transmission); DIN EN ISO 1062 Series (Coatings for Mineral Substrates); DIN EN ISO 4624 (Adhesion); DIN EN ISO 2409	AMPP: SP 13/NACE No.6 where applied on concrete; REACH: Regulation (EC) No. 1907/2006 (waterproofing polymers, additives)
UV Protective Coating	IS 14182	ISO 11507 (Artificial Weathering); ISO 16474 Series (Artificial Radiation Exposure); ISO 4628 Series,ISO 15013; ISO 2808	ASTM G154 (Fluorescent UV Exposure); ASTM G155 (Xenon Arc Exposure); ASTM D4587 (UV Condensation Weathering); ASTM D2244 (Colour Change); ASTM D523 (Gloss Retention),ASTM B117; ASTM D4060; ASTM D4541; ASTM D7091; ASTM G14; ASTM G20	DIN EN ISO 16474 Series (Artificial Weathering); DIN EN ISO 4892 Series (UV Exposure); DIN EN ISO 2813 (Gloss Retention); DIN EN ISO 4628 Series (Degradation); DIN EN ISO 2409	REACH: Regulation (EC) No. 1907/2006 (UV absorbers, stabilisers, additives); AMPP where used in protective coating systems

Product / Application	BIS	ISO	ASTM	DIN	Other Standards(SSPC,AMPP, REACH, FDA)
Heat Resistant Protective Coating	IS 14182	ISO 12944 (Protective Coatings); ISO 2813 (Gloss); ISO 4628 Series,ISO 15013; ISO 2808	ASTM D2485 (Resistance to Heat of Coatings); ASTM D3359 (Adhesion); ASTM D4541 (Pull-Off Strength); ASTM D4060 (Abrasion Resistance),ASTM B117; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 3248 (Heat Resistance of Coatings); DIN EN ISO 2409 (Adhesion); DIN EN ISO 2812 (Chemical Resistance); DIN EN ISO 15184 (Hardness)	AMPP: SP 1; AMPP: SP 6/NACE No.3; REACH: Regulation (EC) No. 1907/2006 (heat-resistant binders, pigments, additives)
Wear Resistant Coating	IS 14182	ISO 7784 Series (Abrasion Resistance); ISO 20566 (Scratch Resistance); ISO 2808 (Film Thickness),ISO 15013	ASTM D4060 (Abrasion Resistance by Taber Abraser); ASTM D1044 (Abrasion Resistance of Transparent Plastics where applicable); ASTM D3359 (Adhesion); ASTM D4541 (Pull-Off Strength),ASTM B117; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 7784 Series (Abrasion Resistance); DIN EN ISO 5470-1 (Abrasion Testing of Rubber/Plastic Materials); DIN EN ISO 2409 (Adhesion); DIN EN ISO 4624 (Pull-Off Strength)	AMPP: SP 1; AMPP: SP 6/NACE No.3; REACH: Regulation (EC) No. 1907/2006 (ceramic fillers, resins, additives)
Abrasion Resistant Coating	IS 14182	ISO 7784 Series (Abrasion Resistance); ISO 2808 (Film Thickness); ISO 2409 (Adhesion),ISO 15013	ASTM D4060 (Abrasion Resistance by Taber Abraser); ASTM D1044 (Abrasion Resistance of Transparent Plastics where applicable); ASTM D3359 (Adhesion),ASTM B117; ASTM D4541; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 7784 series (Abrasion Resistance of Coatings); DIN EN ISO 5470-1 (Rubber/Plastic Abrasion where applicable); DIN EN ISO 2409 (Adhesion)	AMPP: SP 1; AMPP: SP 6/NACE No.3 where applied on industrial substrates; REACH: Regulation (EC) No. 1907/2006 (fillers, resins, additives)
High Build Protective Coating	IS 14182	ISO 2808 (Film Thickness); ISO 12944 (Protective Coating Systems); ISO 4624 (Adhesion),ISO 15013	ASTM D7091 (Dry Film Thickness); ASTM D4541 (Pull-Off Adhesion); ASTM D4060 (Abrasion Resistance); ASTM B117 (Salt Spray); ASTM D5162 (Holiday Detection),ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN ISO 2808 (Dry Film Thickness); DIN EN ISO 4624 (Pull-Off Adhesion); DIN EN ISO 12944 Series; DIN EN ISO 9227 (Salt Spray); DIN EN ISO 5162 (Holiday Detection)	AMPP: SP 5/NACE No.1; AMPP: SP 6/NACE No.3; AMPP: SP 10/NACE No.2; REACH: Regulation (EC) No. 1907/2006
Protective Powder Coating	IS 14182	ISO 8130 Series (Coating Powders); ISO 12944 (Corrosion Protection); ISO 2409 (Adhesion),ISO 15013; ISO 2808	ASTM D3451 (Testing of Coating Powders); ASTM D5965 (Testing Powder Coatings); ASTM D3359 (Adhesion); ASTM D2794 (Impact Resistance); ASTM D4060 (Abrasion Resistance); ASTM G154 (Weathering),ASTM B117; ASTM D4541; ASTM D7091; ASTM G14; ASTM G155; ASTM G20	DIN EN ISO 8130 Series (Coating Powders); DIN EN ISO 12944 Series; DIN EN ISO 2409 (Adhesion); DIN EN ISO 2813 (Gloss); DIN EN ISO 6272 (Impact Resistance); DIN EN ISO 16474 (Weathering)	AMPP: SP 1; AMPP: SP 6/NACE No.3; REACH: Regulation (EC) No. 1907/2006 (powder resins, pigments, additives)
Anti-Carbonation Coating	IS 14182	ISO 1062 Series (Coatings for Concrete Protection); ISO 4624 (Adhesion); ISO 6270 (Humidity Resistance),ISO 15013; ISO 2808	ASTM D4541 (Adhesion); ASTM D1308 (Chemical Resistance); ASTM E96 (Water Vapour Transmission); ASTM D1653 (Water Vapour Transmission of Organic Coating Films); ASTM C1585 (Surface Absorption where applicable),ASTM B117; ASTM D4060; ASTM D7091; ASTM G14; ASTM G154; ASTM G155; ASTM G20	DIN EN 1504-2 (Concrete Protection); DIN EN ISO 7783 (Water Vapour Transmission); DIN EN ISO 1062-6 (Carbon Dioxide Permeability); DIN EN ISO 4624 (Adhesion); DIN EN 1542 (Pull-Off Strength)	AMPP: SP 13/NACE No.6 (Concrete Preparation); REACH: Regulation (EC) No. 1907/2006 (polymer binders, additives)
Protective Elastomeric Coating	IS 14182	ISO 12944 (Protective Coating Systems); ISO 4624 (Adhesion); ISO 11507 (Weathering Resistance),ISO 15013; ISO 2808	ASTM D2370 (Tensile Properties of Organic Coatings); ASTM D6083 (Liquid Applied Acrylic Coating); ASTM D412 (Rubber Tensile Properties where elastomeric materials apply); ASTM D4541 (Adhesion); ASTM D4060 (Abrasion Resistance); ASTM G154 (UV Weathering),ASTM B117; ASTM D7091; ASTM G14; ASTM G155; ASTM G20	DIN EN ISO 527 Series (Tensile Properties); DIN EN ISO 7784 Series (Abrasion Resistance); DIN EN ISO 2409 (Adhesion); DIN EN ISO 16474 (Weathering); DIN EN ISO 4624 (Pull-Off Adhesion); DIN EN ISO 1062 Series (Coating Performance on Mineral Substrates)	AMPP: SP 13/NACE No.6 for concrete applications; REACH: Regulation (EC) No. 1907/2006 (elastomers, plasticisers, additives)

Source field: Dyes and Pigments