Varnishes

Product / Application	BIS	ISO	ASTM	DIN	Other Standards(SSPC,AMPP, REACH, FDA)
Clear Varnish	IS 346 – Spirit Varnish, Clear, Hard — SpecificationIS 337; IS 524	ISO 2813 (Gloss); ISO 2409 (Adhesion); ISO 2808 (Film Thickness),ISO 1524; ISO 3251	ASTM D523 (Gloss); ASTM D3359 (Adhesion); ASTM D3363 (Hardness); ASTM D4060 (Abrasion Resistance),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752	DIN EN ISO 2409 (Cross-Cut Adhesion); DIN EN ISO 2813 (Gloss); DIN EN ISO 15184 (Pencil Hardness); DIN EN ISO 2808 (Dry Film Thickness); DIN EN ISO 11998 (Wet Scrub Resistance where applicable)	REACH: Regulation (EC) No. 1907/2006 (solvents, resins, additives, VOC)
Polyurethane Varnish	IS 337; IS 524	ISO 12944 (Protective Coatings); ISO 2813 (Gloss); ISO 11507 (Weathering Resistance); ISO 2409 (Adhesion),ISO 1524; ISO 3251	ASTM D523 (Gloss); ASTM D3363 (Hardness); ASTM D4060 (Abrasion Resistance); ASTM G154 (Weathering Resistance); ASTM D3359 (Adhesion),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752	DIN EN ISO 2813 (Gloss); DIN EN ISO 2409 (Adhesion); DIN EN ISO 15184 (Hardness); DIN EN ISO 6272 (Impact Resistance); DIN EN ISO 16474 (Artificial Weathering); DIN EN ISO 4628 series (Coating Degradation)	REACH: Regulation (EC) No. 1907/2006 (isocyanates, solvents, additives); REACH Annex XVII (diisocyanates restrictions where applicable)
Acrylic Varnish	IS 337; IS 524	ISO 2813 (Gloss); ISO 2409 (Adhesion); ISO 11507 (Weathering Resistance),ISO 1524; ISO 3251	ASTM D523 (Gloss); ASTM D2244 (Colour Change); ASTM G154 (Weathering); ASTM D3359 (Adhesion),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752	DIN EN ISO 2409 (Adhesion); DIN EN ISO 2813 (Gloss); DIN EN ISO 16474 (Weathering); DIN EN ISO 4628 (Degradation Evaluation); DIN EN ISO 15184 (Hardness)	REACH: Regulation (EC) No. 1907/2006 (acrylate polymers, VOC, additives)
Alkyd Varnish	IS 337; IS 524	ISO 2813 (Gloss); ISO 2409 (Adhesion); ISO 2808 (Film Thickness),ISO 1524; ISO 3251	ASTM D523 (Gloss); ASTM D5895 (Drying Time); ASTM D3359 (Adhesion); ASTM D4060 (Abrasion Resistance),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752	DIN EN ISO 2409 (Adhesion); DIN EN ISO 2813 (Gloss); DIN EN ISO 15184 (Hardness); DIN EN ISO 9117 series (Drying Tests); DIN EN ISO 6272 (Impact Resistance)	REACH: Regulation (EC) No. 1907/2006 (alkyd resins, solvents, drying agents)
Spar Varnish	IS 337; IS 524	ISO 11507 (Weathering Resistance); ISO 2813 (Gloss); ISO 2409 (Adhesion),ISO 1524; ISO 3251	ASTM G154 (UV Weathering); ASTM D523 (Gloss); ASTM D3359 (Adhesion); ASTM D4446 (Water Repellency for Wood Applications),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752	DIN EN 927 series (Coating Materials and Coating Systems for Exterior Wood); DIN EN ISO 16474 (Weathering); DIN EN ISO 2409 (Adhesion); DIN EN ISO 2813 (Gloss); DIN EN ISO 4628 (Coating Defects)	REACH: Regulation (EC) No. 1907/2006 (resins, solvents, UV stabilisers)
Marine Varnish	IS 337; IS 524	ISO 12944 (Corrosion Protection); ISO 20340 (Offshore Protective Coating Performance); ISO 9227 (Salt Spray),ISO 1524; ISO 3251	ASTM B117 (Salt Spray where applicable); ASTM G154 (Weathering); ASTM D523 (Gloss); ASTM D3359 (Adhesion),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752	DIN EN ISO 12944 series (Corrosion Protection); DIN EN ISO 9227 (Salt Spray); DIN EN ISO 4628 series (Rust/Blister Evaluation); DIN EN ISO 2409 (Adhesion); DIN EN ISO 16474 (Weathering)	AMPP: SP 1; AMPP: SP 6/NACE No.3 where applied on metallic substrates; REACH: Regulation (EC) No. 1907/2006 (marine-use additives, solvents, UV stabilisers)
Wood Varnish	IS 337; IS 524	ISO 2409 (Adhesion); ISO 2813 (Gloss); ISO 11507 (Weathering Resistance),ISO 1524; ISO 3251	ASTM D3023 (Coatings Applied to Wood); ASTM D4446 (Water Repellency); ASTM D523 (Gloss); ASTM D3359 (Adhesion),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752	DIN EN 927 series (Exterior Wood Coatings); DIN EN ISO 2409 (Adhesion); DIN EN ISO 2813 (Gloss); DIN EN ISO 4628 (Coating Failure Evaluation); DIN EN ISO 7783 (Water Vapour Transmission)	REACH: Regulation (EC) No. 1907/2006 (solvents, preservatives, additives)
Floor Varnish	IS 337; IS 524	ISO 7784 Series (Abrasion Resistance); ISO 4624 (Adhesion); ISO 2813 (Gloss),ISO 1524; ISO 3251	ASTM D4060 (Abrasion Resistance); ASTM D2047 (Slip Resistance); ASTM D4541 (Adhesion); ASTM D523 (Gloss),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752	DIN EN ISO 7784 series (Abrasion Resistance of Coatings); DIN EN ISO 2409 (Adhesion); DIN 51130 (Slip Resistance of Flooring); DIN EN ISO 2813 (Gloss); DIN EN ISO	REACH: Regulation (EC) No. 1907/2006 (resins, VOC, abrasion additives)

Product / Application	BIS	ISO	ASTM	DIN	Other Standards(SSPC,AMPP, REACH, FDA)
				6272 (Impact Resistance)	
Exterior Varnish	IS 337; IS 524	ISO 11507 (Artificial Weathering); ISO 16474 (Artificial Radiation); ISO 4628 Series,ISO 1524; ISO 3251	ASTM G154 (UV Exposure); ASTM G155 (Xenon Arc); ASTM D2244 (Colour Change); ASTM D523 (Gloss Retention),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752	DIN EN 927 series (Exterior Wood Coating Systems); DIN EN ISO 16474 (Artificial Weathering); DIN EN ISO 4892 (UV Exposure); DIN EN ISO 4628 (Coating Degradation); DIN EN ISO 2409 (Adhesion)	REACH: Regulation (EC) No. 1907/2006 (UV stabilisers, biocides, VOC, additives)
Interior Varnish	IS 337; IS 524	ISO 2813 (Gloss); ISO 2409 (Adhesion); ISO 2808 (Film Thickness),ISO 1524; ISO 3251	ASTM D523 (Gloss); ASTM D3363 (Hardness); ASTM D3359 (Adhesion),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752	DIN EN ISO 2409 (Adhesion); DIN EN ISO 2813 (Gloss); DIN EN ISO 15184 (Hardness); DIN EN ISO 2808 (Thickness)	REACH: Regulation (EC) No. 1907/2006 (VOC, solvents, resins)
UV Resistant Varnish	IS 337; IS 524	ISO 11507 (Artificial Weathering); ISO 16474 (Artificial Radiation); ISO 2813,ISO 1524; ISO 3251	ASTM G154 (UV Weathering); ASTM G155 (Xenon Arc Weathering); ASTM D4587 (UV Condensation); ASTM D2244 (Colour Change),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752; ASTM D523	DIN EN ISO 16474 series (Artificial Weathering); DIN EN ISO 4892 series (Accelerated UV Exposure); DIN EN ISO 2813 (Gloss Retention); DIN EN ISO 4628 (Colour/Film Degradation); DIN EN ISO 2409 (Adhesion)	REACH: Regulation (EC) No. 1907/2006 (UV absorbers, stabilisers, additives)
Heat Resistant Varnish	IS 337; IS 524	ISO 12944 (Protective Coatings); ISO 2813 (Gloss); ISO 4628 Series,ISO 1524; ISO 3251	ASTM D2485 (Heat Resistance of Coatings); ASTM D3359 (Adhesion); ASTM D4060 (Abrasion Resistance),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752; ASTM D523	DIN EN ISO 3248 (Heat Resistance of Coatings where applicable); DIN EN ISO 2409 (Adhesion); DIN EN ISO 15184 (Hardness); DIN EN ISO 2813 (Gloss)	AMPP: SP 1; AMPP: SP 6/NACE No.3 where applied on metal; REACH: Regulation (EC) No. 1907/2006 (heat-resistant resins, pigments, additives)
Electrical Insulating Varnish	IS 356 – Electrical Insulating Varnish — SpecificationIS 337; IS 524	ISO 6043 (Electrical Insulating Varnishes); ISO 60216 (Thermal Endurance Properties of Electrical Insulating Materials),ISO 1524; ISO 3251	ASTM D115 (Testing Varnishes Used for Electrical Insulation); ASTM D149 (Dielectric Breakdown Voltage); ASTM D257 (Electrical Resistance); ASTM D2307 (Thermal Endurance of Electrical Insulating Materials),ASTM D1544; ASTM D1640; ASTM D4752; ASTM D523	DIN EN 60464 series (Varnishes Used for Electrical Insulation); DIN EN IEC 60216 series (Thermal Endurance of Electrical Insulating Materials); DIN EN IEC 62631 series (Dielectric Properties); DIN EN IEC 60243 (Electric Strength); DIN EN IEC 60093 (Volume Resistivity)	REACH: Regulation (EC) No. 1907/2006 (resins, solvents, additives); FDA: —
Baking Varnish	IS 337; IS 524	ISO 9117 Series (Drying Time); ISO 2808 (Film Thickness); ISO 2813 (Gloss),ISO 1524; ISO 3251	ASTM D5895 (Drying/Curing Time); ASTM D3363 (Hardness); ASTM D523 (Gloss); ASTM D3359 (Adhesion),ASTM D115; ASTM D1544; ASTM D1640; ASTM D4752	DIN EN ISO 9117 series (Drying Tests); DIN EN ISO 15184 (Hardness); DIN EN ISO 2409 (Adhesion); DIN EN ISO 2813 (Gloss)	REACH: Regulation (EC) No. 1907/2006 (resins, curing agents, solvents); FDA: 21 CFR 175.300 only where used for food-contact coated metal applications

Source field: Dyes and Pigments