

Production Part Approval - Material Test Results

Page_3_of_3_ Pages

		wateriai Test Resu	1	. 49	e_3_ot_3	agee		
SUPPLIER	Juta, a.s plant 07, Na Borkách 89, 54401 Dvůr Králové nad Labem, CZ		PART NUMBER PART NAME	1827999-165020_D				
NAME OF LABORATORY	Laboratory on plant 07- Na Borkách 89			NON WOVEN NEEDLEPUNCH PES TT1.4MM				
MATERIAL SPECIFICATION N° / REVISION TMS-F9909 B / rev6, 08.04.2020 Roll nr. M123010107								
PROPERTY	TEST METHOD	LIMITS	UNIT	SUPPLIER TEST RESULTS	OK	NOT OK		
3.4.3 Weight	EN 12127	220 (±20)	g/m ²	223	Х			
3.4.4 Thickness	EN ISO 9073-2	1,40 (±0,20)	mm	1,49	Х			
3.4.5 Tensile Strength - MD	EN 29073-3	≥ 260	N/5cm	519,30	Х			
3.4.5 Tensile Strength - CMD	EN 29073-3	≥ 450	N/5cm	557,34	X			
3.4.6 Extension at max load - MD	EN 29073-3	≥ 40	%	54,72	х			
3.4.6 Extension at max load - CMD	EN 29073-3	≥ 30	%	57,63				
3.4.7 Extension at 100 N - MD	EN 29073-3	7 (±3)	%	8,03	Х			
3.4.7 Extension at 100 N - CMD	EN 29073-3	7 (±3)	%	8,51	Х			
3.4.8 Flammability	FMVSS 302	≤ 80	mm/min	0	Х			
3.4.9 Fogging	DIN 75201 B	≤ 1	mg	0,24	Х			
3.4.10 Odour	VDA 270 C1 + C2	≤ 3	Rating	1,5 / 2,0	Х			
			1					

NAME & SIGNATURE		TITLE	DATE
Munzarová Dominika	Henrarone' D.		18.05.2023