



河北屹洋管道设备有限公司
HE BEI WPHY CO.,LTD
MILL TEST CERTIFICATE

工厂检测证书

(EN10204 3.1)

检验证书/Certificate:		证书号/Certificate No.:		ISO 证书号/ISO certificate No:								
EN10204:2004-3.1		MTC-WPHY-YY2026041706		UQ231687R0								
客户/Customer: OIL METAL S.A 订单号/Order No.: PO00010088 品名/Article: 法兰/Flanges 技术条件/Specification: ASME B16.5 材料/Material: ASTM A105 加工工艺/Workmanship: 锻制/Forging 交货状态/Delivery Conditions: Finishing, Anti-rust oil				标识/Marking: 法兰型式 Manufacture's mark: WPHY Standard: ASME B16.5 Grade Material: ASTM A105 Heat Number: 22501154/230202828/25101212								
产品交货范围/Material Delivery Extent												
序号	品名	规格	数量	炉号	备注							
Item No.	Description	Dimension	Quantity	Heat No.	Remark							
17	SLIP ON FLANGE RF	2,5" #150	30	22501154	B16.5							
32	BLIND FLANGE RF	20" #150	5	230202828	B16.5							
35	WELDING NECK FLANGE RTJ	8" #900 SCH80	50	25101212	B16.5							
36	WELDING NECK FLANGE RF	16" #150 SCH20	50	230202828	B16.5							
试验结果/Test Results: 标准要求已符合, 见如下表格/The requirements are fulfilled as listed in Annex.												
A 化学成分/chemical composition:												
炉号/Heat No.	C%	Si%	Mn%	S%	P%	Cr%	Mo%	V%	Ni%	Cu%	Ti%	CE
ASTM A105	≤0.35	0.10-0.35	0.60-1.06	≤0.040	≤0.035	≤0.3	≤0.12	--	≤0.4	--	--	--
22501154	0.19	0.25	0.84	0.006	0.015	0.03	0.01	0.002	0.011	0.010		0.34
230202828	0.20	0.27	0.92	0.002	0.007	0.042	0.001		0.001	0.020	0.002	0.36
25101212	0.19	0.27	0.84	0.004	0.015	0.012	0.001		0.038	0.017	0.002	0.34
B 机械性能/Mechanical												
试样号	试验温度	屈服强度	拉伸强度	延伸率%	收缩率%	硬度	冲击试验					
Specimen	Test Temp	Yield Strength	Tensile Strength	Elongation	Reduction Area	Hardness	Charpy Impact					
Nr./No.		Mpa	Mpa	%	Z%	HB	--					
ASTM A105	24℃	≥250	≥485	≥22	≥30							
22501154		357	539	30	43	129	--					
230202828		371	563	30	43	129	--					
25101212		368	545	31	41	128	--					
C 无损探伤, 尺寸检查及水压试验/Hydrostatic Test, NDT and Dimension check:												
试验/Testing	结果/Result	试验/Testing	结果/Result									
尺寸检查/ Dimension check	OK	水压试验/Hydrostatic pressure test	N/A									
表面检查/Surface quality inspection	OK	100%PMI Test	PASSED									
晶腐/IGC to ASTM A262-2013 "E"	N/A	X 射线/X-ray test	N/A									
D 备注/Remarks:												
1.热处理 / 正火 Heat treatment/normalizing (at 900℃ not less than 60min)												
2.The material manufactured according to a Quality management system approved and registered to ISO 9001 .												
3.We hereby certify that the product described herein has been manufactured in accordance with the specifications concerned and also with the purchaser's requirements and that the test results shown herein are correct.												
地址: 沧州 河北 中国 Address: CANGZHOU HEBEI CHINA		日期: 2026-04-17 Date: Apr.17.,2026										
制单: Inspector: 朱雨晴		复验: Approved:孙少龙										
		审核: Approved: 刘建新										