



河北屹洋管道设备有限公司
HE BEI WPHY CO.,LTD

MILL TEST CERTIFICATE

工厂检测证书

(EN10204 3.1)

检验证书/Certificate:		证书号/Certificate No.:		ISO 证书号/ISO certificate No.:								
EN10204:2004-3.1		MTC-WPHY-YY2026041707		UQ231687R0								
客户/Customer: OIL METAL S.A. 订单号/Order No.:PO00010088 品名/Article: 管件/Fittings 技术条件/Specification: MSS SP 75/ASME B16.9 材料/Material: ASTM A860 WPHY65 加工工艺/Workmanship: 热成型/Hot Forming 交货状态/Delivery Conditions: Solution ,descaled ,Anti-rust paint				标识/Marking:管件型式 Manufacture's mark: WPHY Standard: MSS SP 75/ASME B16.9 Grade Material: ASTM A860 WPHY65 Heat Number: F3502158/20159654								
产品交货范围/Material Delivery Extent												
序号	品名	规格	数量	炉号	备注							
Item No.	Description	Dimension	Quantit	Heat No.	Remark							
6	TEE RED BARRED	12" X 10" SCH 80	1	20159654								
24	RED CON	4" X 3" SCH XXS	50	F3502158								
试验结果/Test Results: 标准要求已符合, 见如下表格/The requirements are fulfilled as listed in Annex.												
A 化学成分/chemical composition:												
炉号/Heat No.	C%	Si%	Mn%	S%	P%	Cr%	Mo%	V%	Ni%	Cu%	Ti%	CE
ASTM A860 WPHY 65	≤0.20	0.1--0.4	1.0--1.45	≤0.010	≤0.030	≤0.3	≤0.25	≤0.10	≤0.5	≤0.35	≤0.05	≤0.42
F3502158	0.10	0.30	1.25	0.003	0.012	0.037	0.001	0.002	0.014	0.009	0.006	0.32
20159654	0.14	0.22	1.31	0.003	0.008	0.11	0.04	0.001	0.06	0.002	0.003	0.38
B 机械性能/Mechanical												
试样号 Specimen	试验温度 Test Temp	屈服强度 Yield Strength	拉伸强度 Tensile Strength	延伸% Elongation	收缩率% Reduction Area	硬度 Hardness	冲击试验 Charpy Impact					
Nr./No.		Mpa	Mpa	%		HRB	-46℃					
ASTM A860 WPHY 65		≥450	≥530	≥28	Z%	≤235	≥18					
F3502158		462	542	35		118	62,79,85					
20159654		491	591	34		128	82,91,79					
C 无损探伤, 尺寸检查及水压试验/Hydrostatic Test,NDT and Dimension check:												
试验/Testing		结果/Result	试验/Testing		结果/Result							
尺寸检查/ Dimension check		OK	水压试验/Hydrostatic pressure test		N/A							
表面检查/Surface quality inspection		OK	100%PHM Test		PASSED							
晶腐/IGC to ASTM A262-2013 "E"		N/A	X 射线/X ray test		N/A							
D 备注/Remarks:												
1.热处理 / 淬火+回火 Heat treatment/Quenching(at 920℃ not less than 85.min in brine water.)+Tempering(at 580℃ not less than 85.min),												
2.The material manufactured according to a Quality management system approved and registered to ISO 9001 .												
3.We hereby certify that the product described herein has been manufactured in accordance with the specifications concerned and also with the purchaser's requirements and that the test results shown herein are correct.												
地址: 沧州 河北 中国 Address: CANGZHOU HEBEI CHINA			日期 :2026-04-17 Date:Apr.17.,2026									
制单: Inspector: 朱雨晴			复验: Approved:孙少龙									
			审核: Approved: 刘建新									