CERTIFIED MILL TEST REPORT

The Best Value - *Price, Quality, Service* All The Time.

LOG NO. F00000000241171 Page 5 of 10

BONNEY FORGE CORPORATION
P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330
(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906
www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 04/21/2026

CUSTOMER ORDER NO.: RMS-327746

BONNEY ORDER NO. B000380893

SHIP TO: EDGEN MURRAY CORPORATION
8445 MILLER RD 2
HOUSTON TX 77049
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO. CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:
19	50	J264	1/2 3M/6M A105 RDPL T SA/A105 Al 0.020 C 0.200 Co 0.010 Cr 0.110 Cu 0.110 Mn 0.970 Mo 0.020 Nb 0.001 Ni 0.050 P 0.010 S 0.021 Si 0.260 V 0.003 CE(Long Formula) = 0.40 T/S(PSI) 77,100 Y/S(PSI) 52,000 EL(%) 33.00 RA(%) 69.00 Brinell Hardness 148 BHN 152 BHN
20	25	52180	1/2 3000 A105 TEE T SA/A105 Al 0.031 C 0.200 Co 0.005 Cr 0.090 Cu 0.260 Mn 0.970 Mo 0.020 Nb 0.005 Ni 0.080 P 0.007 S 0.023 Si 0.245 V 0.021 CE(Long Formula) = 0.41 T/S(PSI) 80,711 Y/S(PSI) 52,025 EL(%) 31.85 RA(%) 60.01 Brinell Hardness 147 BHN 147 BHN
21	100	52342	1 3000 A105 TEE T SA/A105 Al 0.037 C 0.200 Co 0.005 Cr 0.120 Cu 0.250 Mn 0.990 Mo 0.010 Nb 0.002 Ni 0.060 P 0.006 S 0.024 Si 0.176 V 0.021 CE(Long Formula) = 0.42 T/S(PSI) 77,305 Y/S(PSI) 50,305 EL(%) 33.10 RA(%) 60.57 Brinell Hardness 139 BHN 139 BHN
22	40	52293	2 3000 A105 TEE T SA/A105 Al 0.023 C 0.190 Co 0.007 Cr 0.090 Cu 0.180 Mn 1.000 Mo 0.040 Nb 0.004 Ni 0.110 P 0.009 S 0.023 Si 0.205 V 0.022 CE(Long Formula) = 0.41 T/S(PSI) 79,304 Y/S(PSI) 51,862 EL(%) 27.70 RA(%) 60.97 Brinell Hardness 153 BHN 156 BHN

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by Natalie Miller
Natalie Miller
Quality Assurance Representative

CMTR: Rev 3

***