EDGEN MURRAY

an EDGEN Company

# Packing List

**Packing List :** 423161-1
**Ship Date :** 7/23/2026
**Cust/Ship to:** 1641/36

**Issued from :**
Edgen Murray LLC
8445 Miller Rd 2
Houston, TX 77049

**Ship-To :**
**ENVIRONMENTAL AND DEWATERING SOLUTI**
**4266 28TH STREET**
**DORR, MI 49323**

**Delivery Terms :** Prepay & Add
**Terms of Trade :** FOB: Shipping Point
**Carrier :** FEDERAL EXPRESS

**Vehicle No :**
**Trailer No :**
**Tracking No :** 812292886-6

**Our Order :** 2497163 **Your PO :** 26-510 (7/9/2026)

| Item | Product | Mill/Heat | Tag/ID | Qty | Pcs | Total |
|---|---|---|---|---|---|---|
| 5-1 | **Forged Equal Tee ASTM A/SA105 NPT Threaded**<br>**0.50" 3000#** | BON/52180 | 327746-20 | | 18 | 21.60 |
| 6-1 | **Pipe SMLS Nipple ASTM A106-B**<br>**0.50" x 3" XXH**<br>**Thrd Both Ends** | WES/W11542<br>WES/W11542 | 325522-22<br>326011-16 | | 15<br>3<br>Total 18 | 6.42<br>1.29<br>8 |
| 7-1 | **Pipe SMLS Nipple ASTM A106-B**<br>**0.50" x 4" XXH**<br>**Thrd Both Ends** | CPM/79RF | 316485-29 | | 10 | 5.72 |
| 8-1 | **Forged Hex Plug ASTM A/SA105 NPT Threaded**<br>**0.50" 3000#\6000#** | BON/J229 | 327746-15 | | 19 | 2.66 |
| 9-1 | **Pipe SMLS Nipple ASTM A106-B**<br>**1" x 3" XXH**<br>**Thrd Both Ends** | WES/W10439 | 325522-23 | | 8 | 7.33 |
| 11-1 | **Forged Equal Tee ASTM A/SA105 NPT Threaded**<br>**1" 3000#** | BON/52342 | 327746-21 | | 5 | 14.75 |
| 12-1 | **Forged Elbow 90 Deg ASTM A/SA105 NPT Threaded**<br>**1" 6000#** | BON/52212 | 323951-13 | | 5 | 11.65 |

# CERTIFIED MILL TEST REPORT

The Best Value - *Price, Quality, Service* All The Time.

**LOG NO.** F00000000241171 Page 5 of 10

**BONNEY FORGE CORPORATION**
P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330
(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906
www.bonneyforge.com

**CUSTOMER:** EDGEN MURRAY CORPORATION

**DATE** 04/21/2026

**CUSTOMER ORDER NO.:** RMS-327746

**BONNEY ORDER NO.** B000380893

**SHIP TO:** EDGEN MURRAY CORPORATION
8445 MILLER RD 2
HOUSTON TX 77049
United States

| ITEM | QUANTITY | LOT NO. | GRADE OR SPECIFICATION NO. CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS: |
|---|---|---|---|
| 19 | 50 | J264 | 1/2 3M/6M A105 RDPL T SA/A105<br>Al 0.020 C 0.200 Co 0.010 Cr 0.110 Cu 0.110 Mn 0.970 Mo 0.020 Nb 0.001<br>Ni 0.050 P 0.010 S 0.021 Si 0.260 V 0.003<br>CE(Long Formula) = 0.40<br>T/S(PSI) 77,100 Y/S(PSI) 52,000 EL(%) 33.00 RA(%) 69.00<br>Brinell Hardness 148 BHN 152 BHN |
| 20 | 25 | 52180 | 1/2 3000 A105 TEE T SA/A105<br>1/2" TEES THRD 3M<br>Al 0.031 C 0.200 Co 0.005 Cr 0.090 Cu 0.260 Mn 0.970 Mo 0.020 Nb 0.005<br>Ni 0.080 P 0.007 S 0.023 Si 0.245 V 0.021<br>CE(Long Formula) = 0.41<br>T/S(PSI) 80,711 Y/S(PSI) 52,025 EL(%) 31.85 RA(%) 60.01<br>Brinell Hardness 147 BHN 147 BHN |
| 21 | 100 | 52342 | 1 3000 A105 TEE T SA/A105<br>1" TEE THRD 3M<br>Al 0.037 C 0.200 Co 0.005 Cr 0.120 Cu 0.250 Mn 0.990 Mo 0.010 Nb 0.002<br>Ni 0.060 P 0.006 S 0.024 Si 0.176 V 0.021<br>CE(Long Formula) = 0.42<br>T/S(PSI) 77,305 Y/S(PSI) 50,305 EL(%) 33.10 RA(%) 60.57<br>Brinell Hardness 139 BHN 139 BHN |
| 22 | 40 | 52293 | 2 3000 A105 TEE T SA/A105<br>Al 0.023 C 0.190 Co 0.007 Cr 0.090 Cu 0.180 Mn 1.000 Mo 0.040 Nb 0.004<br>Ni 0.110 P 0.009 S 0.023 Si 0.205 V 0.022<br>CE(Long Formula) = 0.41<br>T/S(PSI) 79,304 Y/S(PSI) 51,862 EL(%) 27.70 RA(%) 60.97<br>Brinell Hardness 153 BHN 156 BHN |

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by Natalie Miller
Natalie Miller
**Quality Assurance Representative**

**CMTR: Rev 3**

***