GIBSON PRODUCTS

Gibson Products, Inc.
5691 SURREY SQUARE STREET
HOUSTON, TX 77017
Phone: (713) 941-4890

RTJ Well 318 FLANGE BLIND 8/26/26

Material Test Report

SOLD TO: BAYTOWN PIPE & SUPPLY
4406 ALLANBROK DR.
BAYTOWN, TX 77521

SHIP TO: BAYTOWN PIPE & SUPPLY
4406 ALLANBROK DR.
BAYTOWN, TX 77521

DATE	SALES ORDER #	CUST P.O. #	TAG NUMBER	
08/27/26	307594	6202628		

ITEM#	ITEM DESCRIPTION	SPEC/GRADE	QTY	HEAT CODE	HEAT NUMBER	STARTING MATERIAL
1	2 1/16" 2K RTJ BLIND API 6A TYPE 6B	ASTM A694 F52	3	65300 2@Well 318	207J285	ASTM/ASME A/SA350 LF6 CL1

CHEMICAL ANALYSIS

C	SI	MN	P	S	CR	NI	MO	CU	V	NB	N	B	CE
.15	.27	1.22	.007	.001	.07	.08	.019	.18	.09	.003	.018	.0003	0.4065

PHYSICAL PROPERTIES

Tensile (PSI)	Yield (PSI)	Elongation (2" or 4D)	Reduction of Area %	Hardness *BHN unless noted	Hardness 2
84,200	66,300	32	73.6	163 BHN	163 BHN

IMPACT TESTING

TYPE	TEMP	SMPL# 1	# 2	# 3	AVG	% SHEAR	LAT EXP
CHARPY1	-60 Deg. F	88 FT. LBS.	78 FT. LBS.	94 FT. LBS.	87 FT. LBS.	60-55-60	68-60-73 MLE

SUPPLEMENTAL INFORMATION

QUENCHED @ 1650°F FOR 6.5 HOURS, WATER COOLED START TEMP 76 END TIME 72. TEMPERED @ 1100°F FOR 11 HOURS, AIR COOLED. CE (F-factor): .386.

WE CERTIFY THAT THE MATERIAL FURNISHED ON THIS ORDER COMPLIES WITH THE SPECIFICATIONS AS STATED. IAW GIBSON PRODUCTS Q.A. PROGRAM AND QUALITY MANUAL. COMPLYING WITH ISO 9001 AND PRESSURE EQUIPMENT DIRECTIVE (PED) REQUIREMENTS. THE ISSUE YEAR & ADDENDA FOR THE ABOVE DESCRIBED MATERIAL IS THE SAME AS THE STARTING MATERIAL UNLESS OTHERWISE NOTED.

Dawn Sexton
QUALITY ASSURANCE