Weldolets

INTERNATIONAL WFI NUCLEAR PRODUCTS
Manufacturer of Piping and Pressure Vessel Components
4404 Haygood St - Houston, TX 77022
Phone: 713-695-3633 Fax: 713-695-3528
A Bonney Forge Company

This product has not come in direct contact with mercury or any of its compounds, nor with any mercury-containing device employing a single boundary of containment. No welding performed.

We certify that the contents of this report are correct and accurate, and that all test results and operations performed by WFI or its subcontractors are in compliance with the material specification and requirements of the referenced code or standard, and that the material conforms to the dimensional requirements of the order. This document is in accordance with EN10204 3.1.

Sold To: EDGEN MURRAY CORPORATION
(EARTH CITY)
3300 RIDER TRAIL SOUTH
EARTH CITY MO 63045
United States

- Slip on
- Socket Weld

MTR #: 458,629
PO #: STL-330927
Sales Order #: C002606829
Date: 07/31/2026

Certified Material Test Report

Heat Code: 9484AD
Material: A694 16 F52

Item	Quantity	Description
6	1	16 - 8 X 2 3M SWP
		A694F52

Chemical Composition

Ladle	Al	B	C	Co	Cr	CR+MO	Cu	Mn	Mn/C	Mo	N	Nb
	0.024	0.0003	0.200	0.003	0.10	0.11	0.06	1.060	5.300	0.005	0.003	0.0110
	Ni	P	RE(1)	S	Si	Ti	V					
	0.010	0.005	0.19	0.0190	0.230	0.001	0.00					
	Carbon Equivalency (C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15):				0.40							
Product	Al	B	C	Cr	CR+MO	Cu	Mn	Mn/C	Mo	Nb	Ni	P
	0.026	0.0024	0.186	0.10	0.11	0.06	1.000	5.376	0.007	0.0093	0.018	0.001
	RE(1)	S	Si	Ti	V							
	0.19	*0.0169*	*0.236*	0.001	0.00							
	Carbon Equivalency (C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15):				0.38							

RE(1) = Cu + Ni + Cr + Mo + V

	Tensile PSI	Yield PSI	Elong (4D) %	RA %	Hardness
Product	81,200	55,300	31.25	71.21	169 HBW 169 HBW

Charpy V-Notch Properties

Specimen Size	Test Temperature	Ft Lbs	% Shear	MLE	Direction
10mm x 10mm	-50 F	71/79/68	65/70/60	52/62/48	Longitudinal

MILL/COUNTRY OF ORIGIN: ARCELORMITTAL (MELTED & PRODUCED: CANADA) - HEAT NO.: C158002, CERTIFICATE NO.: 000822797
AUSTENTITIZED AT 1750°F FOR 2 1/4 HRS AND WATER QUENCHED; TEMPERED AT 1000°F FOR 3 HRS AND AIR COOLED
GRAIN SIZE IAW ASTM E112: #7.5

Monica Rogers Quality Assurance Representative