Certified Material Test Report
EN 10204:2004 Type 3.1

ALLOY PIPING PRODUCTS
740 NORTH MARKET STREET, SHREVEPORT LA 71107
Phone: (318)674-9860

Printed on: 08/14/25
Time: 15:54:09

Sold to:	Ship To:	

Sales Order #:	Cust PO #:	Book ID: 45461

Heat Number	Item Number	Item Description	UNS	Quantity
BD5291-1025621	8-I----ISVC7BAP	8" STD CAP MSS SP-75 WPHY52		

Starting Material: Plate

Order Spec:

Item Spec:	MSS SP-75 2019			

Result ID: 1 **Heat Analysis** — **Chemical Composition (wt%)**

Element	Content	Element	Content	Element	Content	Element	Content	Element	Content
C	0.1800	Mn	1.1900	P	0.0170	S	0.0020	Si	0.2900
Ni	0.0100	Cr	0.0100	Mo	0.0010	Cu	0.0100	V	0.0030
Nb	0.0180	Ti	0.0110	Al	0.0400	B	0.0005		

Summary Results

CE	0.38	Sum CuNiCrMo	0.0310	Sum Cr+Mo	0.0110	Sum Nb+V	0.0210	MN/C RATIO	6.6111

Result ID: 2 **Product Analysis** — **Chemical Composition (wt%)**

Element	Content	Element	Content	Element	Content	Element	Content	Element	Content
C	0.1500	Mn	1.1800	P	0.0150	S	0.0020	Si	0.2800
Ni	0.0100	Cr	0.0200	Mo	0.0160	Cu	0.0100	V	0.0020
Nb	0.0160	Ti	0.0090	Al	0.0300	B	0.0005		

Summary Results

CE	0.36	Sum CuNiCrMo	0.0560	Sum Cr+Mo	0.0360	Sum Nb+V	0.0180	MN/C RATIO	7.8667

TEST RESULTS

Work Order: 1025621 **Load Designation:** **Test Set:**

Continued on page: 2

Certified Material Test Report
EN 10204:2004 Type 3.1

ALLOY PIPING PRODUCTS
740 NORTH MARKET STREET, SHREVEPORT LA 71107
Phone: (318)674-9860

Printed on: 08/14/25
Time: 15:54:09

Sold to:	Ship To:	

Sales Order #:	Cust PO #:	Book ID: 45461

Heat Number	Item Number	Item Description	UNS	Quantity
BD5291-1025621	8-I----ISVC7BAP	8" STD CAP MSS SP-75 WPHY52		

Result ID: 1 — **Charpy Test**

Specimen Size: .394 In X .295 In **Test Temperature:** 20 °F

Sample Area: Base **Location:** 1/2 T Transverse

	Sample 1	Sample 2	Sample 3	
Shear (%):	69	72	68	**Average Shear:** 70
Absorbed Energy (ft-lbs):	117	119	115	**Avg Absorbed Energy:** 117 **Minimum Absorbed Energy:** 115
Lateral Expansion (In):	0.039	0.041	0.039	

Result ID: 1 — **Tensile Test**

Specimen type: Transverse Rectangular	**Gauge Length:** 2.00 In
Tensile Strength: 76.8 KSI	**Yield Strength:** 60.3 KSI
Elongation: 33.8 %	**Reduction:**

Result ID: 1 — **Hardness Test**

Hardness: 158 - 161 HBW

SUPPLEMENTAL INFORMATION

Bevels in accordance with ASME B16.25, unless noted otherwise.

Dimensions and tolerances in accordance with the latest edition of ASME B16.9.

Material, when shipped, is free from contamination by mercury, radium, alpha source and low melting elements.

Material supplied in accordance with a Quality Management System certified to ISO:9001-2015. CERTIFICATE NUMBER: Q1674

Hardness is acceptable in accordance with NACE MR0175-2021/ISO 15156:2020 and MR0103/ISO 17945:2015
We hereby certify that the materials listed above have been manufactured, sampled, tested and inspected in accordance with specifications

Continued on page: 3

Alloy Piping Products, LLC
A Texas Pipe & Supply Company

Certified Material Test Report
EN 10204:2004 Type 3.1

ALLOY PIPING PRODUCTS
740 NORTH MARKET STREET, SHREVEPORT LA 71107
Phone: (318)674-9860

Printed on: 08/14/25
Time: 15:54:09

Sold to:	Ship To:	

Sales Order #:	Cust PO #:	Book ID: 45461

Heat Number	Item Number	Item Description	UNS	Quantity
BD5291-1025621	8-I----ISVC7BAP	8" STD CAP MSS SP-75 WPHY52		

and grade listed, and have been found to meet the requirements.

Magnetic Particle Examination in Accordance with Supplemental Requirement S53 of ASTM A960. No Relevant Indications found at time of Inspection.

Heat Treat Statement:
Quenched at 1652°F and tempered at 1202°F

Starting Material Manufacturer: Jindal Steel, India (Heat: F33410)
Forming / Heat Treat: Sivanandha Pipe Fittings Ltd., India

Stacy Bellow
QA Manager

08/14/2025
Date

STEEL FORGINGS INC.

1810 BARTON DR.
PO BOX 7365
SHREVEPORT, LA
71137-7365
PHONE (318)222-3295

MILL TEST CERTIFICATION

FLEETLINE Welding Fittings

SOLD TO: DODSON

SHIP TO:

CUSTOMER PO No.	INVOICE No.	DATE	PAGE
430984	251570-03	8/11/2025	1 of 2

QTY	TYPE	FITTING DESCRIPTION									SPECIFICATION
50	CP	8	x		x		x	0.322	WPHY	52	**MSS-SP75-19**
			x		x		x				
			x		x		x				
			x		x		x				

WPHY	Test No.	CODE	SIZE	WALL	TYPE	STARTING MATERIAL MANUFACTURER/LOCATION
52	11340	CBBD	0.394		PLATE	METINVEST/ITALY

HEAT TREATMENT: TEMPERATURE (F)/TIME (MIN.)					MILL HEAT
ANNEAL	NORMALIZE	QUENCH	TEMPER	STR. RELIEVE	8D23AU
		1650/30	1300/45		

BASE (TRANSVERSE & STANDARD SIZE)			WELD (TRANSVERSE & STANDARD SIZE)		
YIELD	TENSILE	ELONG-IN	YIELD	TENSILE	ELONG-IN
MINIMUM REQUIREMENTS			MINIMUM REQUIREMENTS		
52,000	66,000	25-2	N/A	66,000	N/A
ACTUAL RESULTS			ACTUAL RESULTS		
63,192	77,150	28-2			

X	Testing performed after forming and final heat treatment.
	This is to certify that the weld seams were radiographically examined throughout the entire length of the weld after forming in accordance with para. UW-51 of Sec. VIII of the ASME Boiler& Pressure Vessel code and found to be satisfactory.
	Scraper bar welds and/or weld bevels (if applicable) were ME tested and found to be acceptable in accordance with the more stringent of E709 and customer specification. If bars are installed, stress relieving was performed after bar welding.
	This is to certify that the side wall area of the tee was mag particle examined and found to be satisfactory in accordance with Section 15.3 of MSS and ASME BPVC, Section V

We hereby certify that the above analyses are correct according to the records of the corporation.

Justin Dowty

Justin Dowty, Quality Control Manager

STEEL FORGINGS INC.

PAGE	2 of 2

1810 BARTON DR.
PO BOX 7365
SHREVEPORT, LA
71137-7365
PHONE (318)222-3295

MILL TEST CERTIFICATION

FLEETLINE Welding Fittings

	SIZE	TYPE	TEMP	ORIENTATION
				TRANSVERSE
BASE				WELD

NOTE: LINEAR EXPANSION RESULTS SHOWING "NB" INDICATE THE SAMPLE WAS CONSIDERED UNBROKEN AND THEREFORE COULD NOT BE MEASURED PER ASTM A370 SEC.26.4

LE	FT. LBS.	SHEAR
MINIMUM REQUIREMENTS		
INFO	20/15	INFO
ACTUAL RESULTS		
AVERAGE RESULTS		

LE	FT. LBS.	SHEAR
MINIMUM REQUIREMENTS		
INFO	20/15	INFO
ACTUAL RESULTS		
AVERAGE RESULTS		

HARDNESS (240 BHN Max.)													
	#1	#2	#3	#4	#5	#6	#7	#8	#9	#10	#11	#12	#13
BASE													

C	Mn	P	S	Si	Mo	Ni	Cr	Cu	V	Nb	Ti	B	CE
MAXIMUM LIMITS (UNLESS OTHERWISE NOTED)													
0.250	1.600	0.025	0.015	0.500	0.250	0.500	0.250	0.450	0.110	0.100	0.040	0.0010	0.45
ACTUAL RESULTS BY PRODUCT ANALYSIS													
0.146	1.286	0.015	0.002	0.184	0.005	0.008	0.012	0.009	0.001	0.001	.002	0.0000	0.34
ACTUAL RESULTS BY LADLE ANALYSIS													
0.160	1.387	0.015	0.002	0.204	0.005	0.016	0.013	0.018	0.002	0.001	.002	0.0002	0.39

Invoice NO. 251570-03 PO# 430984 8/11/2025

FLEET-LINE STEEL BUTT-WELDING FITTINGS MADE TO ANSI B16.9 AND MSS-SP75 COMPLY WITH THE REQUIREMENTS OF ANSI/ASME B31.4, ANSI/ASME B31.8, AND PARAGRAPH 192.149(b) OF THE DEPARTMENT OF TRANSPORTATION, TITLE 49, CODE OF FEDERAL REGULATIONS, PART 192 (FEDERAL REGISTER VOLUMN 35, NUMBER 161) FOR THE TRANSPORTATION OF NATURAL AND OTHER GAS BY PIPELINE.

ALL COMPONENTS ARE MANUFACTURED UNDER A QUALITY CONTROL SYSTEM WHEREIN OUR EXPERIENCE HAS SHOWN THAT EACH ITEM MANUFACTURED IS AT LEAST EQUAL IN STRENGTH TO A PROTOTYPE AND THAT THE PROTOTYPE WAS TESTED TO AT LEAST THE PRESSURE REQUIRED FOR THE PIPELINE WHICH IT IS INTENDED TO BE ADDED.

We hereby certify that the above analyses are correct according to the records of the corporation.

Justin Dowty

Justin Dowty, Quality Control Manager