WESTBROOK

MATERIAL TEST REPORT

1111 LOCKWOOD DR.
HOUSTON, TX 77020

Voice 713 675 6438
Fax 713 675 9742

Sold To: *DNOW L.P.* **Purchase Order:** *662766096* **Printed:** *7/10/2025*
Order No.: *362122* **Order Date:** *7/02/2025*

U0921

****** Specifications - Heat Code W24058 PH: ******
A106-19 GR.B, SA106 GR.B, A234-19 WPB, SA234 WPB, A530, A733, ASME B36.10, B1.20.1, MSS SP-25, SP-95
STARTING MATERIAL: A106B PIPE & TUBE
A234-18 WPBN, SA234 WPBN

Chemical Composition %:

C:	Mn:	P:	S:	Si:	Cr:	Ni:	Mo:
0.180	*0.800*	*0.014*	*0.009*	*0.250*	*0.080*	*0.070*	*0.010*
Cu:	**V:**	**Cb/Nb:**	**Ti:**	**B:**	**C.E.:**		
0.180	*0.003*	*0.001*	*0.000*	*.<0001*	*.348*		

Mechanical Properties:

Tensile(PSI):	Yield(PSI):	Elong(%):	Hardness:	Bend:	Hydro(PSI):
76125	*59450*	*34.40*	*<=HRC 22*	*PASSED*	*2970*

Comments:
As finished
Product is compliant with NACE MR0175/ISO 15156 / Product is compliant with NACE MR0103.
No weld repair is performed.
The product is free of Mercury contamination.
Tensile test is taken from round specimen.
Yield Strength is determined using 0.2% offset method, unless otherwise specified.
When reported on the MTR: Tensile testing per ASTM E 8, Charpy impact testing per ASTM E 23 and Brinell Hardness Testing per ASTM E 10.
Products are manufactured in compliance to EN 10204 Type 3.1.

Line: **Description:**
4 *3 X 1 1/2 S80 A234WPB BLK ECC SWG BXP*

739Weld4

****** Specifications - Heat Code W24175 ZZ: ******
A105/A105M-21, SA105, A234-18 WPB, SA234 WPB, ASME B16.5, B16.9, B16.11, B16.36, B1.20.1, MSS SP-25, SP-44, SP-79, SP-83, SP-95, API-605, A.W.W.A.
STARTING MATERIAL: BAR/BILLET/FORGING
A234-18 WPBN, SA234 WPBN

Chemical Composition %:

C:	Mn:	P:	S:	Si:	Cr:	Ni:	Mo:
0.190	*0.950*	*0.006*	*0.014*	*0.260*	*0.140*	*0.070*	*0.030*
Cu:	**V:**	**Al:**	**Co:**	**Cb/Nb:**	**N:**	**W:**	**Sn:**
0.170	*0.001*	*0.023*	*0.006*	*0.001*	*0.011*	*0.001*	*0.009*
Pb:	**Ti:**	**B:**	**Ca:**	**As:**	**C.E.:**		
0.001	*0.001*	*.0004*	*.001*	*.004*	*.398*		

Mechanical Properties:

Tensile(PSI):	Yield(PSI):	Elong(%):	RA(%):	Hardness:
77000	*48721*	*31.10*	*54.20*	*HB 148-148*

Comments:
Normalized 1700F, 5 hrs.
Product is compliant with NACE MR0175/ISO 15156 / Product is compliant with NACE MR0103.
No weld repair is performed.
The product is free of Mercury contamination.

We hereby certify that the contents of this Material Test Report are correct and accurate to the best of our knowledge and belief, that all test results are in compliance with the material specifications and that all material meets the dimensional requirements of the order. The products described have not come into contact with mercury or any of its components. No weld repair performed. Westbrook's Quality System is registered to ISO 9001, Certificate #32813. This document is in accordance with EN10204:2004 3.1/DIN50049 3.1B and was electronically transmitted. This inspection certificate is issued under the authority of Westbrook's QA Manager.

Prop 65 Warning for California Residents - Products listed may contain chemicals including Nickle and/or Carbon known to the State of California to cause cancer, birth defects and other reproductive harm. http://www.p65warnings.ca.gov/