GALPERTI, INC.
160 Southbelt Industrial Drive
Houston, Texas 77047
PH. 713-433-0700 - FAX 713-433-5580
Email: houstonqualityassurance@galperti-am.com

MESSRS
MAVERICK INTERNATIONAL LTD
PO BOX 1994
WINNIE TX 77665
United States

TEST CERTIFICATE EN10204 **3.1** INTERNAL JOB **S10260285**

CERTIFICATE N. CER004069 DATE 06/16/2026
YOUR ORDER 4063887 CODE/CUSTOMER ITEM /
DATE 05/15/2026

GN ITEM	Q.ty	B/ A	DESCRIPTION MATERIAL (1)	HEAT N° TEST N°	COUNTRY OF MELT
47	20	B	8 900 BL RF LF2 B1 F ASTM/ASME A/SA105N - A/SA 350-LF2 CL.1 - A694 F42	1240478/02 T000740	Mexico

CUSTOMER DESCRIPTION

SO NOTES

NOTES (1)
FINISH / ROUGHNESS
F - Stock finish 125-250µinch

STANDARD
B1 - ASME B16.5-2025 Inch STD

CHEMICAL ANALYSIS

	B %	C %	Ca %	Cr %	Cu %	Mn %	Mo %	N %	Nb %	Ni %	P %	S %	Si %	V %				
L	0.0001	0.1500	0.0020	0.1600	0.1300	1.1600	0.0400	0.0060	0.0004	0.2000	0.0087	0.0016	0.2100	0.0207				
C	0.0002	0.1500	0.0042	0.1600	0.1300	1.1600	0.0410	0.0030	0.0010	0.2000	0.0080	0.0020	0.2100	0.0220				
																F_FL %	F_04 %	F_03 %
L																0.4100	0.5507	0.2000
C																0.4100	0.5530	0.2010

NOTES
F_03=Chromium + Molybdenum
F_04=Copper + Nickel + Chromium + Molybdenum + Vanadium
F_FL=Carbon Equivalent (Long Formula)

MECHANICAL PROPERTIES

TENSILE

	POSITION	DIAMETER [in]	AREA [in2]	LENGTH [in]	TEMP. [°F]	TENSILE [ksi]	YIELD [ksi]	ELONG [%]	REDUCT. [%]	HARDNESS [HBW]	NOTES
S	LONG 1/4	0.500	0.196	2.000	68	70	42	22	30	137 - 197	
O	LONG 1/4	0.500	0.196	2.000	68	70	45	38	71.6	137 - 137	

CHARPY TEST

	POSITION	TYPE	SIZE [in]	TEMP. [°F]	VALUES [ftlbs]	EXPANSION [in]	AREA [%]	NOTES
S	LONG 1/4	KV	0.394	-50	15 Med- 12 Min	-	-	
O	LONG 1/4	KV	0.394	-50	226 - 238 - 120 Avg : 194.66	0.08 - 0.08 - 0.08 Avg : 0.08	87 - 87 - 87 Avg : 87	

HEAT TREATMENTS

Normalized at 900 dgr.C.
Soak Time of 1 hour per 25mm thickness, with a minimum soak time of 1 hour.
Material cooled in still air after normalization

HT NOTES

Legenda:
L = LADLE ANALYSIS
C = CHECK ANALYSIS
S = STANDARD
O = OBTAINED
B/A=BALANCE/ADVANCE

NOTES
MATL I.A.W NACE MR-0175/ISO 15156-2-15ED,NACE MR0103 15 ED A/SA105N, A694F42, A/SA350LF2N CL1,
Steel Fully killed made to fine grain practice. MSS-SP44 2026

ONLY THE MECHANICAL PROPERTIES SECTION IS UNDER ISO 17025

TRADE MARK

INT. INSPECT DATE 06/16/2026

CERTIFICATED BY
Marissa Contreras

INSPECTION AUTHORITY

An ISO 9001/2015 certified company
Certification issued by: Lloyd Register quality assurance.
Certification NO. UQA 10580220