FORM 687 Rev B

KERKAU MANUFACTURING

Flanges-Precision Machining

1321 Valley Center Dr.
Bay City, MI 48706

Phone (989) 686-0350
Toll Free (800) 248-5060
Fax (989) 686-0399

Material Test Report

Date: 07/13/2026

Sold To: DNOW - MT.PLEASANT
P.O. BOX 40985

USA

Ship To: DNOW-MT PLEASANT
1701 GOVER PKWY

USA

Order No: 0799366
PO No: 663013458

Ship Instructions:

Item Description

4 900# BLD RF A105 ASTM A105M-21/ASME SA105M-21 NORMALIZED

Lot No.

2DRP

C%	Mn%	P%	S%	Si%	Cr%	Cu%	Ni%	Mo%	V%	Cb%	N%	Al%	Ti%
0.18000	1.07000	0.00900	0.00800	0.22000	0.13000	0.16000	0.10000	0.02000	0.00200	0.00200	0.01000	0.03100	0.01900

B%	Ca%
0.0001	0.00200

Tensile (PSI)	Yield (PSI)	Elong %	Reduction %	Brinell	Rockwell	CE
73,824	49,748	31.8	69.4	146-148	0	.406

Grain Size	Test Size	Impact	Charpy	Shear	Lateral Exp.
0	0	//	0	//	//

"THE RECORDING OF FALSE, FICTITIOUS, OR FRAUDULENT STATEMENT OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE."

EN 10204:2004 3.1
NACE MR0175-2015 ISO 15156-2 2015 NACE MR0103/2015 ISO 17945-1 2015
NO WELD REPAIR MERCURY FREE
ELONGATION TAKEN FROM A ROUND SPECIMEN
YIELD STRENGTH WAS DETERMINED USING THE 0.2% OFFSET METHOD.
FULLY KILLED AND FINE GRAIN PRACTICED
NORMALIZED AT 920°C COOLED IN STILL AIR

THIS IS A DIGITALLY CREATED DOCUMENT

Justin Plowdrey

Justin Plowdrey / QA MANAGER