8/24 Olot

INTERNATIONAL WFI NUCLEAR PRODUCTS
Manufacturer of Piping and Pressure Vessel Components
4404 Haygood St - Houston, TX 77022
Phone: 713-695-3633 Fax: 713-695-3528
A Bonney Forge Company

This product has not come in direct contact with mercury or any of its compounds, nor with any mercury-containing device employing a single boundary of containment. No welding performed.

We certify that the contents of this report are correct and accurate, and that all test results and operations performed by WFI or its subcontractors are in compliance with the material specification and requirements of the referenced code or standard, and that the material conforms to the dimensional requirements of the order. This document is in accordance with EN10204 3.1.

Sold To: EDGEN MURRAY CORPORATION
(EARTH CITY)
3300 RIDER TRAIL SOUTH
EARTH CITY MO 63045
United States

MTR #: 459,721
PO #: STL-331891
Sales Order #: C002607842
Date: 08/25/2026

Certified Material Test Report

Heat Code: 9245AD
Material: A694 16 F52

Item	Quantity	Description
2	1	10 - 5 X 2 3M THP
		A694F52

Chemical Composition

	Al	B	C	Cr	CR+MO	Cu	Mn	Mn/C	Mo	N	Nb	Nb+V
Ladle	0.030	0.0002	0.210	0.09	0.09	0.04	1.070	5.095	0.004	0.003	0.0140	0.02
	Ni	P	RE(1)	S	Si	Ti	V					
	0.020	0.004	0.16	0.0220	0.190	0.001	0.00					
	Carbon Equivalency (C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15):				0.41							

	Al	B	C	Cr	Cu	Mn	Mo	Nb	Ni	P	S	Si
roduct	0.023	0.0006	0.213	0.09	0.04	1.090	0.007	0.0170	0.019	0.005	0.0323	0.184
	V											
	0.00											
	Carbon Equivalency (C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15):				0.42							

RE(1) = Cu + Ni + Cr + Mo + V

	Tensile PSI	Yield PSI	Elong (4D) %	RA %	Hardness
Product	82,300	57,000	33.30	71.40	170 BHN 170 BHN

Charpy V-Notch Properties

Specimen Size	Test Temperature	Ft Lbs	% Shear	MLE	Direction
10mm x 10mm	-50 F	134/115/98	75/75/65	72/68/52	Longitudinal

MILL/COUNTRY OF ORIGIN: ARCELORMITTAL (CANADA) - HEAT NO.: C150346

AUSTENITIZED AT 1675±25°F FOR A MINIMUM OF 60 MINUTES PER INCH OF SECTION THICKNESS, BUT NO LESS THAN 60 MINUTES AT TEMPERATURE (WATER QUENCHED); TEMPERED BETWEEN 1000-1025°F FOR 60 MINUTES OF SECTION THICKNESS (STILL AIR COOLED).

Monica Rogers Quality Assurance Representative