TECTUBI RACCORDI S.p.A. ALLIED GROUP
Via Roma 150,29027 Podenzano (PC), Italy
mail: info@tectubiraccordi.com
Tel: +39 0523555111
Fax: +39 0523555318

INSPECTION CERTIFICATE EN 10204 – 2004

☒ 3.1 ☐ 3.2

NUMBER 23CL-01703
REVISION 1
DATE 01/02/2024

CLIENT: ALLIED FITTING L.P.
ORDER: PO48958
JOB: TI/23C-0012

CLIENT ITEM	ITEM	Q.ty	DESCRIPTION	HEAT CODE	SPECIFICATION	MATERIAL	STEEL MAKER	CERT.N.	RAW MATERIAL
56	53	28	12 XH 3R 90 ELL Y52 SMLS SEGMENTABLE - Product Code: 5P93X12-TIM1	924670	A860/A860M-18 MSS SP-75-2019	WPHY52	TENARIS DALMINE	01-22-13741	PIPE

CHEMICAL COMPOSITION ☒ BY LADLE ANALISYS * ☒ BY CHECK ANALYSIS () **

HEAT	Test	C	Mn	Si	P	S	Cr	Ni	Mo	Ti	Cu	V	Al	Nb
min.			1,00	0,15								0,025	0,02	
max.		0,20	1,35	0,35	0,025	0,01	0,20	0,40	0,10	0,04	0,35	0,08	0,05	0,02
924670*		0,11	1,26	0,30	0,01	0,002	0,13	0,12	0,09	0,003	0,12	0,08	0,029	0,013
924670**		0,12	1,25	0,29	0,011	0,0022	0,12	0,11	0,08	0,0029	0,11	0,07	0,028	0,012

The chemical values and tensile properties are a true and correct copy of the certificate issued by the supplier of raw materials or by the laboratory which has determined them.

MECHANICAL PROPERTIES ☐ ON RAW MATERIAL * ☒ ON FINISHED FITTINGS ** ☐ SUPPLEMENTARY REQ. ***

Tensile Test	Temp. °C:		+ 23	Impact Test		Temp. °C:	- 46				
	Y.S. MPA	U.T.S. MPA	E%	Senso Direct.	Dim. Sample		KCV (Joule)	Shear Area %	Lat.Exp. mm	Hardness HB	Red. Area %
min.	360	455	25			min.	44	min. 75	min. 0,64	min.	
max.	465	585				average	44			max. 197	
(B) 42806CSG**	364	547	35,17	T	10 X 10	351,6-343,1-373,5		100-100-100	1,79-1,78-1,72	163÷169	

REMARKS

Melting process: Electric Furnace
Manufacturing method: Hot Formed (780°C + 980°C)
Heat treatment: Normalised at 920°C (1H/1" WTH) still air cooling

Visual and dimensional examination in accordance with:
ASME B16.9 Latest Edition
ASME B16.25 Latest Edition

Material according to:
NACE MR 01-75 ISO 15156 & NACE MR 01-03 Latest Edition

Ultrasonic Examination of Wth. Through the Body: Satisfactory

All material supplied is certify to be free of mercury contamination & no mercury bearing equipment was used during manufacturing

ACTIVITIES						
CERTIFICATE						
RESULT						
ACTIVITIES						
CERTIFICATE						
RESULT						

Work inspector — TECTUBI RACCORDI S.p.A. S. ANDRINI Q.C.
DATE SIGNATURE

Customer inspector
DATE SIGNATURE

Third part inspector
DATE SIGNATURE

We hereby certify that the materials listed below have been manufactured in compliance with the order and mentioned rules.

☒ 2014/68/EU Directive - Annex I § 4.3