Olet 8/26

INTERNATIONAL WFI NUCLEAR PRODUCTS
Manufacturer of Piping and Pressure Vessel Components
4404 Haygood St - Houston, TX 77022
Phone: 713-695-3633 Fax: 713-695-3528
A Bonney Forge Company

Sold To: EDGEN MURRAY CORPORATION
(EARTH CITY)
3300 RIDER TRAIL SOUTH
EARTH CITY MO 63045
United States

MTR #: 459,721
PO #: STL-331891
Sales Order #: C002607842
Date: 08/25/2026

This product has not come in direct contact with mercury or any of its compounds, nor with any mercury-containing device employing a single boundary of containment. No welding performed.

We certify that the contents of this report are correct and accurate, and that all test results and operations performed by WFI or its subcontractors are in compliance with the material specification and requirements of the referenced code or standard, and that the material conforms to the dimensional requirements of the order. This document is in accordance with EN10204 3.1.

Certified Material Test Report

Heat Code: 9357AH
Material: A694 16 F52

Item	Quantity	Description
3	2	36 - 3 X 1 3M THP
		A694F52

Chemical Composition

	Al	B	C	Co	Cr	Cu	Mn	Mo	Nb	Ni	P	Pb
Ladle	0.032	0.0007	0.200	0.006	0.14	0.23	1.020	0.020	0.0030	0.070	0.014	0.004

	S	Si	Ti	V
	0.0230	0.203	0.002	0.02

Carbon Equivalency (C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15): 0.43

	Al	B	C	Co	Cr	Cu	Mn	Mo	Nb	Ni	P	S
Product	0.035	0.0024	0.225	<0.001	0.13	0.23	1.000	0.017	0.0011	0.071	0.012	0.0226

	Si	Ti	V
	0.193	0.001	0.02

Carbon Equivalency (C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15): 0.45

	Tensile PSI	Yield PSI	Elong (4D) %	RA %	Hardness
Product	85,600	65,400	31.20	70.40	187 BHN 187 BHN

Charpy V-Notch Properties

Specimen Size	Test Temperature	Ft Lbs	% Shear	MLE	Direction
10mm x 10mm	-50 F	124/120/117	100/100/100	76/71/56	Longitudinal

MILL/COUNTRY OF ORIGIN: NUCOR (MELTED AND MANUFACTURED : USA) - HEAT#8000017676
BONNEY FORGE (USA) - LOT#51395

AUSTENTITIZED 1650°F AT 1 HOUR WITH WATER COOLING METHOD
TEMPER 1100°F AT 1 1/4 HOUR WITH AIR COOLING METHOD

Monica Rogers Quality Assurance Representative