TECTUBI RACCORDI S.p.A. ALLIED GROUP
Via Roma 150,29027 Podenzano (PC), Italy
mail: info@tectubiraccordi.com
Tel: +39 0523555111
Fax: +39 0523555318

INSPECTION CERTIFICATE EN 10204 – 2004

NUI
REV

☒ 3.1 ☐ 3.2

Delivered: 11/12/2025

CLIENT: ALLIED FITTING L.P.

ORDER: PO67831

JOB: TI/24C-0033

CLIENT ITEM	ITEM	Q.ty	DESCRIPTION	HEAT CODE	SPECIFICATION	MATERIAL	STEEL MAKER	CER
9	9	16	16 XH 3R 90 ELL Y65 SMLS SEGMENTABLE - Product Code: 65p93x16-TIM1	940006	A860/A860M-18 MSS SP-75-2019	WPHY65	TENARIS DALMINE	C

CHEMICAL COMPOSITION ☒ BY LADLE ANALISYS * ☒ BY CHECK ANALYSIS (

HEAT	Test	C	Mn	Si	P	S	Cr	Ni	Mo	Ti	Cu	V	Al	Nb	Ce	B
min.			1,00	0,15								0,025	0,02			
max.		0,20	1,45	0,35	0,025	0,01	0,15	0,45	0,10	0,04	0,35	0,10	0,05	0,04	0,42	0,0005
940006*		0,13	1,27	0,31	0,014	0,002	0,10	0,10	0,09	0,002	0,13	0,07	0,035	0,014	0,409	0,0002
940006**		0,12	1,26	0,30	0,013	0,0019	0,09	0,11	0,08	0,002	0,12	0,06	0,034	0,013	0,3913	0,0001

The chemical values and tensile properties are a true and correct copy of the certificate issued by the supplier of raw materials or by the laboratory which has determined them

MECHANICAL PROPERTIES ☐ ON RAW MATERIAL * ☒ ON FINISHED FITTINGS ** ☐ SUP

Tensile Test	Temp. °C:		+ 23	Impact Test		Temp. °C:	- 46				
	Y.S. MPA	U.T.S. MPA	E%	Senso Direct.	Dim. Sample		KCV (Joule)	Shear Area %	Lat.Exp. mm	Hardness HB	Red. Area %
min.	450	530	28			min.	44	min. 75	min. 0,64	min.	
max.	550	703				average	44			max. 235	
(B) 49274CSG**	466	613	34,5	T	10 X 10	188,6-225,9-278		90-100-100	2,47-2,22-2,6	198÷204	

ACTIVITIES						
CERTIFICATE						
RESULT						
ACTIVITIES						
CERTIFICATE						
RESULT						

REMARKS

Melting process: Electric Furnace
Manufacturing method: Hot Formed (780°C ÷ 98(
Heat treatment : Quenched at 920°C (1H/1" WT)
Tempered at 680°C (1H/1" WTH) still

Visual and dimensional examination in accordan
MSS SP-75 Latest Edition
MSS SP-75 Latest Edition

Material according to:
NACE MR 01-75 ISO 15156 & NACE MR 01-03 I

Ultrasonic Examination of Wth. Through the Bod

All material supplied is certify to be free of mercu
equipment was used during manufacturing

Work Inspector

TECTUBI RACCORDI S.p.A. S. AMORINI Q.C.

Customer Inspector

Third part inspector