CERTIFIED MATERIAL TEST REPORT
CERTIFICATE OF COMPLIANCE
CERTIFICATE # 253301
REVISION 0

Tube Forgings of America, Inc.
5200 N.W. Front Avenue
Portland, OR 97210
ISO 9001:2015 Certified

8/5/2026

Sold To	DNOW LP #MI04 1701 Gover Pkwy. Mt Pleasant, MI 48858-8140	Ship To	DNOW LP #MI04 1701 Gover Pkwy. Mt Pleasant, MI 48858-8140
Customer ID	34217		
TFA Sales Order	331046\1-1		
Purchase Order	663013400		

TFA Part ID	55214	Heat Code	A2794L
Description	10 X 4 XH TEE Y-52	Grade	Y52
Quantity	1	Raw Material Heat	045179
Customer Part ID	ZFIT	Process	Y52-3BX
		Mill	TPCO

Austenitized @:	1750°	Tempered @:	1100°	Stress Relieved @:		Medium:	WATER
Held For:	60 mins/min	Held For:	60 mins/min	Held For:	mins/min		

Heat Analysis Chemistry

C	Mn	P	S	Si	Mo	Cr	Ni	Cu	V	Cb	B	Ti	Al	N	Co	Ca	C.E.
0.15	1.13	0.012	0.003	0.26	0.02	0.01	0.02	0.02	<0.01	<0.01	0.0005	0.01	0.02				0.34

Product Analysis Chemistry

C	Mn	P	S	Si	Mo	Cr	Ni	Cu	V	Cb	B	Ti	Al	N	Co	Ca	C.E.
0.14	1.11	0.010	0.001	0.28	0.01	0.01	0.01	0.03	<0.01	<0.01	<0.0010	0.01	0.02				0.32

Tensile Test Results

Test	Name	Yield	Tensile	% Elong	R/A %	Gage Length	HBW	*In-Process* Test 1	*In-Process* Test 2	Tensile Orientation	Test Bar Type & Size
1	BASE	57200 (psi)	77000 (psi)	30.70	80.70	4D	156			TRANSVERSE	ROUND (.353" Diameter)

Charpy Impact Test Results

	Impact Energy				Lateral Expansion (Mils)			% Shear				Test Temp.	Size (mm)	Charpy Orientation
	1	2	3	Avg	1	2	3	1	2	3	Avg			

Notes/Comments

1. THIS MATERIAL WAS AUSTENITIZED AT 1750F,WATER QUENCHED, AND TEMPERED AT 1100F. 2. THIS MATERIAL IS OF SEAMLESS MANUFACTURE.

UB= Unbroken Test

Heat: A2794L Grade: Y52

Scot Marshall, Manager Quality Assurance

The recording of fictitious entries on this document and or its fraudulent misuse may be punishable as a felony under Federal Statute.