PFAM PRECISION FLANGE & MACHINE
13123 West Hardy Rd
Houston, TX 77060
Ph: 281-447-8077
Fa: 281-447-8422

Material Test Report

Material Test Report#
35088
Date
07/13/2026

Sold To:
DNOW L.P.

Order	Line	Release	PO#	Tag#	Item
2335411	1	2	663013254	COST CENTER 107334	F26ETC

Specifications

Part Code	Specification	Description
P26E8	API 6A 45K PSL-1	2.06 2K XH RTJ WELDNECK FLANGE 6B R-23 45K PSL-1 TC-L MC-BB

Chemical Analysis

Heat Code	C %	Mn %	Si %	P %	S %	Ni %	Cr %	Mo %	Cu %	V %	Nb %	Al %	Ti %	N
P26E8	0.18	1.13	0.27	0.007	0.006	0.06	0.10	0.03	0.10	0.032	0.003	0.005	0.027	0.0097
Heat Code	Sn %	B %	As %	Ca %	Co %	Pb %	Sb %	Ta %	W %	Te %	Zr %	Bi %		
P26E8	0.41	0.0001	0.002	0.0008	0.005	0	0	1.5 PPM	0.004	0.002	0	0		

Mechanical Properties

Heat Code	% EL	R of A	Yield PSI	Tensile PSI	HB
P26E8	36.4	69.9	51400	77600	156
Heat Code	Grain				
P26E8	10.0				

Impact Tests

Heat Code	Charpy V-Notch	C/V Temp	Test	Shear	Lateral Expansion
P26E8	42 / 56 / 66	-50F	10 X 10 MM	34% / 45% / 55%	31 / 45 / 49

Heat Treatments

Heat Code	Heat Treatment
P26E8	NORMALIZED @ 1665°F FOR 2 HRS; STILL AIR TO 1000°F.

Supplementals

Heat Code	Supplemental
P26E8	YIELD STRENGTH WAS DETERMINED BY .2% IN ACCORDANCE WITH TEST METHODS & DEFINITIONS A370. GRAIN SIZE IN ACCORDANCE PER ASTM E112. ELECTRIC ARC FURNACE. FULLY KILLED. CONFORMS TO NACE MR0175/ISO 15156:2015 & MR0103/ISO 17945:2015. CHARPY V-NOTCH IMPACT RESULTS ARE STATED IN FT. LBS. YIELD & TENSILE RESULTS OBTAINED FROM TEST COUPONS FROM THE SAME HEAT TREATMENT BATCH OF FITTINGS. LATERAL EXPANSION IS IN MILS. MELTED & MANUFACTURED IN THE USA. FINE GRAIN PRACTICE. VACUUM DEGASSED.

I HEREBY CERTIFY THAT THE INFORMATION SUPPLIED ABOVE IS TRUE AND CORRECT AND MATCHED THE INFORMATION KEPT IN OUR FILES. THE MATERIAL IS ALSO IN COMPLIANCE WITH ALL APPLICABLE SPECIFICATIONS. ANY ALTERATION IS PUNISHABLE UNDER FEDERAL LAW. DIN 50049 3.1.B EN 10204 3.1 ISO 10474 3.1.B ISO 9001:2015

Approved By
Sam Brown