WELDBEND

6600 South Harlem Avenue
Argo, IL 60501-1930

Material Test Report

,

Product	Heat Code	Heat Treatment	Steel Mill
6" Std Cap WPHY52	SNAC83	Heat Treat: Normalized	METINVEST TRAMETAL SP75 WPHY 52-08 Dimensional Specification: B16.9

	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Al	Ti	B	Cb	CE (SP75)
L	0.16	1.40	0.015	0.002	0.29	0.01	0.01	0.02	0.005	0.04	0.035	0.022	0.0002	0.024	0.405
P	0.15	1.32	0.016	0.005	0.27	0.01	0.01	0.01	0.010	0.03	0.040	0.020	0.0005	0.020	

Fine Grain Practice

Tens.	Yield	Elon	ROA	BHN	BHN2
81,400	58,200	33.00	77.60	152	157

Y-52

Test Temperature: -50 °F Percent Shear: 30/30/30 Average: 30
Absorbed Energy (ft/lbs): 39/307/30 Average: 125
Lateral Expansion (mils): 54/47/48 Average: 50

	Heat Code	Heat Treatment	Steel Mill
12" Std CAPS - Y52	MNAA06	Heat Treat: Normalized	METINVEST TRAMETAL SP75 WPHY 52-08 Dimensional Specification: B16.9

	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Al	Ti	B	Cb	CE (SP75)
L	0.17	1.40	0.013	0.004	0.29	0.01	0.00	0.01	0.005	0.04	0.027	0.022	0.0005	0.024	0.419
P	0.15	1.43	0.012	0.005	0.29	0.02	0.01	0.01	0.010	0.04	0.029	0.021	0.0005	0.026	

Fine Grain Practice

Tens.	Yield	Elon	ROA	BHN	BHN2
80,500	53,500	32.00	77.00	149	150

Y-52

Test Temperature: -50 °F Percent Shear: 50/100/50 Average: 67
Absorbed Energy (ft/lbs): 127/179/96 Average: 134
Lateral Expansion (mils): 88/94/75 Average: 86

We hereby certify that the material meets the following
- All fittings and flanges meet NACE MRO-175/ISO 15156-Latest Revision.
- All fittings and flanges meet NACE MRO-103 - Latest Revision.
- All non high-yield fittings meet the requirements of ASTM A-234 WPB / ASME SA-234
- All non high-yield flanges meet the requirements of ASTM A-105 WPB / ASME SA-105
- All elbows, tees and reducers are seamless, except as noted.
- Plate for caps and welded fittings.
- Bars, Billets or Blooms for flanges and certain caps and tees.
- MTR only valid with QR code linking to traceability.weldbend.com

† This indicates that the reported yield is capped at 50,000 psi.

Copyright © 2023 Weldbend Corp.

Cert #136726

Richard Purpura

Richard Purpura
Quality Assurance Department
7/17/2026

Scan For Online Report

We hereby certify that the material meets the following:
- ISO 9001:2015 CERTIFIED MANUFACTURER
- Test Results herein are correct as contained in test records retained by the company in accordance with PED Annex 1, Paragraph 4.3 of 2014/68/EU
- No Weld Repair Performed. No Lead Content. No Mercury Content.
- Knowingly making false, fictitious, or fraudulent statements on a MTR may result in legal liability.
- Material has been manufactured/supplied and tested in accordance with the most current version of the Weldbend Quality System Program
- MTR issued in accordance with EN 10204 paragraph 3.1
- L denotes ladle chemistry, P denotes product chemistry.

Generated by nikki.menard@mavint.com