TRILAD FLANGES AND FITTINGS, INC.

TRILAD FLanges & Fittings
7200 Mykawa Rd
Houston, TX 77033
(PHONE) (713) 679-2891

ALLIED GROUP

ISO 9001

CERTIFIED MATERIAL TEST REPORT

EN 10204 3.1

Date of Report: 07/17/2026 **Certificate No.** FT202601-212-001

Customer: DNOW L.P.
PO BOX 4888
Houston, TX 77210-4888

Cust PO#: 663013418 **PO Line#:** 10
Customer Order No: WOSO1239920-1 **Qty:** 6.00
Allied Fitting, LP SO No: SOM1127503

Item Description: 65Q9WRX16 16 900# RF WN XH F65
Specification: ASTM A694/A694M 2022 F65
Heat C.E.: 0.45

Heat #: TL20074497
Melt Practice: BASIC OXYGEN FURNACE

Heat Treatment	Init Temperature	Tempering Temperature	Time
QUENCHED AND TEMPERED	910 C	550 C	Q=3HRS WC T=4.5HRS AC

Heat Composition

	C	Mn	Si	P	S	Cr	Ni
Heat	0.16	1.31	0.26	0.012	0.004	0.20	0.01
Product							

	Mo	Cu	V	Nb	B
Heat	0.07	0.01	0.06	0.02	0.001
Product					

Mechanical Properties

Tensile Specimen Size: STD
Tensile Specimen Orientation:
Impact Specimen Size: 10 X 10
Impact Specimen Orientation: T

	Hardness	Ultimate Strength	Yield Strength	Elongation	Area Reduction
Base	209 213 HBW	690 Mpa	531 Mpa	20 %	70 %
Weld					
HAZ					

Full Size Charpy

	Impact Value	Shear Fracture	Lateral Expansion	Temperature
Base Value	J 113 104 103	% 60 60 60	MM 1.36 1.22 1.28	-46.00 °C

Notes

ANSI/NACE MR0103-2015/ISO 17945:2015(R2023)
ANSI/NACE MR0175-2021/ISO 15156:2020+ERR:2025
DOMESTIC

Material in accordance with the latest edition of the applicable Standard to which it is ordered including:
ASME Sect II-A, ASME B16.5, B16.36, B16.47, MSS-SP-44.
NO WELD REPAIR **MERCURY FREE RADIATION CONTAMINATION FREE**
Material conforms to both ASTM (A) and ASME (SA) applicable specifications.
We hereby certify that all information presented on this CMTR conforms to the above specification.

Troy Gorrell
Q.C Inspector