



CERTIFICATE OF CONFORMANCE

[illegible]

Cenia Chavarria

AUTHORIZED SIGNATURE

CLIENTE / Customer / Client
INDUSTRIAL VALCO (HSTN)
635 GELLHORN
HOUSTON, TX 77029
USA

CERTIFICADO DE INSPECCION

Inspection Certificate - Certificat de Réception

FECHA: 06/06/2023
Date: 06/06/2023

N.º No. 225609

HOJA: Page: 2

Company management certifications:

ISO 9001: 2015
ISO 14001: 2015
ISO 45001: 2018



ULMA FORJA, S.COOP.

Management Systems certified by LRQAE

Certified acc. PED 2014/68/EU+AD2000-W0
by TÜV Rheinland
N.º 01 202 E/Q 02 7443

UNE EN 10204-06 / 3.1
ISO 10474:13 / 3.1

Bº Zubillaga, 3 - Apdo. 14
20560 ONATI (Gipuzkoa) SPAIN
Tel.: 34 - 943 780552
Fax: 34 - 943 781808
E-mail: ulma@ulmaforge.com

MARCA DEL FABRICANTE

Mark of factory
Marque du fabricant



Packing List: 176779
Expedition : 429784

DEPARTAMENTO

Section
Département

QUALITY ASSURANCE

PRODUCTO
Article - Produit

FLANGES

SU PEDIDO N.º
Your Order No.
Votre Cde. N.º

UL112HA HOUSTON

DE
of. - de 23/11/2022

NORMAS APLICABLES
Requirements - Normes Applicables

ASME B16.5-20

MATERIAL CORRESPONDIENTE ASME SA105M-21, ASTM A105M-21, EN 10222-2 P280GH-17.

Material Correspondent - Qualité

MODO DE FUSION (*)

Steel Making - Elaboration de l'acier

E = Elec. Y = Oxígeno básico

ANSI/NACE MR0175-2021/ISO 15156:2020 & ANSI/NACE MR0103/ISO 17495:2015

PARTIDA Item Poste	CANTIDAD Quantity Quantité	DESCRIPCION Description Description	OBSERVACIONES Remarks Observations (*)	COLADA N.º Heat No N.ºCoulée	RESISTENCIA		LIMITE ELAST	ALARGAM. Elongation Allongement Lo:50mm/4d	ESTRICCION	RESILIENCIA			CHARPY V 10x10mm		DUREZA
					T.Strength	Y.Strength	Red. Area	Impact test			Hardness Dureté HBW				
					Resist Rupt N/mm2	0.2 % N/mm2	%	Résilience Joules	MEDIA Average Moyenne	°C					
35 225B-E:AP	43	LJ 3/4 150LB A105N	05S904 NE	B95A9	491	286	35,24	72,56	92	94	71	86	-29	149 152	
35 225B-E:AP	17	LJ 3/4 150LB A105N	06F312 NE	F1AV22	511	331	31,71	69,40	107	93	78	93	-29	143 146	
45 2BF08:AP	24	WN 8 600LB STD/40 RF A105N	08Y301 NE	22AV23	507	280	32,90	70,33	52	54	56	54	-29	149 149	
45 2BF08:AP	24	WN 8 600LB STD/40 RF A105N	08Y303 NE	22AV23	507	280	32,90	70,33	52	54	56	54	-29	149 149	
51 2BGD04:AP	15	WN 4 900LB XS/80 RF A105N	28N215 NE	032A22	538	346	36,07	75,68	127	94	112	111	-29	152 156	
52 2BHB01:AP	21	WN 1 1500LB STD/40 RF A105N	29O208 NE	02NC0	496	297	37,19	73,24	112	105	99	105	-50	146 149	
52 2BHB01:AP	4	WN 1 1500LB STD/40 RF A105N	23O103 NE	61AV0	514	320	36,14	75,17	125	139	117	127	-29	143 146	
54 2BHD25:AP	3	WN 2.1/2 1500LB XS/80 RF A105N	19Y002 NE	21AV9	507	314	36,23	68,61	96	102	119	106	-29	143 146	
54 2BHD25:AP	1	WN 2.1/2 1500LB XS/80 RF A105N	30E923 NE	C81A8	505	312	34,75	72,87	132	130	92	118	-29	142 147	

COLADA N.º Heat No Ladle: L Product: P		COMPOSICION QUIMICA - STEEL MAKER'S LADLE ANALYSIS - ANALYSE CHIMIQUE															Origin of Steel	
		C %	Si %	Mn %	P %	S %	Cr %	Ni %	Mo %	Nb %	V %	Cu %	Al %	Ti %	Ca %	B %		CEq %
B95A9	L	0,190	0,201	1,136	0,012	0,004	0,039	0,037	0,013	0,001	0,002	0,047	0,025	0,002	0,002	0,0002	0,40	Germany
F1AV22	L	0,181	0,250	1,100	0,009	0,005	0,130	0,100	0,030	0,003	0,003	0,190	0,031	0,004	0,001	0,0001	0,42	Italy
22AV23	L	0,173	0,220	1,120	0,011	0,003	0,130	0,090	0,020	0,002	0,003	0,140	0,028	0,003	0,003	0,0001	0,41	Croatia
032A22	L	0,179	0,210	1,120	0,010	0,002	0,100	0,110	0,015	0,001	0,003	0,240	0,036	0,001	0,003	0,0003	0,41	France
02NC0	L	0,180	0,197	1,228	0,007	0,004	0,040	0,038	0,011	0,000	0,002	0,060	0,029	0,001	0,002	0,0004	0,40	Germany
61AV0	L	0,179	0,240	1,100	0,009	0,003	0,140	0,080	0,020	0,003	0,004	0,130	0,030	0,003	0,001	0,0001	0,41	Italy
21AV9	L	0,180	0,200	1,210	0,009	0,008	0,090	0,060	0,010	0,001	0,002	0,080	0,024	0,002	0,003	0,0000	0,41	Italy
C81A8	L	0,188	0,207	1,160	0,011	0,003	0,058	0,050	0,011	0,001	0,002	0,074	0,029	0,001	0,002	0,0002	0,40	Germany

- Las dimensiones y la condición superficial se hallaron satisfactorias.
- Dimension and surface condition were found acceptable.
- Les dimensions et états de surface sont satisfaisants.

- Los materiales citados cumplen las normas aplicables.
- Manufacturing requirements are satisfied.
- Les normes applicables sont respectées.

EL INSPECTOR
Works Inspector - L'Inspecteur



(*) OBSERVACIONES:
Remarks
Observations

FLANGES ARE FULLY KILLED AND FINE GRAIN PRACTICED
N.º NORMALIZED ABOVE 900°C AND COOLED IN AIR.