



CERTIFICATE OF CONFORMANCE

[illegible]

Cenia Chavarria

AUTHORIZED SIGNATURE

CLIENTE / Customer / Client
DODSON GLOBAL, INC.
 P.O. Box 330759
 77233 Houston
 Texas
 USA

CERTIFICADO DE INSPECCION
 Inspection Certificate - Certificat de Réception

FECHA: N.º
 Date: 21/10/2025 No. 238097

Company management certifications:

ISO 9001: 2015
 ISO 14001: 2015
 ISO 45001: 2018



ULMA FORJA, S.COOP.

Management Systems certified by LRQAE

Certified acc. PED 2014/68/EU+AD2000-WO
 by TÜV Rheinland
 N.º 01 202 E/Q 02 7443
 UNE EN 10204:06 / 3.1
 ISO 10474:13 / 3.1

Bº Zubillaga, 3 - Apdo. 14
 20560 ONATI (Gipuzkoa) SPAIN
 Tel.: 34 - 943 780552
 Fax: 34 - 943 781808
 E-mail: ulma@ulmaforge.com

MARCA DEL FABRICANTE

Mark of factory
 Marque du fabricant



Packing List: 193018
 Expedition: 679448

DEPARTAMENTO
 Section
 Département

QUALITY ASSURANCE

PRODUCTO FLANGES SU PEDIDO N.º
 Article - Produit Your Order No. 432628-48
 NORMAS APLICABLES ASME B16.5-20
 Requirements - Normes Applicables Votre Cde. N.º

MATERIAL CORRESPONDIENTE ASME SA105M-23, ASTM A105M-24, EN 10222-2 P280GH-17.
 Material Correspondent - Qualité
 MODO DE FUSION (*) ANSI/NACE MR0175-2021/ISO 15156:2020 & ANSI/NACE MR0103/ISO 17945:2015
 Steel Making - Elaboration de l'acier
 EAF(Electric Arc Furnace)

PARTIDA Item Poste	CANTIDAD Quantity Quantité	DESCRIPCION Description Description	OBSERVACIONES Remarks Observations (*)	COLADA N.º Heat No N.ºCoulée	RESISTENCIA T.Strength Resist Rupt N/mm2	LIMITE ELAST. Y.Strength 0.2 % N/mm2	ALARGAM. Elongation Allongement Lo:50mm/4d %	ESTRICCION Red. Area Striction %	RESILIENCIA Impact test Résilience Joules	PROBETA - SPECIMEN CHARPY V 10x10mm MEDIA Average Moyenne °C	DUREZA Hardness Dureté HBW
5	35	SW 2 300LB XS/80 FF A105N	19Y502	EAF	05HC25	509	327	38,70	73,16	122 145 131	133 -29 143 146
57	26	SW 2 300LB STD/40 RF A105N	19Y502	EAF	05HC25	509	327	38,70	73,16	122 145 131	133 -29 143 146
106	4	WN 4 900LB XS/80 RF A105N B16.5	18M515	EAF	02HC25	542	343	35,60	73,66	119 111 121	117 -29 143 146
106	9	WN 4 900LB XS/80 RF A105N B16.5	19M501	EAF	02HC25	542	343	35,60	73,66	119 111 121	117 -29 143 146
106	32	WN 4 900LB XS/80 RF A105N B16.5	22L510	EAF	07HC25	519	339	33,80	72,11	127 158 124	136 -29 143 146
107	60	WN 4 900LB S120 RF A105N	25G506	EAF	89EE25	531	365	34,60	71,19	67 68 55	63 -29 149 152

COLADA N.º Heat No Ladle: L Product: P	COMPOSICION QUIMICA - STEEL MAKER'S LADLE ANALYSIS - ANALYSE CHIMIQUE																	
	C %	Si %	Mn %	P %	S %	Cr %	Ni %	Mo %	Nb %	V %	Cu %	Al %	Ti %	N %	Ca %	B %	CEq %	Melt/Pour Origin
05HC25 L	0,182	0,200	1,054	0,010	0,002	0,072	0,126	0,029	0,001	0,002	0,181	0,031	0,001	0,0052	0,002	0,0002	0,40	Germany
02HC25 L	0,188	0,190	1,120	0,011	0,005	0,070	0,080	0,010	0,001	0,003	0,160	0,029	0,001	0,0099	0,005	0,0000	0,41	France
07HC25 L	0,181	0,210	1,110	0,012	0,005	0,090	0,080	0,012	0,001	0,002	0,180	0,023	0,002	0,0063	0,002	0,0002	0,40	France
89EE25 L	0,190	0,250	1,050	0,014	0,003	0,120	0,050	0,010	0,001	0,002	0,150	0,026	0,018	0,0100	0,001	0,0002	0,40	Italy

- Las dimensiones y la condición superficial se hallaron satisfactorias.
 - Dimension and surface condition were found acceptable.
 - Les dimensions et états de surface sont satisfaisants.

- Los materiales citados cumplen las normas aplicables.
 - Manufacturing requirements are satisfied.
 - Les normes applicables sont respectées.

DIRECTOR DE CALIDAD
 Quality Director - Directeur de la Qualité



(*) OBSERVACIONES:
 Remarks
 Observations
 FLANGES MANUFACTURED IN SPAIN.
 STEEL IS FULLY KILLED AND MELTED TO FINE GRAIN PRACTICE.
 N_NORMALIZED ABOVE 900°C (≥30min/inch) & COOLED IN AIR.