



VIRGILIO CENA & FIGLI S.p.A.

www.cenafittings.com
Via G. Oberdan, 39 – 25128 – BRESCIA (ITALY)

QMS approved acc.to ISO 9001:2015
LRQA Cert. N° 10082605 according to
Annex I, Chapt. 4.3 PED 2014/68/EU

Issued in agreement with TÜV SÜD Industrie
Service GmbH (05.1992) and approved according
to PED, annex I, para 4.3 by Notified body 0036,
cert. n. DGR-QS-W 024/2002/MUC-001

INSPECTION CERTIFICATE EN 10204/3.1

CE23012483_3.1_01

Customer Order

317553+add.

Your Item Ref.

8

CENA FITTINGS USA, LLC

400 N. SAM HOUSTON PARK EAST

Houston (Texas), 77060

United States of America

Article/Specification

Seamless caps
WPHY52 ASTM A860/A860M-18, MSS SP75-19, WPL6 ASTM A420/A420M-19, ASME II Part.A-2019 SA420/SA420M, ASME B16.9-18, NACE
MR0175/ISO15156-2015 NACE MR0103/ISO17945-2016 ASME II Part.D Tab.Y1

Heat Treatment

Hot formed at 780°C to 920°C - Water quenched at 920°C, 1,5/mm - Tempered at 590°C, holding 3'/mm

Brand of manufacturer

CENA

Marking

Manufacturer - A860 WPHY52 - Heat Nr - Od. x Th. - ITALY

Extent of material delivered

Our pos.

Quantity

Article

OV22000598/80000

NR 10

10" XH CAP A860/MSS SP-75/A420 WPHY52/WPL6 HTS CODE 7307.93.30.40

Heat

1TAT11

Marking code

1TAT11

Certificate

504308 *

Supplier

METINVEST TRAMETAL SPA

Raw material

Hot rolled plates P355NL2 EN 10028-3

Results of chemical analysis %

Ceq: C+ (Mn/6) + (Cr+Mo+V)/5 + (Cu+Ni)/15

	C	Mn	Si	P	S	Cu	Ni	Cr	Mo	Al	Ti	Nb	V	N	B	Ceq	Pcm	Jfact.
min.			0,1500							0,0200								
max.	0,2500	1,6000	0,4500	0,0250	0,0150	0,4500	0,5000	0,2500	0,2500	0,0600	0,0400	0,1000	0,1100		0,00050	0,4200		
Ladle	0,15	1,37	0,18	0,014	0,003	0,03	0,02	0,04	0,005	0,037	0,005	0,010	0,005	0,009	0,0003	0,38		
Check	0,15	1,36	0,17	0,013	0,004	0,028	0,018	0,04	0,003	0,035	0,004	0,008	0,004	0,008	0,0004	0,38		

Mechanical Tests: On fittings

Specimen	Position	Direction	Temperature °C	Dimension mm	Yield Point N/mm²	Tensile Strength N/mm²	Elongation %	Ys ----- Ts	Hardness HB 10% of batch 3 tests min.	Impact Test - Specimen = KV										
										Position	Direction	Temperature °C	Dimension mm	Obtained energy				Shear Area		
														Joule				%		
														Values		Average	Values			
25802.1.0	A	T	20	19,2x10,7	430	574	34	0,75	167-171	A	T	-50	10x10	217,0	216,0	216,0	216,3	85	85	85

The pipes are tested on tightness.

Steel making process: Basic oxygen

Specimen position: A=neutral axis of base material; W=weld; E=extrados of base material; I=intrados of base material; Z=heat affected zone

Results of visual and dimensional inspection of fittings: SATISFACTORY Supplied products are in compliance with the requirements of the order The values of elongation and impact-test are according to PED 2014/68/UE The steel is fully killed and produced to a fine grain practice No weld repair, mercury and radiation free

25802.1.0: Rp = 62366 psi - Rm = 83252 psi - Lateral Expansion (mils): L1=82 L2=82 L3=82

Country of origin of fittings: Italia

Country of origin of raw material: Italia

The material referenced herein is not of Russian origin and does not incorporate any material originating from or processes carried out in Russia.

Date

11/12/23

DTV2302585

Inspection

Quality Control Manager

BUTTURINI RICCARDO

THIS DOCUMENT HAS BEEN ISSUED WITH THE INFORMATIC HELP
AND IT IS VALID WITHOUT A SIGNATURE
MODIFICATIONS OR ELSE OTHER PRODUCTS USE WILL BE PERSECUTED ACCORDING TO THE LAW
AS FALSIFICATION OF DOCUMENTS OR FRAUD.