



CERTIFICATE OF CONFORMANCE

AUTHORIZED SIGNATURE

CLIENTE / Customer / Client
DODSON GLOBAL, INC.
PO BOX 330759
HOUSTON, TEXAS 77233
USA
USA

CERTIFICADO DE INSPECCION
Inspection Certificate - Certificat de Réception

FECHA: 14/10/2024
Date: 14/10/2024
N.º No. 232732

HOJA: Page:

Company management certifications:

ISO 9001: 2015
ISO 14001: 2015
ISO 45001: 2018



ULMA FORJA, S.COOP.

Management Systems certified by LRQAE

Certified acc. PED 2014/68/EU+AD2000-W0
by TÜV Rheinland
N.º 01 202 E/Q 02 7443

UNE EN 10204:06 / 3.1
ISO 10474:13 / 3.1

MARCA DEL FABRICANTE
Mark of factory
Marque du fabricant



Bº Zubillaga, 3 - Apdo. 14
20560 ONATI (Gipuzkoa) SPAIN
Tel.: 34 - 943 780552
Fax: 34 - 943 781808
E-mail: ulma@ulmaforge.com

Packing List: 186307
Expedition: 498468

PRODUCTO
Article - Produit

FLANGES

SU PEDIDO N.º
Your Order No. 396998-408
Votre Cde. N.º

DE
of. - de 28/08/2024

NORMAS APLICABLES
Requirements - Normes Applicables

ASME B16.5-20

MATERIAL CORRESPONDIENTE
Material Correspondent - Qualité

ASME SA105M-23, ASTM A105M-24

MODO DE FUSION (*)
Steel Making - Elaboration de l'acier
EAF (Electric Arc Furnance)

ANSI/NACE MR0175-2021/ISO 15156:2020 & ANSI/NACE MR0103/ISO 17945:2015

DEPARTAMENTO
Section
Département

QUALITY ASSURANCE

PARTIDA Item Poste	CANTIDAD Quantity Quantité	DESCRIPCION Description Description	OBSERVACIONES Remarks Observations (*)	COLADA N.º Heat No N.ºCoulée	RESISTENCIA T.Strength Resist Rupt N/mm2	LIMITE ELAST Y.Strength 0.2 % N/mm2	ALARGAM. Elongation Allongement Lo:50mm/4d %	ESTRICCION Red. Area Striction %	RESILIENCIA Impact test Résilience Joules	PROBETA - SPECIMEN CHARPY V 10x10mm			DUREZA Hardness Dureté HBW
										MEDIA Average Moyenne	°C		
206	62	WN 8 300LB XS/80 RF A105N	25S410 EAF	83EE24	507	326	36,90	66,11	133 131 130	131	-29	144 145	
206	17	WN 8 300LB XS/80 RF A105N	25S412 EAF	83EE24	507	326	36,90	66,11	133 131 130	131	-29	144 145	
206	41	WN 8 300LB XS/80 RF A105N	26S406 EAF	83EE24	507	326	36,90	66,11	133 131 130	131	-29	144 145	
208	30	WN 10 300LB XS/60 RF A105N B16.5	18S404 EAF	13HC24	528	341	35,70	73,19	72 65 67	68	-29	146 149	
232	30	WN 4 900LB XS/80 RF A105N	16S408 EAF	20HC24	531	339	36,90	73,43	107 114 95	105	-29	146 149	

COLADA N.º Heat No Ladle: L Product: P		COMPOSICION QUIMICA - STEEL MAKER'S LADLE ANALYSIS - ANALYSE CHIMIQUE																	
		C %	Si %	Mn %	P %	S %	Cr %	Ni %	Mo %	Nb %	V %	Cu %	Al %	Ti %	N %	Ca %	B %	CEq %	Origin of Steel
83EE24	L	0,180	0,180	1,138	0,014	0,001	0,080	0,075	0,016	0,001	0,002	0,125	0,030	0,002	0,0043	0,001	0,0004	0,40	France
13HC24	L	0,186	0,250	1,180	0,013	0,002	0,050	0,080	0,010	0,001	0,004	0,170	0,035	0,002	0,0087	0,002	0,0003	0,41	France
20HC24	L	0,185	0,230	1,120	0,011	0,005	0,070	0,080	0,015	0,001	0,001	0,180	0,029	0,002	0,0071	0,002	0,0001	0,41	France

- Las dimensiones y la condición superficial se hallaron satisfactorias.
- Dimension and surface condition were found acceptable.
- Les dimensions et états de surface sont satisfaisants.

- Los materiales citados cumplen las normas aplicables.
- Manufacturing requirements are satisfied.
- Les normes applicables sont respectées.

DIRECTOR DE CALIDAD
Quality Director - Directeur de la Qualité



(*) OBSERVACIONES:
Remarks
Observations
STEEL IS FULLY KILLED AND MELTED TO FINE GRAIN PRACTICE.
N_NORMALIZED ABOVE 900°C (≥30min/inch) & COOLED IN AIR.