




DL FLANGE

ISO 9001

DL Flange
7200 Mykawa Rd.
Houston, TX 77033



CERTIFIED MATERIAL TEST REPORT EN 10204 3.1

Date of Report: 12/30/2025

Certificate No. 30023997

Page 1 of 1

Customer:

Cust PO#:

Customer Order No: WO36306

Qty: 18.00

Allied Fitting, LP SO No:

Item Description: 5Q9WRS6 6 900# RF WN STD F52

Heat #: DL83600 ✓

Specification: ASTM A694/A694M 2022 F52

Heat C.E.: 0.41

Melt Practice: ELECTRIC FURNACE

Heat Treatment

Init Temperature

Tempering Temperature

Time

QUENCHED AND TEMPERED

910 C

605 C

Q=2.30HRS T=3.30HRS

Heat Composition

Heat Product	C 0.20	Mn 1.25	Si 0.19	P 0.018	S 0.008	Cr 0.01	Ni 0.00
Heat Product	Mo 0.00	Cu 0.00	V 0.00	Nb 0.00	B 0.000		

Mechanical Properties

Tensile Specimen Size: STD

Tensile Specimen Orientation:

Impact Specimen Size: 10 X 10

Impact Specimen Orientation: T

	Hardness	Ultimate Strength	Yield Strength	Elongation	Area Reduction
Base Weld HAZ	178 180 HBW	585 Mpa	408 Mpa	30 %	73 %

Full Size Charpy

	Impact Value	Shear Fracture	Lateral Expansion	Temperature
Base Value	J 82 79 82	% 57 59 55	MM 0.03 0.02 0.03	-46.00 °C

Notes

NACE MR0103/ISO17945:2015 (R2023)
NACE MR0175-2021/ISO15156-1:2020
DOMESTIC

Material in accordance with the latest edition of the applicable Standard to which it is ordered including:

ASME Sect II-A, ASME B16.5, B16.36, B16.47, MSS-SP-44.

NO WELD REPAIR

MERCURY FREE RADIATION CONTAMINATION

FREE

Material conforms to both ASTM (A) and ASME (SA) applicable specifications.

We hereby certify that all information presented on this CMTR conforms to the above specification.

Troy Gorrell

Q.C Inspector