

BENTELER Steel/Tube
1 Benteler Drive|Shreveport|LA 71115|USA
Tel.: +1 318-216-4215
qms.shreveport@benteler.com

26797600

BENTELER 
Steel/Tube

INSPECTION CERTIFICATE EN 10204-3.1
EN 10204:2005-01

Document No.: 465-1603493/001/E
Purchase Order No.: 26797600
Benteler Order No.: 48011314
Dispatch Note No.:
Product: SEAMLESS STEEL TUBES

Inspection No.: Page: 1 / 3
Manufacturer: BSTMC Shreveport USA
Manufacturer's brand: 
Stamp of the inspection representative: MI
Steelmaking process: ELECTRIC FURNACE

DNOW L.P.
7402 N. Eldridge Parkway
HOUSTON TX 77041
USA

Terms of delivery: ASTM-A 53-2024, ASME SA-53, ASME BPVC.II.A-2025, ASTM-A 106-19a, ASME SA-106, ASME BPVC.II.A-2025, API Specification 5L
Forty-Sixth Edition April 2018 incl. Errata 1, May 2018, PSL 2, ANSI/NACE MR0175-2021/ISO 15156-1:2020, ANSI/NACE MR0175-2021/ISO
15156-2:2020, ANSI/NACE MR0103/ISO 17945:2015, ASME B36.10-2022

Dimensions-tolerances: ASTM-A 106-19a, ASME SA-106, ASME BPVC.II.A-2025, ASTM-A 53-2024, ASME SA-53, ASME BPVC.II.A-2025, API Specification 5L
Forty-Sixth Edition April 2018 incl. Errata 1, May 2018

Steel grade: GRADE B, GRADE C, GRADE BN, GRADE X42N

Delivery condition: N

Product marking: S: BENTELER - BENTELER-Sign - API 5L 1072 - API-Sign - Month/Year - A/SA 53 A/SA 106 NACE - 4,500" OD x
0,337" WT - B/C/BN/X42N - PSL2 - SMLS - Heat No. - Tube length feet - 2.970 - 15049473 - LONGHORN

AEZ = Etching ink marking FK = color marking FS = paint stenciling FSD = Color Jet printer FSI = Color Jet printer inside LK = Laser marking PKE = tag marking PS = die stamp TS = Ink Jet spray marking

Item	Dimensions	Heat No.	Test pressure	
			PSI	sec
0020	4 NPS - SCH 80 35,000 FT - 45,000 FT	1161795	325163	2970 5

Country of melt and pour

Melted & Manufactured in USA
Nucor, Jewett, TX, US

Heat analysis [%]

Item	Heat No.	C	SI	MN	P	S	CR	MO	NI	CU	V	NB	TI	B
0020	325163	0.160	0.281	0.99	0.010	0.002	0.15	0.02	0.08	0.20	0.002	0.001	0.002	0.0003

- Formula: $CE_{IIW} = C + (Mn/6) + ((Cr+Mo+V)/5) + ((Cu+Ni)/15) \leq 0.43 \%$
- Formula: $Cr+Cu+Mo+Ni+V \leq 1.00 \%$
- Formula: $Nb+V \leq 0.06 \%$
- Formula: $Nb+Ti+V \leq 0.15 \%$

INSPECTION CERTIFICATE EN 10204-3.1

Document No.:

465-1603493/001/E

Inspection No.:

Page: 2 / 3

Formula results

Item	Heat No.	1. Formula	2. Formula	3. Formula	4. Formula
0020	325163	0,378	0,452	0,003	0,005

Product analysis [%]

Item	Heat No.	C	SI	MN	P	S	CR	MO	NI	CU	V	NB	TI	B
0020	325163	0.170	0.290	0.99	0.010	0.001	0.15	0.02	0.07	0.20	0.003	0.001	0.003	0.0002
0020	325163	0.170	0.290	0.99	0.010	0.001	0.15	0.02	0.07	0.20	0.003	0.001	0.003	0.0003

1. Formula: $CE_{IIW} = C + (Mn/6) + ((Cr+Mo+V)/5) + ((Cu+Ni)/15) \leq 0,43 \%$

2. Formula: $Cr+Cu+Mo+Ni+V \leq 1.00 \%$

3. Formula: $Nb+V \leq 0.06 \%$

4. Formula: $Nb+Ti+V \leq 0.15 \%$

Formula results

Item	Heat No.	1. Formula	2. Formula	3. Formula	4. Formula
0020	325163	0,388	0,443	0,004	0,007
0020	325163	0,388	0,443	0,004	0,007

Test results

The tubes have been submitted to a leak tightness test by:	Hydrostatic test: acc. to API 5L; Test pressure/Time-record, the test records/charts shall be available for examination by the inspector	PASSED
The tubes are non destructive tested:	ET - Test standard: acc. to API 5L; ET - Test method: acc. to ASTM-E 309; ET - Test drilled hole: 0,125 IN.; ET - Notch shape/hole: drilled hole	PASSED
Visual inspection:	PASSED	Dimensions examination: PASSED

Results of mechanical testing

Tensile test longitudinal at RT, Strip test specimen

Item	Specimen No.	Heat No.	Specimen dimensions	Yield strength	Tensile strength	Elongation	1. Formula	Rt 0,5/Rm
Requirements			IN	RT 0,5 % PSI 42100-71800	Rm PSI 70000-95000	A2" %		MAX 0,93
0020	000011	325163	0,997 X 0,338	51053	77595	34,00	22,00	0,66

Elongation formula

1. Formula $AF = 625000 * AXC^{0,2} / U^{0,9}$

INSPECTION CERTIFICATE EN 10204-3.1

Document No.:

465-1603493/001/E

Inspection No.:

Page: 3 / 3

Notched bar impact test [1 CHARPY_V]

Specimen position: longitudinal (L); Test temperature: -50 °F

Item	Specimen No.	Heat No.	Specimen dimensions			Absorbed energy		Impact strength	Shear fracture	
			Length	Width	Height	single	average		single	average
			mm	mm	mm	ft-lbf	ft-lbf		%	%
			55	6,67	10,00		MIN 000			
0020	000011	325163	55	6,67	10,00	49			20	
				6,67	10,00	415			20	
				6,67	10,00	45			20	20

Protection

outside surface varnished

Item	Heat No.	Production No.
0020	325163	15049473

Remark

NACE Standard: Hardness acc. to ANSI/NACE MR0175/ISO 15156: HRC max 22 as per ASTM A370 table 2&3., Hardness acc. to ANSI/NACE MR0103/ISO 17945: HRC max. 22 as per ASTM A370 table 2&3.; Certificate remarks: material free from mercury contamination, Material must be suitable for external fusion bond coating., Data converted from SI units, No weld repair has been carried out; Certificate-Remark: LONGHORN