



2669 Martin Luther King Jr Blvd  
Youngstown, OH 44510

# 1-Piece of Pipe

## VALLOUREC STAR LP

Seamless Tubular Products

Certified Test Report  
10/22/2025  
Revision: 0

Order: Y-221130322-001

Desc: Seamless Line Pipe - As Rolled

Customer: Kelly Pipe Company

SLN / (Heat): PJ0438

Grade: API 5L X42/B N/BN PSL2 46th Edition May 01, 2019

Customer Order: 10P46177

Split: 00

OD(in): 4.500

Wall(in): 0.337

Lbs/Ft: 15.00

Length: Double Random

End Finish: Plain End Beveled

Comments: Melted and Manufactured in Youngstown, Ohio USA

Pipe is also manufactured to: ASTM A106B/C-19a, ASTM A53B-24, ASME SA106B/C-2023, ASME SA53B-2023. Vallourec Star's QA program meets the requirements of Directive 2014/68/EU and DIN EN10204-2004 Type 3.1. Satisfies NACE MR0175-2021/15156-1 2020 and ANSI/NACE MR0103/ISO17945:2015(R2023). Material has been produced using silicon killed carbon steel with aluminum fine grain practice. No repair welding has been conducted. Material is free from Mercury. API MONOGRAMMED

### Mechanical Properties

|                                                  |       | Tensile Size<br>Specimen Cross Section |            |             | Strength (ksi)                                 |         |           | Elongation                                |         |      |
|--------------------------------------------------|-------|----------------------------------------|------------|-------------|------------------------------------------------|---------|-----------|-------------------------------------------|---------|------|
| Orientation                                      | Type  | Width (in)                             | Thick (in) | Area (sqin) | Yield                                          | Tensile | Y/T Ratio | Gage Length                               | % Elong | % RA |
| Longitudinal                                     | Strip | 1.000                                  | 0.350      | 0.3600      | 46.7                                           | 73.3    | 0.64      | 2                                         | 37.6    | 58.7 |
| Required Min/Max Yield Strength (ksi): 42.1/71.8 |       |                                        |            |             | Required Min/Max Tensile Strength (ksi): 70/95 |         |           | Calculated Max Internal Yield (psi): 6127 |         |      |

Required Min Elongation(%): 30

### Supplemental Requirements

|                       |               |
|-----------------------|---------------|
| Flattening Test       | Passed        |
| Hardness 3 Point      | 76.7 avg HRBW |
| Hydrostatic Pressure  | 4730 psi      |
| Hydrostatic Hold Time | 5 seconds     |

### Chemical Analysis

Chem Spec: 61M

| WT%       | C    | Mn   | P     | S     | Si   | Cu   | Ni   | Cr   | Mo   | Sn    | Nb    | V     | Al    | Ca     | B      | Ti    | N      | C.E. |
|-----------|------|------|-------|-------|------|------|------|------|------|-------|-------|-------|-------|--------|--------|-------|--------|------|
| Heat      | 0.19 | 0.73 | 0.008 | 0.006 | 0.21 | 0.18 | 0.06 | 0.09 | 0.02 | 0.009 | 0.000 | 0.002 | 0.025 | 0.0014 | 0.0004 | 0.002 | 0.0088 | 0.35 |
| Product 1 | 0.20 | 0.73 | 0.008 | 0.005 | 0.22 | 0.17 | 0.06 | 0.09 | 0.03 | 0.007 | 0.000 | 0.002 | 0.026 | 0.0013 | 0.0002 | 0.002 | 0.0089 | 0.36 |
| Product 2 | 0.20 | 0.72 | 0.008 | 0.006 | 0.21 | 0.16 | 0.06 | 0.09 | 0.03 | 0.008 | 0.000 | 0.002 | 0.027 | 0.0014 | 0.0002 | 0.002 | 0.0087 | 0.36 |

### Charpy Impact Testing - Not required per API.

This material has been produced and tested in accordance with the requirements of applicable specifications unless otherwise listed below. We hereby certify that the above test results are representative of those contained in the records of the company. Any modification to this certification as provided by Vallourec Star without the expressed written consent of Vallourec Star negates the validity of this test report. Vallourec Star is not responsible for the inability of this material to meet specific applications. THIS CERTIFICATE IS NOTARIZED ONLY WHEN REQUESTED.

Signed: *Jeff Schultz*

Name: Jeff Schultz, Lab Supervisor

Date Approved: 10/22/2025

This document is uncontrolled when printed. Always refer to the MTR System for the most current version. FS-VMS-8.2.4.1.1 Rev 7



2669 Martin Luther King Jr Blvd  
Youngstown, OH 44510

**VALLOUREC STAR LP**  
Seamless Tubular Products

Certified Test Report  
10/22/2025  
Revision: 0

Order: Y-221130322-001

Desc: Seamless Line Pipe - As Rolled

Customer: Kelly Pipe Company

SLN / (Heat): PJ0438

Grade: API 5L X42/B N/BN PSL2 46th Edition May 01, 2019

Customer Order: 10P48177

Split: 00

OD(in): 4.500

Wall(in): 0.337

Lbs/Ft: 15.00

Length: Double Random

End Finish: Plain End Beveled

Inspection Company: L Bay

**Non-Destructive Evaluation Criteria**

**EMI CHANNELS**

ID

10% Longitudinal

10% Transverse

OD

10% Longitudinal

10% Transverse

**FULL LENGTH WALL THICKNESS CHECK**

Wall

87.5% Wall Reduction

Required Volumetric Coverage: 50%

**ADDITIONAL REQUIREMENTS**

Notch Length  $\leq 1.00"$

Notch Width .020" Max

Untested Ends Cropped

OD

Visual Insp. Full Length - White Light

ID

Visual Insp. Pipe Ends - White Light