




TRILAD Flanges & Fittings

7200 Mykawa Rd
Houston, TX 77033
(PHONE) (713) 679-2891



ISO 9001

CERTIFIED MATERIAL TEST REPORT

EN 10204 3.1

Page 1 of 1

Date of Report: 07/29/2026

Certificate No. WP-1532/25-26

Customer: DNOW L.P.
PO BOX 4888
Houston, TX 77210-4888

Cust PO#: 663020224

Customer Order No: WOSO1245772-1

PO Line#: 10

Qty: 1.00

Allied Fitting, LP SO No: SOM1132774

Item Description: 5Q9WRS6 6 900# RF WN STD F52

Heat #: TL20076117

Specification: ASTM A694/A694M 2022 F52

Heat C.E.: 0.43

Melt Practice: ELECTRIC FURNACE

Heat Treatment

Init Temperature

Tempering Temperature

Time

QUENCHED AND TEMPERED

920 C

590 C

Q=3.30HRS T=3HRS

Heat Composition

Heat Product	C 0.18	Mn 1.26	Si 0.25	P 0.022	S 0.006	Cr 0.16	Ni 0.01
Heat Product	Mo 0.00	Cu 0.01	V 0.00	Nb 0.00	B 0.000		

Mechanical Properties

Tensile Specimen Size: STD

Tensile Specimen Orientation:

Impact Specimen Size: 10 X 10

Impact Specimen Orientation: T

	Hardness	Ultimate Strength	Yield Strength	Elongation	Area Reduction
Base Weld HAZ	170 180 HBW	559 Mpa	389 Mpa	29 %	77 %

Full Size Charpy

	Impact Value	Shear Fracture	Lateral Expansion	Temperature
Base Value	J 88 90 92	% 60 65 65	MM 0.90 0.90 0.95	-46.00 °C

Notes

ANSI/NACE MR0103-2015/ISO 17945:2015(R2023)
ANSI/NACE MR0175-2021/ISO 15156:2020+ERR:2025
DOMESTIC

Material in accordance with the latest edition of the applicable Standard to which it is ordered including:

ASME Sect II-A, ASME B16.5, B16.36, B16.47, MSS-SP-44.

NO WELD REPAIR
FREE

MERCURY FREE RADIATION CONTAMINATION

Material conforms to both ASTM (A) and ASME (SA) applicable specifications.
We hereby certify that all information presented on this CMTR conforms to the above specification.

Troy Gorrell

Troy Gorrell

Q.C Inspector