



03669

DNow L.P.

Description:

2 X 6 S80 A106B BLK SMLS NPL PXT

***** Specifications - Heat Code W24128: *****

A106-19 GR.B, SA106 GR.B, A234-19 WPB, SA234 WPB, A530,

A733, ASME B36.10, B1.20.1, MSS SP-25, SP-95

STARTING MATERIAL: A106B PIPE & TUBE

Chemical Composition:

C:	Mn:	P:	S:	Si:	Cr:	Ni:	Mo:
0.182	0.830	0.008	0.004	0.200	0.040	0.070	0.020
Cu:	V:	Cb:	Ti:	B:	C.E.:		
0.160	0.024	0.001	0.001	.0002	.352		

Mechanical Properties:

Tensile(PSI):	Yield(PSI):	Elong(%):	Hardness:	Bend:	Hydro(PSI):
75238	52045	34.00	HRB 79-80	PASSED	2970

Comments:

Normalized at 895C for 8 min, air cooled

Product is compliant with NACE MR0175/ISO 15156 / Product is compliant with NACE MR0103.

No weld repair is performed.

The product is free of Mercury contamination.

Tensile test is taken from round specimen.

Yield Strength is determined using 0.2% offset method, unless otherwise specified.

When reported on the MTR: Tensile testing per ASTM E 8, Charpy impact testing per ASTM E 23 and Brinell Hardness Testing per ASTM E 10.

Products are manufactured in compliance to EN 10204 Type 3.1.

CERTIFIED TO A/SA53-B A/SA106-B/C API 5L -B/X42 PSL 1 (BP 8/29/2025)

We certify only the chemistry and physical results shown for the referenced Heat Code as furnished by the Producing Mill. The Description is the responsibility of the requesting party. This document was electronically transmitted and is in accordance with EN10204 3.1/DIN50049 3.1B.