WELDBEND®

6600 South Harlem Avenue
Argo, IL 60501-1930

Material Test Report

WELDBEND CORPORATION
P O BOX 945650
MAITLAND,FL
PO: S014201970

Quantity	Product	Heat Code	Heat Treatment	Steel Mill
51	4" Class 900 Weld Neck XSB RF	JF2	Heat Treat: Normalized	CMC STEEL

A 105-23
Dimensional Specification: B16.5

	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Al	Ti	B	Cb	CE (IIW)	Tens.	Yield	Elon	ROA	BHN	BHN2
L	0.20	1.05	0.008	0.019	0.20	0.35	0.09	0.05	0.024	0.00	0.000	0.001	0.0006	0.001	0.419	79,100	47,300	31.20	58.00	152	152

A 105

Quantity	Product	Heat Code	Heat Treatment	Steel Mill
8	4" XS Straight Tee	25N46	Heat Treat: Normalized	NIPPON

A 234-18 WPB
Dimensional Specification: B16.9

	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Al	Ti	B	Cb	CE (IIW)	Tens.	Yield	Elon	ROA	BHN	BHN2
L	0.11	1.30	0.011	0.002	0.27	0.02	0.03	0.12	0.010	0.00	0.030	0.010	0.0001	0.000	0.356	70,100	50,000†	34.40	-	153	152

WPB

Quantity	Product	Heat Code	Heat Treatment	Steel Mill
18	4" x 2" XS Reducing Tee	19N78	Heat Treat: Normalized	NIPPON

A 234 WPB-13
Dimensional Specification: B16.9

	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Al	Ti	B	Cb	CE (IIW)	Tens.	Yield	Elon	ROA	BHN	BHN2
L	0.11	1.28	0.018	0.005	0.25	0.01	0.02	0.11	0.010	0.01	-	0.013	0.0000	0.000	0.351	67,300	47,300	37.30	-	133	133

WPB

We hereby certify that the material meets the following
- All fittings and flanges meet NACE MRO-175/ISO 15156-Latest Revision.
- All fittings and flanges meet NACE MRO-103 - Latest Revision.
- All non high-yield fittings meet the requirements of ASTM A-234 WPB (AND SA-234)
- All non high-yield flanges meet the requirements of ASTM A-105 WPB (AND SA-105)
- All elbows, tees and reducers are seamless, except as noted.
- Plate for caps and welded fittings.
- Bars, Billets or Blooms for flanges and certain caps and tees.
- MTR only valid with QR code linking to traceability.weldbend.com

† This indicates that the reported yield is capped at 50,000 psi.

Cert #410240

Richard Purpura

Richard Purpura
Quality Assurance Department
3/10/2025

Scan For Online Report

We hereby certify that the material meets the following:
- ISO 9001:2015 CERTIFIED MANUFACTURER
- Test Results herein are correct as contained in test records retained by the company in accordance with PED Annex 1, Paragraph 4.3 of 2014/68/EU
- No Weld Repair Performed. No Lead Content. No Mercury Content.
- Knowingly making false, fictitious, or fraudulent statements on a MTR may result in legal liability.
- Material has been manufactured/supplied and tested in accordance with the most current version of the Weldbend Quality System Program
- MTR issued in accordance with EN 10204 paragraph 3.1
- L denotes ladle chemistry, P denotes product chemistry.

Generated by nklimala@weldbend.com