**Capitol Manufacturing**
1125 Capitol Avenue
Crowley, LA 70526

*Commanding a Higher Standard℠*

**Phoenix * Capitol * Camco**
**CapProducts**

# Certified Material Test Report

Printed: 7/15/2026 Certified: 03/24/2026

**Customer**
ENVIRONMENTAL AND DEWATERING SOI
4266 28TH STREET

DORR ,MI 49323

4 Pieces

**P.O.** STL-330923
**Tag**
**Material**
ASTM A106B-2019a / ASME SA106B-2023 Edition

**Heat No** 2419517
**Heat Code** 79VX
**Order #** 103796

**Part Number**
15111012PXT

M2413-PRS
SHEET 06

**Description**
1 X 6" XHSML BLK NIP TOE/ SQU

**Chemical Properties**

| C | Mn | P | S | Si | Cu | Ni | Cr |
|---|---|---|---|---|---|---|---|
| 0.1720 | 0.6330 | 0.0120 | 0.0040 | 0.2620 | 0.0060 | 0.0090 | 0.0200 |

| C Eq. Long |
|---|
| 0.2830 |

| Mo | V | Co | Al | Nb | N | Pb | Sn | Ta | Ti |
|---|---|---|---|---|---|---|---|---|---|
| 0.0015 | 0.0012 | | | 0.0004 | | | | | |

**Additional Chemical Properties**

| | | | | |
|---|---|---|---|---|
| | | | | |

| CE CSA |
|---|
| N/A |

| Cr + Cu + Ni |
|---|
| 0.0350 |

**Mechanical Properties**

| Tensile (PSI) | Yield (PSI) | Elong. % in 2 in. or 4D | R of A % | HBW | HBW2 |
|---|---|---|---|---|---|
| 73019 | 48798 | 30.94 | | 123 | 125 |

**Charpy Minimum Impact - ft/lbs** **Fracture Appearance - %**

| Test 1 | Test 2 | Test 3 | Average | Test Temp. | Test Size | Test 1 | Test 2 | Test 3 | Average |
|---|---|---|---|---|---|---|---|---|---|
| | | | | | | | | | |

* Hydro test passed. at 2500 psi.
* Eddy Current test passed
* Bend test passed.

We hereby certify that these parts were manufactured, sampled, tested, and inspected in accordance with the product specifications stated and were found to meet the requirements.
This document is according to EN 10204 Inspection Certificate 3.1 requirements.
These products meet the requirements of the latest editions of NACE MR0175/ISO 15156 and NACE MR0103. No weld repair has been performed on these products. This material was not exposed to mercury or any other metal alloy that is liquid at ambient temperatures during processing or while in our possession.

Meets ASME SA 106 Grade B Requirements.